

<b>STN</b>	<b>Pracovná expozícia. Meranie prašnosti sypkých materiálov. Časť 2: Metóda rotačného bubna.</b>	<b>STN EN 15051-2</b>  83 3618
------------	--	--

Workplace exposure - Measurement of the dustiness of bulk materials - Part 2: Rotating drum method

Táto norma obsahuje anglickú verziu európskej normy.  
This standard includes the English version of the European Standard.

Obsahuje: EN 15051-2:2013

Spolu s STN EN 15051-1 a STN EN 15051-3 ruší  
STN EN 15051 (83 3618) z novembra 2006

**118704**

---

Úrad pre normalizáciu, metrológiu a skúšobníctvo SR, odbor SÚTN, 2014  
Podľa zákona č. 264/1999 Z. z. v znení neskorších predpisov sa môžu slovenské technické normy  
rozmnžovať a rozširovať iba so súhlasom Úradu pre normalizáciu, metrológiu a skúšobníctvo SR.

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**EN 15051-2**

November 2013

ICS 13.040.30

Supersedes EN 15051:2006

English Version

**Workplace exposure - Measurement of the dustiness of bulk  
materials - Part 2: Rotating drum method**

Exposition sur les lieux de travail - Mesurage du pouvoir de  
resuspension des matériaux pulvérulents en vrac - Partie 2:  
Méthode du tambour rotatif

Exposition am Arbeitsplatz - Messung des  
Staubungsverhaltens von Schüttgütern - Teil 2: Verfahren  
mit rotierender Trommel

This European Standard was approved by CEN on 28 September 2013.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

## Contents

	Page
Foreword.....	3
Introduction .....	4
1 Scope .....	5
2 Normative references .....	5
3 Terms and definitions .....	5
4 Requirements .....	5
4.1 General.....	5
4.2 Condition of the bulk material .....	6
4.3 Sample and environmental control.....	6
4.4 Moisture content.....	6
4.5 Bulk density.....	6
4.6 Test procedure .....	6
4.7 Replicate tests.....	6
4.8 Reporting .....	6
5 Rotating drum method .....	6
5.1 Description of test apparatus .....	6
5.2 Particle size-selective foams .....	8
5.3 Filters .....	8
5.4 Ancillary equipment .....	8
5.5 Preparation of test sample.....	8
5.6 Preparation of test apparatus.....	8
5.7 Running the test apparatus .....	9
5.8 Weighing the foams and filters .....	9
5.9 Determination of the inhalable, thoracic and respirable dustiness mass fractions.....	10
6 Evaluation of dustiness .....	10
7 Test report .....	11
Bibliography.....	12

## Foreword

This document (EN 15051-2:2013) has been prepared by Technical Committee CEN/TC 137 "Assessment of workplace exposure to chemical and biological agents", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2014, and conflicting national standards shall be withdrawn at the latest by May 2014.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document, together with EN 15051-1:2013 and EN 15051-3:2013, supersedes EN 15051:2006.

The major technical changes between this European Standard and the previous edition are as follows:

- a) EN 15051:2006 has been split in three parts (see below);
- b) the test methods given are no longer referred as reference test methods;
- c) the test of equivalence between an alternative (candidate) test method and any of the test methods now given in this European Standard and in EN 15051-3:2013 has been deleted.

EN 15051 *Workplace exposure – Measurement of the dustiness of bulk materials* consists of the following parts:

- *Part 1: Requirements and choice of test methods;*
- *Part 2: Rotating drum method;*
- *Part 3: Continuous drop method.*

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## Introduction

This European Standard gives details of the design and operation of the rotating drum test method that classifies the dustiness of solid bulk materials, in terms of health-related fractions.

A dustiness classification is presented to provide users (e.g. manufacturers, producers, occupational hygienists and workers) with information on the potential for dust emissions when the bulk material is handled or processed in workplaces. It provides the manufacturers of bulk materials with information that can help to improve their products. It allows the users of the bulk materials to assess the effects of pre-treatments, and also to select less dusty products, if available. It is envisaged that different branches of industry might develop their own classification schemes using experimentally determined dustiness values of the bulk materials of interest.

Although this European Standard does not discuss the analysis of dust released from bulk materials (except in terms of health-related fractions), the test method produces samples with the potential for chemical analysis of the contents.

This European Standard was developed based on the results of the European project SMT4-CT96-2074 "Development of a Method for Dustiness Testing" (see [1]). This project investigated the dustiness of 12 bulk materials, with the intention to test as wide a range of bulk materials as possible, i.e. magnitude of dustiness, industrial sectors, chemical composition and particle size distribution. Meanwhile the method has been applied to investigate the dustiness values of more than 220 different bulk materials.

## 1 Scope

This European Standard specifies the rotating drum test apparatus and associated test method for the reproducible production of dust from a bulk material under standard conditions, and the measurement of the inhalable, thoracic and respirable fractions of this dust, with reference to existing European Standards, where relevant (see Clause 6).

This method is suitable for general bulk material handling processes, including all those processes where the bulk material is dropped, or can be dropped. It differs from the continuous drop method presented in EN 15051-3 in this European Standard, the same bulk material is repeatedly dropped, while in EN 15051-3, the bulk material is dropped only once, but continuously.

Furthermore, this European Standard specifies the environmental conditions, the sample handling and analytical procedures, and the method of calculating and presenting the results. A classification scheme for dustiness is specified, to provide a standardised way to express and communicate the results to users of the bulk materials.

This European Standard is applicable to powdered, granular or pelletised bulk materials. A standard sample volume is used.

This European Standard is not applicable to test the dust released when solid bulk materials are mechanically reduced (e.g. cut, crushed) or to evaluate handling procedures for the bulk materials.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1540, *Workplace exposure - Terminology*

EN 15051-1:2013, *Workplace exposure - Measurement of the dustiness of bulk materials - Part 1: Requirements and choice of test methods*

EN 22768-1, *General tolerances - Part 1: Tolerances for linear and angular dimensions without individual tolerance indications (ISO 2768-1)*

ISO 15767, *Workplace atmospheres - Controlling and characterizing uncertainty in weighing collected aerosols*

**koniec náhľadu – text ďalej pokračuje v platenej verzii STN**