

	Výrobky založené na biomase. Prehľad metód na stanovenie obsahu založeného na biomase.	TNI CEN/TR 16721 65 9810
--	---	--

Bio-based products - Overview of methods to determine the bio-based content

Táto technická normalizačná informácia obsahuje anglickú verziu CEN/TR 16721:2014.
This Technical standard information includes the English version of CEN/TR 16721:2014.

Táto technická normalizačná informácia bola oznámená vo Vestníku ÚNMS SR č. 10/14

119673

Úrad pre normalizáciu, metrológiu a skúšobníctvo SR, odbor SÚTN, 2014
Tento dokument a ani jeho časti sa nesmú rozmnožovať a rozširovať v akejkoľvek podobe
a akýmkoľvek prostriedkami bez písomného povolenia ÚNMS SR.

ICS 13.020.60

English Version

Bio-based products - Overview of methods to determine the bio-based content

Produits biosourcés - Vue d'ensemble des méthodes pour
déterminer la teneur biosourcée

Biobasierte Produkte - Überblick über verfügbare und
mögliche Methoden und Techniken zur Bestimmung des
gesamten biobasierten Gehaltes von Produkten

This Technical Report was approved by CEN on 21 July 2014. It has been drawn up by the Technical Committee CEN/TC 411.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents		Page
Foreword.....		3
Introduction		4
1	Scope	5
2	Terms and definitions	5
3	Method using the radiocarbon analysis and elemental analysis	5
3.1	Background	5
3.2	Principle	6
3.3	Basic rules	6
3.3.1	Oxygen, hydrogen and nitrogen elements	6
3.3.2	Chemical reactions	6
3.3.3	Natural products	7
3.4	Test methods	7
3.5	Products obtained by chemical synthesis (Group 1)	7
3.5.1	General	7
3.5.2	Validation criteria	8
3.6	Formulated products (Group 2)	9
3.6.1	General	9
3.6.2	Calculation of the bio-based content of a sample	9
3.6.3	Calculation of the bio-based carbon content of a sample	10
3.6.4	Assessment of deviations of measured ^{14}C values from theoretical values	11
4	Methods based on measurement of stable isotopic ratio	11
4.1	General	11
4.1.1	Introduction	11
4.1.2	Material and Methods	12
4.2	$^{13}\text{C}/^{12}\text{C}$ isotope ratio	14
4.3	$^{18}\text{O}/^{16}\text{O}$ isotope ratio	14
4.3.1	Isotopic measurement of water	14
4.3.2	Isotopic measurements of organic samples	14
4.4	$^2\text{H}/^1\text{H}$ isotope ratio	15
4.5	$^{15}\text{N}/^{14}\text{N}$ Isotope ratio	15
4.6	Isotopes S	15
4.7	Multi-isotopic determinations	15
5	Method based on material balance	15
5.1	General	15
5.2	Principle	16
5.3	Examples	16
5.3.1	Paint formulation	16
5.3.2	Flexible insulation panel made from wood fibres	17
6	Applicability of the different methods	17
7	Recommendations	18
Annex A (informative) Isotope ratio tables		19
Bibliography		23

Foreword

This document (CEN/TR 16721:2014) has been prepared by Technical Committee CEN/TC 411 "Bio-based products", the secretariat of which is held by NEN.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

Introduction

Bio-based products from forestry and agriculture have a long history of application, such as paper, board and various chemicals and materials. The last decades have seen the emergence of new bio-based products in the market. Some of the reasons for the increased interest lie in the bio-based products' benefits in relation to the depletion of fossil resources and climate change. Bio-based products may also provide additional product functionalities. This has triggered a wave of innovation with the development of knowledge and technologies allowing new transformation processes and product development.

Acknowledging the need for common standards for bio-based products, the European Commission issued mandate M/492¹, resulting in a series of standards developed by CEN/TC 411, with a focus on bio-based products other than food, feed and biomass for energy applications.

The standards of CEN/TC 411 "Bio-based products" provide a common basis on the following aspects:

- Common terminology;
- Bio-based content determination;
- Life Cycle Assessment (LCA);
- Sustainability aspects;
- Declaration tools.

It is important to understand what the term bio-based product covers and how it is being used. The term "bio-based" means "derived from biomass". Bio-based products (bottles, insulation materials, wood and wood products, paper, solvents, chemical intermediates, composite materials, et cetera.) are products which are wholly or partly derived from biomass. It is essential to characterize the amount of biomass contained in the product by for instance its bio-based content or bio-based carbon content.

The bio-based content of a product does not provide information on its environmental impact or sustainability, which may be assessed through LCA and sustainability criteria. In addition, transparent and unambiguous communication within bio-based value chains is facilitated by a harmonized framework for certification and declaration.

The purpose of this Technical Report is provide an overview of methods for the determination of the bio-based content of solid, liquid and gaseous products.

The ability to determine the bio-based content of a product is an obvious prerequisite for developing the market for bio-based products. Currently, the bio-based content is usually derived from the determination of the bio-based carbon content by means of ¹⁴C measurement (as described in ASTM D6866-12 [1]). This methodology is used because ¹⁴C is measurable.

However, results based on the ¹⁴C methodology are expressed as a fraction of bio-based carbon on the total (organic) carbon content of the sample. In some cases the bio-based content of a product can differ substantially from the bio-based carbon content. For example, for products in which a fraction of the raw materials has been replaced by bio-based materials/constituents containing other elements such as oxygen, nitrogen or hydrogen (e.g. carbohydrate-based products), the bio-based carbon content may be substantially lower than the fraction of the product that is derived from biomass. This Technical Report describes three different methodologies to determine the bio-based content in a product and proposes the development of standards.

It should be noted that the quantification of the bio-based content is not a measure of sustainability of a bio-based product.

¹ A Mandate is a standardization task embedded in European trade laws. M/492 Mandate is addressed to the European Standardization bodies, CEN, CENELEC and ETSI, for the development of horizontal European Standards for bio-based products.

1 Scope

This Technical Report gives an overview of methods which can be used for the determination of the bio-based content of solid, liquid and gaseous products. It describes more specifically:

- a) a method using the radiocarbon analysis and elemental analysis: this method is based on a statement and a verification of the composition of the products;
- b) methods based on measurement of stable isotopic ratio; and
- c) a method based on the material balance.

This Technical Report gives guidance on the applicability of the different methods.

This Technical Report also gives recommendations for the further development of European Standards for the determination of the bio-based content.

koniec náhľadu – text ďalej pokračuje v platenej verzii STN