

<b>STN</b>	<b>Plasty. Termogravimetria (TG) polymérov. Časť 1: Všeobecné princípy (ISO 11358-1: 2014).</b>	<b>STN EN ISO 11358-1</b>  64 0747
------------	---	--

Plastics - Thermogravimetry (TG) of polymers - Part 1: General principles (ISO 11358-1:2014)

Táto norma obsahuje anglickú verziu európskej normy.  
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 03/15

Obsahuje: EN ISO 11358-1:2014, ISO 11358-1:2014

Oznámením tejto normy sa ruší  
STN EN ISO 11358 (64 0747) z augusta 2000

**120318**

---

Úrad pre normalizáciu, metrológiu a skúšobníctvo SR, odbor SÚTN, 2015  
Podľa zákona č. 264/1999 Z. z. v znení neskorších predpisov sa môžu slovenské technické normy rozmnožovať a rozširovať iba so súhlasom Úradu pre normalizáciu, metrológiu a skúšobníctvo SR.

EUROPEAN STANDARD

**EN ISO 11358-1**

NORME EUROPÉENNE

EUROPÄISCHE NORM

July 2014

ICS 83.080.01

Supersedes EN ISO 11358:1997

English Version

**Plastics - Thermogravimetry (TG) of polymers - Part 1: General principles (ISO 11358-1:2014)**Plastiques - Thermogravimétrie (TG) des polymères - Partie  
1: Principes généraux (ISO 11358-1:2014)Kunststoffe - Thermogravimetrie (TG) von Polymeren - Teil  
1: Allgemeine Grundsätze (ISO 11358-1:2014)

This European Standard was approved by CEN on 28 June 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

**Contents**

**Page**

Foreword.....3

## **Foreword**

This document (EN ISO 11358-1:2014) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2015, and conflicting national standards shall be withdrawn at the latest by January 2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 11358:1997.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

### **Endorsement notice**

The text of ISO 11358-1:2014 has been approved by CEN as EN ISO 11358-1:2014 without any modification.

---

---

**Plastics — Thermogravimetry (TG) of  
polymers —**

**Part 1:  
General principles**

*Plastiques — Thermogravimétrie (TG) des polymères —  
Partie 1: Principes généraux*





**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

<b>Foreword</b> .....	<b>iv</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>2</b>
<b>5 Apparatus</b> .....	<b>2</b>
<b>6 Test specimen preparation</b> .....	<b>2</b>
6.1 General.....	2
6.2 Test specimens from finished products.....	3
6.3 Test specimen conditioning.....	3
6.4 Test specimen mass.....	3
<b>7 Calibration</b> .....	<b>3</b>
7.1 Mass calibration.....	3
7.2 Temperature calibration.....	3
<b>8 Procedure</b> .....	<b>4</b>
8.1 General.....	4
8.2 Temperature scanning mode.....	4
8.3 Isothermal mode.....	5
<b>9 Expression of results</b> .....	<b>5</b>
9.1 Graphical representation.....	5
9.2 Determination of increase in mass.....	5
9.3 Determination of loss in mass.....	6
<b>10 Test report</b> .....	<b>8</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical chemical properties*.

This first edition of ISO 11358-1 cancels and replaces ISO 11358:1997, which has been technically revised.

The main changes are:

- a) addition of ISO 472 to the Normative references clause and removal of definitions specified therein;
- b) revision of apparatus specifications.

ISO 11358 consists of the following parts, under the general title *Plastics — Thermogravimetry (TG) of polymers*:

- *Part 1: General principles*
- *Part 2: Determination of activation energy*
- *Part 3: Determination of the activation energy using the Ozawa-Friedman plot and analysis of the reaction kinetics*

# Plastics — Thermogravimetry (TG) of polymers —

## Part 1: General principles

### 1 Scope

This part of ISO 11358 specifies general conditions for the analysis of polymers using thermogravimetric techniques. It is applicable to liquids or solids. Solid materials may be in the form of pellets, granules or powders. Fabricated shapes reduced to appropriate specimen size may also be analysed by this method.

Thermogravimetry can be used to determine the temperature(s) and rate(s) of decomposition of polymers, and to measure at the same time the amounts of volatile matter, additives and/or fillers they contain.

The thermogravimetric measurements may be carried out in dynamic mode (mass change versus temperature or time under programmed conditions) or isothermal mode (mass change versus time at constant temperature).

Thermogravimetric measurements may also be carried out using different testing atmospheres, e.g. to separate decomposition in an inert atmosphere from oxidative degradation.

### 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 472, *Plastics — Vocabulary*

ISO 11357-1, *Plastics — Differential scanning calorimetry (DSC) — Part 1: General principles*

**koniec náhľadu – text ďalej pokračuje v platenej verzii STN**