

<b>STN</b>	<b>Asfalty a asfaltové spojivá. Stanovenie odolnosti proti tvrdnutiu pôsobením tepla a vzduchu. Časť 2: Metóda TFOT.</b>	<b>STN EN 12607-2</b>  65 7070
------------	--	--

Bitumen and bituminous binders - Determination of the resistance to hardening under the influence of heat and air - Part 2: TFOT method

Táto norma obsahuje anglickú verziu európskej normy.  
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 04/15

Obsahuje: EN 12607-2:2014

Oznámením tejto normy sa ruší  
STN EN 12607-2 (65 7070) zo septembra 2007

**120616**

---

Úrad pre normalizáciu, metrológiu a skúšobníctvo SR, odbor SÚTN, 2015  
Podľa zákona č. 264/1999 Z. z. v znení neskorších predpisov sa môžu slovenské technické normy rozmnožovať a rozširovať iba so súhlasom Úradu pre normalizáciu, metrológiu a skúšobníctvo SR.

## English Version

## Bitumen and bituminous binders - Determination of the resistance to hardening under influence of heat and air - Part 2: TFOT method

Bitumes et liants bitumineux - Détermination de la résistance au durcissement sous l'effet de la chaleur et de l'air - Partie 2: Méthode TFOT

Bitumen und bitumenhaltige Bindemittel - Bestimmung der Beständigkeit gegen Verhärtung unter Einfluss von Wärme und Luft - Teil 2: TFOT-Verfahren

This European Standard was approved by CEN on 16 August 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

## Contents

Page

Foreword.....	3
1 Scope .....	4
2 Normative references .....	4
3 Principle .....	4
4 Apparatus .....	5
5 Sampling .....	6
6 Procedure .....	7
7 Calculation.....	7
8 Expression of results .....	8
9 Precision .....	8
10 Test report .....	9
Annex A (informative) Characteristics of thermometers.....	10
Bibliography .....	11

## Foreword

This document (EN 12607-2:2014) has been prepared by Technical Committee CEN/TC 336 "Bituminous binders", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2015 and conflicting national standards shall be withdrawn at the latest by May 2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12607-2:2007.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

In comparison with EN 12607-2:2007, the following significant changes have been made:

- changed/added wording of the Warning in the Scope;
- EN 12595, *Bitumen and bituminous binders — Determination of kinematic viscosity* has been added to Clause 2;
- the reference to mercury thermometer has been deleted (see subclause 4.2) and Annex A is informative.

EN 12607 consists of the following parts under the general title "*Bitumen and bituminous binders – Determination of the resistance to hardening under the influence of heat and air*":

- *Part 1: RTFOT method*;
- *Part 2: TFOT method*;
- *Part 3: RFT method*.

The scope of this standard has been enlarged by adding oxidized bitumens and hard industrial bitumens that are not used for paving applications. The reason is to facilitate that EN 13303, *Bitumen and bituminous binders – Determination of the loss of mass after heating of industrial bitumen* can be replaced in product standards by EN 12607-2 at the next revision of EN 13303.

It is to be noted that this – if so decided – will change the property from loss in mass into change in mass in EN 13304, *Bitumen and bituminous binders – Framework for specification of oxidized bitumens* and in EN 13305, *Bitumen and bituminous binders – Framework for specification of hard industrial bitumens*.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## 1 Scope

This part of EN 12607 specifies a method for measuring the combined effects of heat and air on a film of bitumen or bituminous binder, simulating the hardening which most bituminous binders undergo during mixing in an asphalt mixing plant. The method is suitable for other bituminous binders than paving grade bitumen, but the reference temperature might give excessive hardening that does not resemble real conditions during mixing at the plant. The method may not represent the hardening that occurs during mixing of warm mix binders.

Additionally, this part of EN 12607 specifies a method for the determination of the change in mass of oxidized bitumens and hard industrial bitumens after heating. The method is used to detect volatile components.

The method is referred to as TFOT, i.e. Thin Film Oven Test.

**WARNING — Use of this European Standard can involve hazardous materials, operations and equipment. This European Standard does not purport to address all of the safety problems associated with its use. It is the responsibility of the user of this European Standard to identify the hazards and assess the risks involved in performing this test method and to implement sufficient control measures to protect individual operators (and the environment). This includes appropriate safety and health practices and determination of the applicability of regulatory limitations prior to use.**

If there is a likelihood of volatile components being present in a binder, this procedure should not be used. It should not be used for cut-back bitumen or bituminous emulsions before these products have been stabilized, e.g. in accordance with EN 13074-2.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 58, *Bitumen and bituminous binders - Sampling bituminous binders*

EN 1425, *Bitumen and bituminous binders - Characterization of perceptible properties*

EN 12594, *Bitumen and bituminous binders - Preparation of test samples*

EN 12595, *Bitumen and bituminous binders - Determination of kinematic viscosity*

**koniec náhl'adu – text ďalej pokračuje v platenej verzii STN**