

STN	Kovové materiály. Skúška ťahom. Časť 3: Metóda skúšky pri nízkej teplote (ISO 6892-3: 2015).	STN EN ISO 6892-3 42 0310
------------	---	---

Metallic materials - Tensile testing - Part 3: Method of test at low temperature (ISO 6892-3:2015)

Táto norma obsahuje anglickú verziu európskej normy.
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 08/15

Obsahuje: EN ISO 6892-3:2015, ISO 6892-3:2015

121379

Úrad pre normalizáciu, metrológiu a skúšobníctvo SR, 2015
Podľa zákona č. 264/1999 Z. z. v znení neskorších predpisov sa môžu slovenské technické normy
rozmnžovať a rozširovať iba so súhlasom Úradu pre normalizáciu, metrológiu a skúšobníctvo SR.

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 6892-3

April 2015

ICS 77.040.10

English Version

Metallic materials - Tensile testing - Part 3: Method of test at low temperature (ISO 6892-3:2015)

Matériaux métalliques - Essai de traction - Partie 3:
Méthode d'essai à basse température (ISO 6892-3:2015)

Metallische Werkstoffe - Zugversuch - Teil 3: Prüfverfahren
bei tiefen Temperaturen (ISO 6892-3:2015)

This European Standard was approved by CEN on 3 January 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
Foreword.....	3

Foreword

This document (EN ISO 6892-3:2015) has been prepared by Technical Committee ISO/TC 164 "Mechanical testing of metals" in collaboration with Technical Committee ECISS/TC 101 "Test methods for steel (other than chemical analysis)" the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2015, and conflicting national standards shall be withdrawn at the latest by October 2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 6892-3:2015 has been approved by CEN as EN ISO 6892-3:2015 without any modification.

**Metallic materials — Tensile testing —
Part 3:
Method of test at low temperature**

*Matériaux métalliques — Essai de traction —
Partie 3: Méthode d'essai à basse température*





COPYRIGHT PROTECTED DOCUMENT

© ISO 2015

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols and designations	2
5 Principle	3
6 Test piece	3
7 Determination of original cross-sectional area (S_0)	3
8 Marking the original gauge length (L_0)	3
9 Apparatus	3
9.1 Force measuring system	3
9.2 Extensometer	3
9.3 Cooling device	3
9.3.1 General	3
9.3.2 Permitted deviations of temperature	4
9.3.3 Measurement of temperature	4
9.3.4 Verification of the temperature-measuring system	5
10 Test conditions	5
10.1 Setting the force zero point	5
10.2 Gripping of the test piece, fixing of the extensometer and cooling of the test piece, not necessarily in the following sequence	5
10.2.1 Method of gripping	5
10.2.2 Fixing of the extensometer and establishing the gauge length	5
10.2.3 Cooling of the test piece	6
10.3 Testing rate based on strain rate control (Method A)	6
10.3.1 General	6
10.3.2 Strain rate for the determination of the upper yield strength (R_{eH}) or proof strength properties (R_p and, if required, R_t)	6
10.3.3 Strain rate for the determination of the lower yield strength (R_{eL}) and percentage yield point extension (A_e) if required	7
10.3.4 Strain rate for the determination of the tensile strength (R_m), percentage elongation after fracture (A), percentage reduction area (Z), and, if required, percentage total extension at the maximum force (A_{gt}), percentage plastic extension at maximum force (A_g)	7
10.4 Method of testing with expanded strain rate ranges (Method B)	7
10.4.1 General	7
10.4.2 Rate for the determination of yield strength or proof strength properties	7
10.4.3 Rate for the determination of tensile strength	8
10.5 Choice of the method and rates	8
10.6 Documentation of the chosen testing conditions	8
11 Determination or calculation of the properties	8
12 Test report	8
13 Measurement uncertainty	9
14 Figures	10
15 Annexes	11
Annex A (informative) Addition to ISO 6892-1:2009, Annexes B and D	12

Annex B (informative) Example for cooling curves of steel depending on test piece dimensions and the specified test temperature in ethanol and liquid nitrogen	17
Annex C (informative) Measurement uncertainty	21
Bibliography	22

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT), see the following URL: [Foreword — Supplementary information](#).

The committee responsible for this document is ISO/TC 164, *Metallic materials*, Subcommittee SC 1, *Uniaxial testing*.

This first edition cancels and replaces ISO 15579:2000.

ISO 6892 consists of the following parts, under the general title *Metallic materials — Tensile testing*:

- *Part 1: Method of test at room temperature*
- *Part 2: Method of test at elevated temperature*
- *Part 3: Method of test at low temperature*
- *Part 4: Method of test in liquid helium*

Introduction

In this edition, there are two methods of testing speeds available. The first one, Method A, is based on strain rates (including crosshead separation rate) with narrow tolerances ($\pm 20\%$) and the second, Method B, is based on conventional strain rate ranges and tolerances. Method A is intended to minimize the variation of the test rates during the moment when strain rate sensitive parameters are determined and to minimize the measurement uncertainty of the test results.

Mechanical properties determined by tensile test at low temperatures have been determined at the same rates at room temperature. This revised part of ISO 6892 incorporates the new set of testing rates of ISO 6892-1 and ISO 6892-2, developed to reduce the variability of test results.

Metallic materials — Tensile testing —

Part 3:

Method of test at low temperature

WARNING — This International Standard calls for the use of substances and/or procedures that can be injurious to health if adequate safety measures are not taken. This International Standard does not address any health hazards, safety or environmental matters associated with its use. It is the responsibility of the user of this International Standard to establish appropriate health, safety and environmentally acceptable practices and take suitable actions for any national and international regulations. Compliance with this International Standard does not in itself confer immunity from legal obligations.

1 Scope

This part of ISO 6892 specifies a method of tensile testing of metallic materials at temperatures between +10 °C and -196 °C.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6892-1:2009, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*

ISO 7500-1, *Metallic materials — Verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Verification and calibration of the force-measuring system*

ISO 9513, *Metallic materials — Calibration of extensometer systems used in uniaxial testing*

koniec náhľadu – text ďalej pokračuje v platenej verzii STN