

STN	Kovové materiály. Prístrojová skúška tvrdosti a parametre materiálov. Časť 1: Skúšobná metóda (ISO 14577-1: 2015).	STN EN ISO 14577-1 42 0375
------------	---	--

Metallic materials - Instrumented indentation test for hardness and materials parameters - Part 1: Test method (ISO 14577-1:2015)

Táto norma obsahuje anglickú verziu európskej normy.
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 12/15

Obsahuje: EN ISO 14577-1:2015, ISO 14577-1:2015

Oznámením tejto normy sa ruší
STN EN ISO 14577-1 (42 0375) z apríla 2003

121921

Úrad pre normalizáciu, metrológiu a skúšobníctvo SR, 2016
Podľa zákona č. 264/1999 Z. z. v znení neskorších predpisov sa môžu slovenské technické normy
rozmnžovať a rozširovať iba so súhlasom Úradu pre normalizáciu, metrológiu a skúšobníctvo SR.

EUROPEAN STANDARD

EN ISO 14577-1

NORME EUROPÉENNE

EUROPÄISCHE NORM

July 2015

ICS 77.040.10

Supersedes EN ISO 14577-1:2002

English Version

**Metallic materials - Instrumented indentation test for hardness
and materials parameters - Part 1: Test method (ISO 14577-
1:2015)**

Matériaux métalliques - Essai de pénétration instrumenté
pour la détermination de la dureté et de paramètres des
matériaux - Partie 1 : Méthode d'essai (ISO 14577-1:2015)

Metallische Werkstoffe - Instrumentierte Eindringprüfung
zur Bestimmung der Härte und anderer Werkstoffparameter
- Teil 1: Prüfverfahren (ISO 14577-1:2015)

This European Standard was approved by CEN on 16 April 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

	Page
European foreword.....	3

European foreword

This document (EN ISO 14577-1:2015) has been prepared by Technical Committee ISO/TC 164 “Mechanical testing of metals” in collaboration with Technical Committee ECISS/TC 101 “Test methods for steel (other than chemical analysis)” the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2016, and conflicting national standards shall be withdrawn at the latest by January 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 14577-1:2002.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 14577-1:2015 has been approved by CEN as EN ISO 14577-1:2015 without any modification.

**Metallic materials — Instrumented
indentation test for hardness and
materials parameters —**

**Part 1:
Test method**

*Matériaux métalliques — Essai de pénétration instrumenté pour la
détermination de la dureté et de paramètres des matériaux —*

Partie 1: Méthode d'essai





COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Symbols and designations	2
4 Principle	4
5 Testing machine	4
6 Test piece	5
7 Procedure	5
8 Uncertainty of the results	8
9 Test report	9
Annex A (normative) Materials parameters determined from the force/indentation depth data set	11
Annex B (informative) Types of control use for the indentation process	24
Annex C (normative) Machine compliance and indenter area function	25
Annex D (informative) Notes on diamond indenters	27
Annex E (normative) Influence of the test piece surface roughness on the accuracy of the results	28
Annex F (informative) Correlation of indentation hardness H_{IT} to Vickers hardness	29
Annex G (normative) Drift and creep rate determination	31
Annex H (informative) Estimation of uncertainty of the calculated values of hardness and materials parameters	33
Annex I (normative) Calculation of radial displacement correction	43
Bibliography	45

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 164, *Mechanical testing of metals*, Subcommittee SC 3, *Hardness testing*.

This second edition cancels and replaces the first edition (ISO 14577-1:2002), which has been technically revised.

ISO 14577 consists of the following parts, under the general title *Metallic materials — Instrumented indentation test for hardness and materials parameters*:

- *Part 1: Test method*
- *Part 2: Verification and calibration of testing machines*
- *Part 3: Calibration of reference blocks*
- *Part 4: Test method for metallic and non-metallic coatings*

Introduction

Hardness has typically been defined as the resistance of a material to permanent penetration by another harder material. The results obtained when performing Rockwell, Vickers, and Brinell tests are determined after the test force has been removed. Therefore, the effect of elastic deformation under the indenter has been ignored.

ISO 14577 (all parts) has been prepared to enable the user to evaluate the indentation of materials by considering both the force and displacement during plastic and elastic deformation. By monitoring the complete cycle of increasing and removal of the test force, hardness values equivalent to traditional hardness values can be determined. More significantly, additional properties of the material, such as its indentation modulus and elasto-plastic hardness, can also be determined. All these values can be calculated without the need to measure the indent optically. Furthermore, by a variety of techniques, the instrumented indentation test allows to record hardness and modulus depth profiles within a, probably complex, indentation cycle.

ISO 14577 (all parts) has been written to allow a wide variety of post-test data analysis.

Metallic materials — Instrumented indentation test for hardness and materials parameters —

Part 1: Test method

1 Scope

This part of ISO 14577 specifies the method of instrumented indentation test for determination of hardness and other materials parameters for the following three ranges:

- macro range: $2\text{ N} \leq F \leq 30\text{ kN}$;
- micro range: $2\text{ N} > F$; $h > 0,2\text{ }\mu\text{m}$;
- nano range: $h \leq 0,2\text{ }\mu\text{m}$.

For the nano range, the mechanical deformation strongly depends on the real shape of indenter tip and the calculated material parameters are significantly influenced by the contact area function of the indenter used in the testing machine. Therefore, careful calibration of both instrument and indenter shape is required in order to achieve an acceptable reproducibility of the materials parameters determined with different machines.

The macro and micro ranges are distinguished by the test forces in relation to the indentation depth.

Attention is drawn to the fact that the micro range has an upper limit given by the test force (2 N) and a lower limit given by the indentation depth of 0,2 μm .

The determination of hardness and other material parameters is given in [Annex A](#).

At high contact pressures, damage to the indenter is possible. For this reason in the macro range, hardmetal indenters are often used. For test pieces with very high hardness and modulus of elasticity, permanent indenter deformation can occur and can be detected using suitable reference materials. It is necessary that its influence on the test result be taken into account.

This test method can also be applied to thin metallic and non-metallic coatings and non-metallic materials. In this case, it is recommended that the specifications in the relevant standards be taken into account (see also [6.3](#) and ISO 14577-4).

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 14577-2:2015, *Metallic materials — Instrumented indentation test for hardness and materials parameters — Part 2: Verification and calibration of testing machines*

ISO/IEC Guide 98-3:2008, *Uncertainty of measurement — Part 3: Guide to the expression of uncertainty in measurement (GUM:1995)*

koniec náhľadu – text ďalej pokračuje v platenej verzii STN