

STN	Jemná keramika (špeciálna keramika, špeciálna technická keramika). Mikroštruktúrna charakteristika. Časť 2: Stanovenie podielu objemu fáz vyhodnotením mikrografov (ISO 13383-2: 2012).	STN EN ISO 13383-2 72 7511
------------	--	--

Fine ceramics (advanced ceramics, advanced technical ceramics) - Microstructural characterization - Part 2: Determination of phase volume fraction by evaluation of micrographs (ISO 13383-2:2012)

Táto norma obsahuje anglickú verziu európskej normy.
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 09/16

Obsahuje: EN ISO 13383-2:2016, ISO 13383-2:2012

Oznámením tejto normy sa ruší
STN EN 623-5 (72 7511) z novembra 2009

123297

Úrad pre normalizáciu, metrológiu a skúšobníctvo SR, 2016
Podľa zákona č. 264/1999 Z. z. v znení neskorších predpisov sa môžu slovenské technické normy rozmnožovať a rozširovať iba so súhlasom Úradu pre normalizáciu, metrológiu a skúšobníctvo SR.

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 13383-2

April 2016

ICS 81.060.30

Supersedes EN 623-5:2009

English Version

Fine ceramics (advanced ceramics, advanced technical ceramics) - Microstructural characterization - Part 2: Determination of phase volume fraction by evaluation of micrographs (ISO 13383-2:2012)

Céramiques techniques - Caractérisation
microstructurale - Partie 2: Détermination de la
fraction volumique des phases par évaluation de
micrographies (ISO 13383-2:2012)

Hochleistungskeramik - Mikrostrukturelle
Charakterisierung - Teil 2: Bestimmung des
Volumenanteils von Phasen durch Auswertung von
Mikrogefügeaufnahmen (ISO 13383-2:2012)

This European Standard was approved by CEN on 19 March 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
European foreword.....	3

European foreword

The text of ISO 13383-2:2012 has been prepared by Technical Committee ISO/TC 206 “Fine ceramics” of the International Organization for Standardization (ISO) and has been taken over as EN ISO 13383-2:2016 by Technical Committee CEN/TC 184 “Advanced technical ceramics” the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2016, and conflicting national standards shall be withdrawn at the latest by October 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 623-5:2009.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 13383-2:2012 has been approved by CEN as EN ISO 13383-2:2016 without any modification.

**Fine ceramics (advanced ceramics,
advanced technical ceramics) —
Microstructural characterization —
Part 2:
Determination of phase volume
fraction by evaluation of micrographs**

Céramiques techniques — Caractérisation microstructurale —

*Partie 2: Détermination de la fraction volumique des phases par
évaluation de micrographes*





COPYRIGHT PROTECTED DOCUMENT

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Apparatus	2
4.1 Sectioning equipment.....	2
4.2 Mounting equipment.....	2
4.3 Grinding and polishing equipment.....	2
4.4 Microscope.....	2
4.5 Transparent grid.....	2
5 Test piece preparation	3
5.1 Sampling.....	3
5.2 Cutting.....	3
5.3 Mounting.....	3
5.4 Grinding and polishing.....	3
5.5 Etching.....	3
6 Photomicrography	4
6.1 General aspects.....	4
6.2 Inspection.....	4
6.3 Number of micrographs.....	4
6.4 Optical microscopy.....	4
6.5 Scanning electron microscopy.....	5
7 Measurement of micrographs	5
8 Calculation of results	6
9 Interferences and uncertainties	6
10 Test report	7
Annex A (informative) Use of automatic image analysis (AIA)	9
Annex B (informative) Round-robin verification of this procedure	10
Annex C (informative) Results sheet — ISO 13383-2	11
Bibliography	12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

ISO 13383-2 was prepared by Technical Committee ISO/TC 206, *Fine ceramics*.

ISO 13383 consists of the following parts, under the general title *Fine ceramics (advanced ceramics, advanced technical ceramics)* — *Microstructural characterization*:

- *Part 1: Determination of grain size and size distribution*
- *Part 2: Determination of phase volume fraction by evaluation of micrographs*

Fine ceramics (advanced ceramics, advanced technical ceramics) — Microstructural characterization —

Part 2:

Determination of phase volume fraction by evaluation of micrographs

1 Scope

This part of ISO 13383 specifies a manual method of making measurements for the determination of the volume fraction of major phases in fine ceramics (advanced ceramics, advanced technical ceramics) using micrographs of polished and etched sections, overlaying a square grid of lines, and counting the number of intersections lying over each phase.

NOTE 1 This method assumes that the true phase volume fractions are equivalent to area fractions on a randomly cut cross-section according to stereological principles.

NOTE 2 Guidelines for polishing and etching of advanced technical ceramics can be found in Annexes A and B of ISO 13383-1:2012.

The method applies to ceramics with one or more distinct secondary phases, such as found in $\text{Al}_2\text{O}_3/\text{ZrO}_2$, Si/SiC , or $\text{Al}_2\text{O}_3/\text{SiC}_w$.

If the test material contains discrete pores, these are to be treated as a secondary phase for the purpose of this method, provided that there is no evidence of grain pluck-out during polishing being confused with genuine pores.

NOTE 3 If the material contains more than about 20 % porosity, there is a strong risk that the microstructure will be damaged during the polishing process, and measurement of the volume fraction of pores may become misleading. Secondary phase volume fractions or porosity present at levels of less than 0,05 are subject to considerable error and potential scatter in results. A larger number of micrographs than the minimum of three is normally needed to improve the consistency and accuracy of the results.

NOTE 4 Many ceramics contain small amounts of secondary glassy phases. In order to make a reasonable estimate of glassy phase content, the glass material between crystalline grains should be readily observable, and thus should be at least 0,5 μm in width. The method in this part of ISO 13383 is not considered appropriate for narrow glassy films around grains.

NOTE 5 Microstructures are seldom homogeneous, and the phase contents can vary from micrograph to micrograph. It is essential to survey a sufficiently wide area of the prepared section to ensure that those areas selected for evaluation are representative, and do not contain eye-catching irregularities. This method assumes that the selected regions of a prepared cross-section are statistically representative of the whole sampled section.

Some users of this part of ISO 13383 may wish to apply automatic or semiautomatic image analysis to micrographs or directly captured microstructural images. This is currently outside the scope of this part, but some guidelines are given in Annex A.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO/IEC 17025, *General requirements for the competence of testing and calibration laboratories*

koniec náhľadu – text ďalej pokračuje v platenej verzii STN