

<b>STN</b>	<b>Geotextílie a geotextíliám podobné výrobky. Stanovenie dlhodobej ochranej účinnosti geotextílií v kontakte s geosyntetickými zábranami.</b>	<b>STN EN 13719</b>  80 6149
------------	--	--

Geosynthetics - Determination of the long term protection efficiency of geosynthetics in contact with geosynthetic barriers

Táto norma obsahuje anglickú verziu európskej normy.  
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 09/16

Obsahuje: EN 13719:2016

Oznámením tejto normy sa ruší  
STN EN 13719 (80 6149) z augusta 2003

**123303**

---

Úrad pre normalizáciu, metrológiu a skúšobníctvo SR, 2016  
Podľa zákona č. 264/1999 Z. z. v znení neskorších predpisov sa môžu slovenské technické normy  
rozmnožovať a rozširovať iba so súhlasom Úradu pre normalizáciu, metrológiu a skúšobníctvo SR.

EUROPEAN STANDARD

**EN 13719**

NORME EUROPÉENNE

EUROPÄISCHE NORM

April 2016

ICS 59.080.70; 91.100.50

Supersedes EN 13719:2002

English Version

## Geosynthetics - Determination of the long term protection efficiency of geosynthetics in contact with geosynthetic barriers

Géosynthétiques - Détermination de l'efficacité de protection à long terme des géosynthétiques en contact avec les géomembranes

Geokunststoffe - Bestimmung der langfristigen Schutzwirksamkeit von Geokunststoffen im Kontakt mit geosynthetischen Dichtungsbahnen

This European Standard was approved by CEN on 20 February 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

<b>Contents</b>		Page
European foreword.....		4
<b>1</b>	<b>Scope.....</b>	<b>5</b>
<b>2</b>	<b>Normative references.....</b>	<b>5</b>
<b>3</b>	<b>Terms and definitions.....</b>	<b>5</b>
<b>4</b>	<b>Principle.....</b>	<b>6</b>
<b>5</b>	<b>Apparatus.....</b>	<b>6</b>
<b>5.1</b>	<b>Cylinder.....</b>	<b>6</b>
<b>5.2</b>	<b>Lower steel plate.....</b>	<b>6</b>
<b>5.3</b>	<b>Dense rubber pad.....</b>	<b>6</b>
<b>5.4</b>	<b>Lead sheet.....</b>	<b>6</b>
<b>5.5</b>	<b>Simulated standard aggregate.....</b>	<b>6</b>
<b>5.6</b>	<b>Applied stress.....</b>	<b>6</b>
<b>5.7</b>	<b>Timing device.....</b>	<b>6</b>
<b>5.8</b>	<b>Deformation measurement.....</b>	<b>6</b>
<b>6</b>	<b>Specimen.....</b>	<b>8</b>
<b>6.1</b>	<b>Sampling.....</b>	<b>8</b>
<b>6.2</b>	<b>Number and dimensions of specimens.....</b>	<b>8</b>
<b>7</b>	<b>Conditioning.....</b>	<b>8</b>
<b>8</b>	<b>Procedure.....</b>	<b>8</b>
<b>9</b>	<b>Calculation.....</b>	<b>9</b>
<b>10</b>	<b>Test report.....</b>	<b>9</b>
<b>Annex A (normative) Determination of the deformation characteristics of the lead sheet used for recording local strains.....</b>		<b>10</b>
<b>A.1</b>	<b>Principle.....</b>	<b>10</b>
<b>A.2</b>	<b>Apparatus.....</b>	<b>10</b>
<b>A.3</b>	<b>Specimens.....</b>	<b>10</b>
<b>A.4</b>	<b>Procedure.....</b>	<b>10</b>
<b>A.5</b>	<b>Acceptance criteria.....</b>	<b>11</b>
<b>A.6</b>	<b>Test report.....</b>	<b>11</b>
<b>Annex B (informative) Performance Test.....</b>		<b>12</b>
<b>B.1</b>	<b>Scope.....</b>	<b>12</b>
<b>B.2</b>	<b>Definition.....</b>	<b>12</b>
<b>B.3</b>	<b>Principle.....</b>	<b>12</b>
<b>B.4</b>	<b>Apparatus.....</b>	<b>12</b>
<b>B.5</b>	<b>Specimens.....</b>	<b>12</b>
<b>B.6</b>	<b>Conditioning.....</b>	<b>12</b>
<b>B.7</b>	<b>Procedure.....</b>	<b>12</b>

<b>B.8</b>	<b>Calculation.....</b>	<b>13</b>
<b>B.9</b>	<b>Test report .....</b>	<b>14</b>

## **European foreword**

This document (EN 13719:2016) has been prepared by Technical Committee CEN/TC 189 “Geosynthetics”, the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2016, and conflicting national standards shall be withdrawn at the latest by October 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13719:2002.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## 1 Scope

This European Standard is an index test used to determine the efficiency with which a geosynthetic product will protect a geosynthetic barrier or other contact surface against the mechanical long term effects of static point loads.

The test is performed on the geosynthetic product in isolation. It measures the strains experienced by a geosynthetic product in contact with a deformable pad.

NOTE Other properties relevant to the protection of geosynthetic barriers against differing actions are covered by other standards, e.g. dynamic perforation is covered in EN ISO 13433.

A related performance test simulating specific site conditions is described in Annex B (informative).

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12588, *Lead and lead alloys — Rolled lead sheet for building purposes*

EN ISO 139, *Textiles — Standard atmospheres for conditioning and testing (ISO 139)*

EN ISO 9862, *Geosynthetics — Sampling and preparation of test specimens (ISO 9862)*

EN ISO 10320, *Geotextiles and geotextile-related products — Identification on site (ISO 10320)*

ISO 7619-1, *Rubber, vulcanized or thermoplastic — Determination of indentation hardness — Part 1: Durometer method (Shore hardness)*

**koniec náhľadu – text ďalej pokračuje v platenej verzii STN**