

STN	Hliník a zliatiny hliníka Tvárnené výrobky Označovanie stavov	STN EN 515 42 0053
------------	--	--------------------------------------

Aluminium and aluminium alloys - Wrought products - Temper designations

Táto norma obsahuje anglickú verziu európskej normy.
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 08/17

Obsahuje: EN 515:2017

Oznámením tejto normy sa ruší
STN EN 515 (42 0053) z júna 2003

125411

Úrad pre normalizáciu, metrológiu a skúšobníctvo Slovenskej republiky, 2017
Podľa zákona č. 264/1999 Z. z. o technických požiadavkách na výrobky a o posudzovaní zhody a o zmene a doplnení niektorých zákonov v znení neskorších predpisov sa slovenská technická norma a časti slovenskej technickej normy môžu rozmnožovať alebo rozširovať len so súhlasom slovenského národného normalizačného orgánu.

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 515

March 2017

ICS 01.040.77; 77.120.10; 77.150.01

Supersedes EN 515:1993

English Version

**Aluminium and aluminium alloys - Wrought products -
Temper designations**

Aluminium et alliages d'aluminium - Produits corroyés
- Désignation des états métallurgiques

Aluminium und Aluminiumlegierungen - Halbzeug -
Bezeichnungen der Werkstoffzustände

This European Standard was approved by CEN on 6 February 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

European foreword.....	3
1 Scope	4
2 Normative references.....	4
3 Terms and definitions	4
4 Basis of codification	6
5 Basic temper designations.....	6
5.1 F – as fabricated	6
5.2 O – Annealed	6
5.3 H – Strain-hardened	6
5.4 W – Solution heat-treated	7
5.5 T – Thermally treated to produce stable tempers other than F, O or H (for heat-treatable alloys only)	7
6 Subdivision of O (annealed) temper designations.....	7
6.1 O ₁ – High temperature annealed and slow cooled	7
6.2 O ₂ – Thermo-mechanically processed	7
6.3 O ₃ – Homogenized	7
7 Subdivision of H (strain-hardened) temper designations	7
8 Subdivision of T (thermally treated to produce stable tempers other than F, O or H) temper designations	10
8.1 First digit after T.....	10
8.2 Additional digits added to designations T1 to T10	12
8.3 Assigned additional digits for stress-relieved T tempers	12
8.3.1 Stress-relieved by stretching	12
8.3.2 Stress-relieved by compressing	13
8.3.3 Stress-relieved by combined stretching and compressing.....	13
8.3.4 Assigned additional digits for stress-relieved W tempers	13
8.4 Assigned additional digits for variations of T7 type tempers.....	13
8.5 Demonstration of response to heat treatment.....	14
8.5.1 Temper designations for producer/supplier — Laboratory demonstration of response to heat treatment.....	14
8.5.2 Temper designations for producer/supplier — Demonstration of response to temper conversion	14
8.5.3 Temper designations for purchaser/user heat treatment	14
9 Summary	14
Annex A (informative) Recommendations for further T tempers extensions	23
A.1 Numeral 1 as a second digit after T	23
A.2 Numerals 1 and 3 to 9 as a second digit after T3, T8 or T9	23
A.3 Numerals 1 and 3 to 5 as a second digit after T5 or T6	23
A.4 Numeral 6 as a second digit after T5 or T6	23
A.5 Summary of possible uses of a second digit after T	23
Bibliography	25

European foreword

This document (EN 515:2017) has been prepared by Technical Committee CEN/TC 132 “Aluminium and aluminium alloys”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2017, and conflicting national standards shall be withdrawn at the latest by September 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 515:1993.

The following modifications were implemented in this new version of EN 515:

- Addition of Clause 2 “Normative references”;
- new definitions and sources in Clause 3;
- new precision in Subclauses 6.1, 7 and 7.3;
- new Table 1 and modification of Table 2;
- improvement of the content of Clause 8.4;
- modification of Figure 1;
- inclusion of new tempers in Table 3: T552, T554, T72, T72510, T72511, T74511, T7452, T7454, T7752, T7754, T7852, T7854, T7952 and T7954;
- modification of new tempers in Table 3: H131, T3510;
- updating Annex A.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard establishes temper designations for all forms of wrought aluminium and aluminium alloys and for continuously cast aluminium and aluminium alloys drawing stock and strip intended to be wrought.

NOTE Some of these temper designations may be subject of patent or patent applications and their listing herein is not to be construed in any way as the granting of a license under such patent right.

Additional temper designations, conforming to this standard, may be standardized with CEN/TC 132 and AECMA/5 provided:

- the temper is used or is available for use by more than one user;
- mechanical property limits are defined;
- the characteristics of the temper are significantly different from those of all other tempers which have the same sequence of basic treatments and for which designations already have been assigned for the same alloy and product;
- the following are also defined if characteristics other than mechanical properties are considered significant:
 - a) test methods and limits for the characteristics; or
 - b) the specific practices used to produce the temper.

2 Normative references

Not applicable.

koniec náhľadu – text ďalej pokračuje v platenej verzii STN