

STN	Prepravné fľaše na plyn Kompatibilita fľašových a ventilových materiálov s plynovým obsahom Časť 4: Skúšobné metódy na vybrané kovové materiály odolné proti vodíkovej krehkosti (ISO 11114-4: 2017)	STN EN ISO 11114-4 07 8609
------------	---	--

Transportable gas cylinders - Compatibility of cylinder and valve materials with gas contents - Part 4: Test methods for selecting steels resistant to hydrogen embrittlement (ISO 11114-4:2017)

Táto norma obsahuje anglickú verziu európskej normy.
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 09/17

Obsahuje: EN ISO 11114-4:2017, ISO 11114-4:2017

Oznámením tejto normy sa ruší
STN EN ISO 11114-4 (07 8609) z novembra 2005

125500

Úrad pre normalizáciu, metrológiu a skúšobníctvo Slovenskej republiky, 2017
Podľa zákona č. 264/1999 Z. z. o technických požiadavkách na výrobky a o posudzovaní zhody a o zmene a doplnení niektorých zákonov v znení neskorších predpisov sa slovenská technická norma a časti slovenskej technickej normy môžu rozmnožovať alebo rozširovať len so súhlasom slovenského národného normalizačného orgánu.

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 11114-4

April 2017

ICS 23.020.35

Supersedes EN ISO 11114-4:2005

English Version

**Transportable gas cylinders - Compatibility of cylinder and
valve materials with gas contents - Part 4: Test methods
for selecting steels resistant to hydrogen embrittlement
(ISO 11114-4:2017)**

Bouteilles à gaz transportables - Compatibilité des
matériaux et des robinets avec les contenus gazeux -
Partie 4: Méthodes d'essai pour le choix des aciers
résistants à la fragilisation par l'hydrogène (ISO
11114-4:2017)

Ortsbewegliche Gasflaschen - Verträglichkeit von
Werkstoffen für Gasflaschen und Ventile mit den in
Berührung kommenden Gasen - Teil 4: Prüfverfahren
zur Auswahl von Stählen, die gegen
Wasserstoffversprödung unempfindlich sind (ISO
11114-4:2017)

This European Standard was approved by CEN on 8 December 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
European foreword.....	3

European foreword

This document (EN ISO 11114-4:2017) has been prepared by Technical Committee ISO/TC 58 “Gas cylinders” in collaboration with Technical Committee CEN/TC 23 “Transportable gas cylinders” the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2017, and conflicting national standards shall be withdrawn at the latest by October 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 11114-4:2005.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 11114-4:2017 has been approved by CEN as EN ISO 11114-4:2017 without any modification.

**Transportable gas cylinders —
Compatibility of cylinder and valve
materials with gas contents —**

**Part 4:
Test methods for selecting steels
resistant to hydrogen embrittlement**

Bouteilles à gaz transportables — Compatibilité des matériaux et des robinets avec les contenus gazeux —

Partie 4: Méthodes d'essai pour le choix des aciers résistants à la fragilisation par l'hydrogène



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms, definitions, symbols and abbreviated terms	2
3.1 Terms and definitions	2
3.2 Symbols and abbreviated terms	3
4 General requirements	3
5 Test methods	4
5.1 Disc test (method A)	4
5.1.1 Principle of test	4
5.1.2 Test conditions and procedure	4
5.1.3 Treatment and interpretation of test results	6
5.1.4 Failure in conducting test	7
5.1.5 Test report	7
5.2 Fracture mechanics test (method B)	10
5.2.1 Principle of the test method	10
5.2.2 Test procedure	10
5.2.3 Test results	14
5.3 Test method to determine the resistance to hydrogen assisted cracking of steel cylinders (method C)	14
5.3.1 General	14
5.3.2 Specimen configurations and numbers of tests	15
5.3.3 Fatigue precracking	15
5.3.4 Specimen testing procedure	15
5.3.5 Test procedure	16
5.3.6 Crack growth examination	16
5.3.7 Cylinder material qualification	17
5.3.8 Failure in conducting test	17
5.3.9 Test report	17
5.4 Tensile tests	17
Bibliography	18

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is ISO/TC 58, *Gas cylinders*.

This second edition cancels and replaces the first edition (ISO 11114-4:2005), which has been technically revised with the following changes:

- improvement of the procedure corresponding to Method C and adjustment of acceptance criteria;
- light modifications on procedures corresponding to Method A and Method B.

A list of parts in the ISO 11114 series can be found on the ISO website.

Introduction

It is widely recognized that compressed hydrogen and some hydrogen bearing gases can have an embrittling effect on steels. This embrittling effect has resulted in the failure of hydrogen gas cylinders (including some bursts) that has led gas cylinder users and manufacturers to adopt specific measures.

The adoption of these measures has eliminated all known failures of hydrogen cylinders from this embrittlement phenomenon as far has been reported.

The basic recommendation is to limit the tensile strength of the steels (see ISO 11114-1) and eliminate manufacturing defects.

This tensile strength limit of 950 MPa was developed for quenched and tempered gas cylinders of 34 Cr Mo 4 type steels using steelmaking practices, chemistry and manufacturing techniques typical of those used during the early 1980's and successfully used for filling pressures up to 300 bar. This practice has been in widescale use up to the current time. Other higher pressures, although at lower tensile strength limits, have also been used.

In recent years, improvements in steelmaking, e.g. by reducing the sulphur and phosphorus contents, have indicated the possibility of increasing the tensile strength limit of 950 MPa for embrittling gas service. Experimental work has shown that the relevant parameters affecting hydrogen embrittlement are the following:

- a) microstructure resulting from the combination of the chemistry and the heat treatment;
- b) mechanical properties of the material;
- c) applied stress;
- d) internal surface imperfections resulting in local stress concentrations;
- e) characteristics of the gas contained (composition, quality, pressure, etc.).

When developing this document, only the material aspects, a) and b) and the characteristics of the gas e) above, were considered. Other essential features, c) and d), are covered by the relevant parts of ISO 9809.

Some low alloy steels other than 34 Cr Mo 4 may require tensile strength to be lower than 950 MPa, or may be permitted to be higher than 950 MPa, to be suitable for the manufacture of gas cylinders for embrittling gas service.

This document specifies test methods to identify steels which, when combined with the cylinder manufacturing requirements specified in ISO 9809 (all parts), will result in cylinders suitable for use in embrittling gas service.

These tests have been developed following an extensive world-wide programme which incorporated laboratory and full scale tests. See also AFNOR FD E29-753.

Transportable gas cylinders — Compatibility of cylinder and valve materials with gas contents —

Part 4: Test methods for selecting steels resistant to hydrogen embrittlement

1 Scope

This document specifies test methods and the evaluation of results from these tests in order to qualify steels suitable for use in the manufacture of gas cylinders (up to 3 000 l) for hydrogen and hydrogen bearing embrittling gases.

This document only applies to seamless steel gas cylinders.

The requirements of this document are not applicable if at least one of the following conditions for the intended gas service is fulfilled:

- the working pressure of the filled embrittling gas is less than 20 % of the test pressure of the cylinder;
- the partial pressure of the filled embrittling gas of a gas mixture is less than 5 MPa (50 bar) in the case of hydrogen and other embrittling gases, with the exception of hydrogen sulphide and methyl mercaptan; in such cases, the partial pressure shall not exceed 0,25 MPa (2,5 bar).

NOTE In such cases, it is possible to design the cylinder as for ordinary (non-embrittling) gases.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 7539-1, *Corrosion of metals and alloys — Stress corrosion testing — Part 1: General guidance on testing procedures*

ISO 7539-6:2011, *Corrosion of metals and alloys — Stress corrosion testing — Part 6: Preparation and use of precracked specimens for tests under constant load or constant displacement*

ISO 9809-1, *Gas cylinders — Refillable seamless steel gas cylinders — Design, construction and testing — Part 1: Quenched and tempered steel cylinders with tensile strength less than 1 100 MPa*

ISO 9809-2, *Gas cylinders — Refillable seamless steel gas cylinders — Design, construction and testing — Part 2: Quenched and tempered steel cylinders with tensile strength greater than or equal to 1 100 MPa*

ISO 11114-1:2012, *Gas cylinders — Compatibility of cylinder and valve materials with gas contents — Part 1: Metallic materials*

ISO 11120, *Gas cylinders — Refillable seamless steel tubes of water capacity between 150 l and 3000 l — Design, construction and testing*

koniec náhľadu – text ďalej pokračuje v platenej verzii STN