

STN	Metalografické stanovenie obsahu nekovových prímeskov v oceliach použitím štandardných obrazov	STN EN 10247 42 0471
------------	---	--

Micrographic examination of the non-metallic inclusion content of steels using standard pictures

Táto norma obsahuje anglickú verziu európskej normy.
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 12/17

Obsahuje: EN 10247:2017

Oznámením tejto normy sa ruší
STN EN 10247 (42 0471) zo septembra 2007

125945

Úrad pre normalizáciu, metrológiu a skúšobníctvo Slovenskej republiky, 2018
Podľa zákona č. 264/1999 Z. z. o technických požiadavkách na výrobky a o posudzovaní zhody a o zmene a doplnení niektorých zákonov v znení neskorších predpisov sa slovenská technická norma a časti slovenskej technickej normy môžu rozmnožovať alebo rozširovať len so súhlasom slovenského národného normalizačného orgánu.

EUROPEAN STANDARD

EN 10247

NORME EUROPÉENNE

EUROPÄISCHE NORM

July 2017

ICS 77.040.99

Supersedes EN 10247:2007

English Version

Micrographic examination of the non-metallic inclusion content of steels using standard pictures

Détermination micrographique de la teneur en
inclusions non-métalliques des aciers à l'aide d'images-
types

Metallographische Prüfung des Gehaltes
nichtmetallischer Einschlüsse in Stählen mit Bildreihen

This European Standard was approved by CEN on 18 January 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
European foreword.....	5
Introduction	6
1 Scope.....	7
2 Normative references.....	7
3 Terms and definitions	7
4 Symbols and abbreviations	10
5 Principles	12
6 Brief practical guide.....	13
6.1 Basic rules for evaluation.....	13
6.2 Evaluation according to the default rating methods	14
7 Sampling.....	14
7.1 General.....	14
7.2 Degree of reduction.....	15
7.3 Size and location of test area	15
7.4 Number of specimens	15
7.5 Preparation of specimens	16
8 Test method	16
8.1 Magnification.....	16
8.2 Microscope settings for image analysis and manual analysis	16
8.3 Field of view	17
8.4 Definition of the pictures of the chart.....	17
8.4.1 Size and Shape.....	17
8.4.2 Parameters	17
8.4.3 Arrangement of the pictures.....	17
8.5 Procedure.....	18
8.5.1 General.....	18
8.5.2 Several inclusions of mixed sizes in one field.....	18
8.5.3 Scanning	18
8.5.4 Assessment and evaluation	19
8.5.5 Evaluation of different types of inclusions	19
8.5.6 Recording of results	19
9 Types of assessment.....	19
9.1 Worst inclusion method: method P	19
9.1.1 Principle	19
9.1.2 Evaluation of P_L (worst length)	20
9.1.3 Evaluation of P_d (worst diameter).....	20
9.1.4 Evaluation of P_a (worst area)	20
9.2 Worst field method: method M.....	20
9.2.1 Principle	20
9.2.2 Evaluation of M_n (rating according to number)	20
9.2.3 Evaluation of M_L (rating according to length).....	20

9.2.4	Evaluation of M_D (rating according to diameter).....	20
9.2.5	Evaluation of M_a (rating according to area)	21
9.3	Average field method: method K.....	21
9.3.1	Principle.....	21
9.3.2	Scanning of a specimen for average field assessment.....	21
9.3.3	Evaluation.....	21
9.3.4	Evaluation of K_n , K_L for elongated and K_n , K_d for globular inclusions.....	21
9.3.5	Evaluation of K_n and K_a	22
10	Test report	22
Annex A (normative) Type of inclusions		34
Annex B (normative) Parameters and assessments to be used if not otherwise specified		37
Annex C (informative) Examples for inclusions of different types		38
Annex D (informative) Shape factor		42
Annex E (informative) Examples for magnification		43
Annex F (informative) Details of the eyepiece graticules		45
Annex G (normative) Manufacturing specifications of the eyepiece graticule.....		46
G.1	General	46
G.2	Narrow field microscopes.....	46
G.3	Broad field microscopes.....	48
Annex H (normative) Calculation basis for the pictures of the chart		50
Annex I (normative) Rules for classification		52
I.1	Definition of classes	52
I.2	Classification of length.....	52
I.3	Classification of width.....	52
I.4	Classification of diameter	52
Annex J (informative) Comparison of inclusion types in different standards.....		53
Annex K (informative) Worst inclusion assessment.....		54
Annex L (informative) Worst field assessment.....		58
L.1	General	58
L.2	Evaluation of M_n	58
L.3	Evaluation of M_n , M_L and M_d	58
L.4	Evaluation of M_n and M_a	58
Annex M (informative) Average field assessment		62
M.1	General	62
M.2	Evaluation of K_n , K_L and K_d	62
M.3	Evaluation of K_n and K_a	62
M.4	Restricted assessment	62

Annex N (normative) Calculation basis for the assessment.....	74
N.1 Worst inclusion assessment.....	74
N.2 Worst field assessment	74
N.3 Average field	75
Annex O (informative) Edge Errors correction	77
O.1 General.....	77
O.2 Measurement.....	77
O.3 Large inclusions.....	77
Annex P (normative) Calculation of average values of parameters for one class.....	79
Annex Q (normative) Average values of parameters	80
Bibliography.....	81

European foreword

This document (EN 10247:2017) has been prepared by Technical Committee ECiSS/TC 101 “Test methods for steel (other than chemical analysis)”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2018, and conflicting national standards shall be withdrawn at the latest by January 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 10247:2007.

The many changes in the current revision result from only a few basic adjustments. The length to width limit ratio for globular inclusions has been changed from 1,3 to 3 (Annex I), and the mathematical principles underlying the chart have been more clearly defined (Annex H). These two changes have led to many numerical changes in Table 2 and Figure 11, where moreover some classes have been deleted and others added. The rules of assessment have changed, most notably to allow stringer formation from two particles upward (Subclause 3.1.2, Annex B), to exclude stringer formation between a stringer and a single particle (Subclause 3.1.2), and to consistently define the classification of inclusions by shape, arrangement, and colour (Clause 3, Annexes A and B). Finally, the assessment and recording sheets have been redesigned to simplify manual use (Annexes K, L, and M).

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

This document establishes procedures for the assessment of inclusions in steels, based on their morphology using standard pictures.

These procedures include principles that yield results coherent with consolidated individual inclusion measurements and expressed in physical units.

The chart of standard pictures is derived from mathematical principles. In distinction to other inclusion rating standards, in this standard the order of the classification begins with the length (row index q).

The results may be directly computed from field assessments. The same precision level is achieved by using the same method in manual evaluation and computer controlled measurements.

The results are in physical units: length in $\mu\text{m}/\text{mm}^2$, number/ mm^2 , areas in $\mu\text{m}^2/\text{mm}^2$.

1 Scope

This European Standard defines a method of microscopic non-metallic endogenous inclusion assessment using picture charts.

The method does not apply to particles of a length or diameter less than 3,0 μm or a width smaller than 2,0 μm . If defined by a product standard or agreement between the involved parties for certain special products, inclusions with a width below 2,0 μm can be evaluated by length alone. Inclusions with dimensions exceeding the upper limits in Table 2 are evaluated as belonging to the maximum class and noted separately with their true dimensions (see 8.5.6).

It is assumed, if particles are elongated or if there are stringers of particles, that they are parallel to each other. Other arrangements are not covered by this draft standard. This draft European Standard applies to samples with a microscopic precipitation approaching random distribution.

From the data of measurements obtained by this method, evaluation according to other standards can be established.

This draft European Standard does not apply to free cutting steels.

NOTE The basic principle of this draft European Standard allows the determination of non-metallic inclusion content by image analysis techniques.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN ISO/IEC 17025, *General requirements for the competence of testing and calibration laboratories (ISO/IEC 17025)*

ISO 9042, *Steels — Manual point counting method for statistically estimating the volume fraction of a constituent with a point grid*

koniec náhľadu – text ďalej pokračuje v platenej verzii STN