

STN	Kontinuálne lakované kovy Skúšobné metódy Časť 8: Odolnosť proti soľnej hmle	STN EN 13523-8 03 8761
------------	---	--

Coil coated metals - Test methods - Part 8: Resistance to salt spray (fog)

Táto norma obsahuje anglickú verziu európskej normy.
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 01/18

Obsahuje: EN 13523-8:2017

Oznámením tejto normy sa ruší
STN EN 13523-8 (03 8761) zo septembra 2010

125999

Úrad pre normalizáciu, metrológiu a skúšobníctvo Slovenskej republiky, 2018
Podľa zákona č. 264/1999 Z. z. o technických požiadavkách na výrobky a o posudzovaní zhody a o zmene a doplnení niektorých zákonov v znení neskorších predpisov sa slovenská technická norma a časti slovenskej technickej normy môžu rozmnožovať alebo rozširovať len so súhlasom slovenského národného normalizačného orgánu.

EUROPEAN STANDARD

EN 13523-8

NORME EUROPÉENNE

EUROPÄISCHE NORM

July 2017

ICS 25.220.60

Supersedes EN 13523-8:2010

English Version

Coil coated metals - Test methods - Part 8: Resistance to salt spray (fog)

Tôles prélaquées - Méthodes d'essais - Partie 8 :
Résistance au brouillard salin

Bandbeschichtete Metalle - Prüfverfahren - Teil 8:
Beständigkeit gegen Salzsprühnebel

This European Standard was approved by CEN on 21 May 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents		Page
European foreword		3
1	Scope	5
2	Normative references	5
3	Terms and definitions	5
4	Principle	6
5	Apparatus	7
6	Sampling	7
7	Test panels	7
7.1	General	7
7.2	Option 1	8
7.3	Option 2	8
8	Procedure	9
8.1	Test conditions	9
8.2	Exposure of test panels	9
8.3	Evaluation	10
8.3.1	General	10
8.3.2	Blistering	10
8.3.3	Corrosion and/or delamination	10
9	Expression of results	10
10	Precision	11
11	Test report	11
Bibliography		12

European foreword

This document (EN 13523-8:2017) has been prepared by Technical Committee CEN/TC 139 "Paints and varnishes", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2018, and conflicting national standards shall be withdrawn at the latest by January 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13523-8:2010.

The main changes compared to the previous edition are:

- a) definitions for the following terms were implemented from EN ISO 4628-8: holiday, artificial defect, circular defect, scribe, corroded area, delaminated area;
- b) definitions for edge and general surface were added;
- c) the term creep corrosion was changed to corrosion;
- d) use of a hole punch for application of the hole was added;
- e) EN ISO 4628-8 was introduced for the inspection of delamination and corrosion around the scribe;
- f) the text has been editorially revised and the normative references have been updated.

The EN 13523 series, *Coil coated metals — Test methods*, consists of the following parts:

- *Part 0: General introduction*
- *Part 1: Film thickness*
- *Part 2: Gloss*
- *Part 3: Colour difference — Instrumental comparison*
- *Part 4: Pencil hardness*
- *Part 5: Resistance to rapid deformation (impact test)*
- *Part 6: Adhesion after indentation (cupping test)*
- *Part 7: Resistance to cracking on bending (T-bend test)*
- *Part 8: Resistance to salt spray (fog)*
- *Part 9: Resistance to water immersion*
- *Part 10: Resistance to fluorescent UV radiation and water condensation*

EN 13523-8:2017 (E)

- *Part 11: Resistance to solvents (rubbing test)*
- *Part 12: Resistance to scratching*
- *Part 13: Resistance to accelerated ageing by the use of heat*
- *Part 14: Chalking (Helmen method)*
- *Part 15: Metamerism*
- *Part 16: Resistance to abrasion*
- *Part 17: Adhesion of strippable films*
- *Part 18: Resistance to staining*
- *Part 19: Panel design and method of atmospheric exposure testing*
- *Part 20: Foam adhesion*
- *Part 21: Evaluation of outdoor exposed panels*
- *Part 22: Colour difference — Visual comparison*
- *Part 23: Resistance to humid atmospheres containing sulfur dioxide*
- *Part 24: Resistance to blocking and pressure marking*
- *Part 25: Resistance to humidity*
- *Part 26: Resistance to condensation of water*
- *Part 27: Resistance to humid poultice (Cataplasm test)*
- *Part 29: Resistance to environmental soiling (Dirt pick-up and striping)*

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This part of the EN 13523 series specifies the procedures for determining the resistance to salt spray (fog) of an organic coating on a metallic substrate (coil coating).

For steel, neutral salt spray (fog) is usually used, and for aluminium, acetic acid salt spray (fog).

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 13523-0, *Coil coated metals - Test methods - Part 0: General introduction*

EN 13523-7:2014, *Coil coated metals - Test methods - Part 7: Resistance to cracking on bending (T-bend test)*

EN 13523-19:2011, *Coil coated metals - Test methods - Part 19: Panel design and method of atmospheric exposure testing*

EN 60454-2, *Pressure-sensitive adhesive tapes for electrical purposes — Part 2: Methods of test (IEC 60454-2)*

EN ISO 3696, *Water for analytical laboratory use - Specification and test methods (ISO 3696)*

EN ISO 4628-2, *Paints and varnishes - Evaluation of degradation of coatings - Designation of quantity and size of defects, and of intensity of uniform changes in appearance - Part 2: Assessment of degree of blistering (ISO 4628-2)*

EN ISO 4628-8:2012, *Paints and varnishes - Evaluation of degradation of coatings - Designation of quantity and size of defects, and of intensity of uniform changes in appearance - Part 8: Assessment of degree of delamination and corrosion around a scribe or other artificial defect (ISO 4628-8:2012)*

EN ISO 9227:2017, *Corrosion tests in artificial atmospheres - Salt spray tests (ISO 9227:2017)*

EN ISO 17872, *Paints and varnishes - Guidelines for the introduction of scribe marks through coatings on metallic panels for corrosion testing (ISO 17872)*

koniec náhľadu – text ďalej pokračuje v platenej verzii STN