

<b>STN</b>	<b>Rezivo</b> <b>Hodnotenie kvality sušenia</b>	<b>STN</b> <b>EN 14298</b>  49 1019
------------	--	--

Sawn timber - Assessment of drying quality

Táto norma obsahuje anglickú verziu európskej normy.  
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 03/18

Obsahuje: EN 14298:2017

Oznámením tejto normy sa ruší  
STN EN 14298 (49 1019) z júna 2005

**126452**

EUROPEAN STANDARD

**EN 14298**

NORME EUROPÉENNE

EUROPÄISCHE NORM

October 2017

ICS 79.040

Supersedes EN 14298:2004

English Version

**Sawn timber - Assessment of drying quality**

Bois scié - Estimation de la qualité du séchage

Schnittholz - Ermittlung der Trocknungsqualität

This European Standard was approved by CEN on 4 September 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

**EN 14298:2017 (E)**

<b>Contents</b>		<b>Page</b>
<b>European foreword</b> .....		<b>3</b>
<b>1</b>	<b>Scope</b> .....	<b>4</b>
<b>2</b>	<b>Normative references</b> .....	<b>4</b>
<b>3</b>	<b>Terms and definitions</b> .....	<b>4</b>
<b>4</b>	<b>Symbols and abbreviations</b> .....	<b>5</b>
<b>5</b>	<b>Drying quality specification</b> .....	<b>5</b>
<b>5.1</b>	<b>General</b> .....	<b>5</b>
<b>5.2</b>	<b>Standard drying quality</b> .....	<b>5</b>
<b>5.3</b>	<b>Specific end-use drying</b> .....	<b>6</b>
<b>6</b>	<b>Assessment by control of drying quality of a lot of sawn timber</b> .....	<b>6</b>
<b>6.1</b>	<b>General</b> .....	<b>6</b>
<b>6.2</b>	<b>Sampling</b> .....	<b>7</b>
<b>6.3</b>	<b>Moisture content</b> .....	<b>7</b>
<b>6.4</b>	<b>Criteria drying quality</b> .....	<b>8</b>
<b>6.4.1</b>	<b>Moisture content</b> .....	<b>8</b>
<b>6.4.2</b>	<b>Case-hardening</b> .....	<b>8</b>
<b>6.5</b>	<b>Test report</b> .....	<b>8</b>
<b>Annex A (informative) Example for an assessment of standard drying quality 12 %</b> .....		<b>9</b>
<b>A.1</b>	<b>General</b> .....	<b>9</b>
<b>A.2</b>	<b>Sampling</b> .....	<b>9</b>
<b>A.3</b>	<b>Measurements</b> .....	<b>9</b>
<b>A.4</b>	<b>Assessment of drying quality</b> .....	<b>9</b>
<b>A.5</b>	<b>Conclusion</b> .....	<b>10</b>

## **European foreword**

This document (EN 14298:2017) has been prepared by Technical Committee CEN/TC 175 “Round and sawn timber”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2018, and conflicting national standards shall be withdrawn at the latest by April 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 14298:2004.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

**EN 14298:2017 (E)****1 Scope**

This European Standard defines a method of assessment of drying quality. It applies to a lot of dried sawn timber (surfaced or not). It applies to both softwood and hardwood with a thickness not greater than 100 mm.

The quality of drying is expressed in terms of moisture content: target, average of the lot and variation between the pieces of the lot.

An option for specifying the degree of case-hardening is included.

NOTE 1 Other features related to drying, e.g. check, shake, warp, stain, etc., are specified in documents for visual grading of sawn timber or in product specifications and are not covered by this document.

NOTE 2 In the following the term “sawn timber” is used for all dried timber covered by this scope.

**2 Normative references**

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 844-3:1995, *Round and sawn timber — Terminology — Part 3: General terms relating to sawn timber*

EN 844-4:1997, *Round and sawn timber — Terminology — Part 4: Terms relating to moisture content*

EN 844-12:2000, *Round and sawn timber — Terminology — Part 12: Additional terms and general index*

EN 1438, *Symbols for timber and wood-based products*

EN 13183-1, *Moisture content of a piece of sawn timber — Part 1: Determination by oven dry method*

EN 13183-2, *Moisture content of a piece of sawn timber — Part 2: Estimation by electrical resistance method*

CEN/TS 12169, *Criteria for the assessment of conformity of a lot of sawn timber*

CEN/TS 14464, *Sawn timber — Method for assessment of case-hardening*

**koniec náhľadu – text ďalej pokračuje v platenej verzii STN**