

<b>STN</b>	<b>Plasty</b> <b>Stanovenie úplnej anaeróbnej biodegradácie</b> <b>plastových materiálov vo vodnom systéme</b> <b>Metóda merania produkcie bioplynu (ISO 14853:</b> <b>2016)</b>	<b>STN</b> <b>EN ISO 14853</b>  64 8009
------------	--	--

Plastics - Determination of the ultimate anaerobic biodegradation of plastic materials in an aqueous system - Method by measurement of biogas production (ISO 14853:2016)

Táto norma obsahuje anglickú verziu európskej normy.  
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 06/18

Obsahuje: EN ISO 14853:2017, ISO 14853:2016

**126774**

EUROPEAN STANDARD

EN ISO 14853

NORME EUROPÉENNE

EUROPÄISCHE NORM

December 2017

ICS 83.080.01

English Version

Plastics - Determination of the ultimate anaerobic  
biodegradation of plastic materials in an aqueous system -  
Method by measurement of biogas production (ISO  
14853:2016)

Plastiques - Évaluation de la biodégradabilité  
anaérobie ultime des matériaux plastiques en milieu  
aqueux - Méthode par détermination de la production  
de biogaz (ISO 14853:2016)

Kunststoffe - Bestimmung der vollständigen anaeroben  
Bioabbaubarkeit von Kunststoff-Materialien in einem  
wässrigen Medium - Verfahren mittels Analyse der  
Biogasentwicklung (ISO 14853:2016)

This European Standard was approved by CEN on 17 October 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

**EN ISO 14853:2017 (E)**

<b>Contents</b>	<b>Page</b>
<b>European foreword.....</b>	<b>3</b>

## **European foreword**

The text of ISO 14853:2016 has been prepared by Technical Committee ISO/TC 61 “Plastics” of the International Organization for Standardization (ISO) and has been taken over as EN ISO 14853:2017 by Technical Committee CEN/TC 249 “Plastics” the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2018, and conflicting national standards shall be withdrawn at the latest by June 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

### **Endorsement notice**

The text of ISO 14853:2016 has been approved by CEN as EN ISO 14853:2017 without any modification.

# INTERNATIONAL STANDARD

**ISO**  
**14853**

Second edition  
2016-07-15

---

---

## **Plastics — Determination of the ultimate anaerobic biodegradation of plastic materials in an aqueous system — Method by measurement of biogas production**

*Plastiques — Évaluation de la biodégradabilité anaérobie ultime des  
matériaux plastiques en milieu aqueux — Méthode par détermination  
de la production de biogaz*



Reference number  
ISO 14853:2016(E)

© ISO 2016

## ISO 14853:2016(E)



### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Ch. de Blandonnet 8 • CP 401  
CH-1214 Vernier, Geneva, Switzerland  
Tel. +41 22 749 01 11  
Fax +41 22 749 09 47  
copyright@iso.org  
www.iso.org

# Contents

Page

<b>Foreword</b> .....	<b>v</b>
<b>Introduction</b> .....	<b>vi</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>3</b>
<b>5 Reagents and materials</b> .....	<b>3</b>
<b>6 Apparatus</b> .....	<b>5</b>
6.1 Laboratory equipment.....	5
6.2 Apparatus for use when biogas is measured by a manometric method.....	6
6.3 Apparatus for use when biogas is measured by a volumetric method.....	6
<b>7 Procedure</b> .....	<b>6</b>
7.1 General.....	6
7.2 Digested sludge.....	6
7.3 Preparation of the inoculum.....	7
7.4 Preparation of test suspensions and controls.....	7
7.5 Incubation and gas measurement.....	8
7.6 Test duration.....	9
7.7 Measurement of inorganic carbon.....	9
7.8 Specific analyses.....	9
<b>8 Calculation and expression of results</b> .....	<b>9</b>
8.1 Amount of carbon in headspace.....	9
8.2 Calculation of amount of carbon in headspace when manometric measurement method is used.....	10
8.3 Calculation of amount of carbon in headspace when volumetric measurement method is used.....	11
8.4 Amount of inorganic carbon in the liquid.....	11
8.5 Total amount of carbon converted to gas.....	11
8.6 Amount of carbon in test material.....	12
8.7 Calculation of percentage biodegradation.....	12
<b>9 Validity of results</b> .....	<b>12</b>
9.1 Maintenance of anaerobic conditions.....	12
9.2 Inhibition of degradation.....	12
9.3 Validity of the test.....	12
<b>10 Test report</b> .....	<b>13</b>
<b>Annex A (informative) Example of apparatus for determining the amount of biogas produced by measuring the increase in gas pressure</b> .....	<b>14</b>
<b>Annex B (informative) Example of apparatus for determining volumetrically the amount of biogas produced</b> .....	<b>15</b>
<b>Annex C (informative) Example of a biodegradation curve</b> .....	<b>17</b>
<b>Annex D (informative) Examples of data sheets for anaerobic biodegradability tests</b> .....	<b>18</b>
<b>Annex E (informative) Table of water vapour pressures at various temperatures</b> .....	<b>21</b>
<b>Annex F (informative) Calculation of theoretical carbon dioxide (ThCO<sub>2</sub>) and theoretical methane (ThCH<sub>4</sub>) production</b> .....	<b>22</b>
<b>Annex G (informative) Example of determination of recovery rate</b> .....	<b>23</b>
<b>Annex H (informative) Example of a workflow scheme</b> .....	<b>26</b>

# ISO 14853:2016(E)

<b>Bibliography</b> .....	<b>28</b>
---------------------------	-----------

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

The committee responsible for this document is ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*.

This second edition cancels and replaces the first edition (ISO 14853:2005), which has been technically revised. It also incorporates the Technical Corrigendum ISO 14853:2005/Cor.1:2009.

**ISO 14853:2016(E)****Introduction**

With the increasing use of plastics, their recovery and disposal have become a major issue. As a first priority, recovery should be promoted. For example, plastic litter, which originates mainly from consumers, is difficult to recover completely. Additional examples of materials difficult to recover are found in the disposal of fishing tackle, agricultural mulch films and water-soluble polymers. These plastic materials tend to leak from closed waste management infrastructures into natural environments. Biodegradable plastics are now emerging as one of the available options to solve such environmental issues. Plastic materials, such as products or packaging, which are sent to anaerobic treatment facilities should be potentially biodegradable. Therefore, it is very important to determine the potential biodegradability of such materials and to obtain a quantitative measure of their biodegradability in anaerobic environments.

# Plastics — Determination of the ultimate anaerobic biodegradation of plastic materials in an aqueous system — Method by measurement of biogas production

**WARNING** — Sewage and activated sludge may contain potentially pathogenic organisms. Therefore, appropriate precautions should be taken when handling them. Digesting sewage sludge produces flammable gases which present fire and explosion risks. Care should be taken when transporting and storing quantities of digesting sludge. Toxic test chemicals and those whose properties are not known should be handled with care and in accordance with safety instructions. The pressure meter and microsyringes should be handled carefully to avoid needle stick injuries. Contaminated syringe needles should be disposed of in a safe manner.

## 1 Scope

This International Standard specifies a method for the determination of the ultimate anaerobic biodegradability of plastics by anaerobic microorganisms. The conditions described in this International Standard do not necessarily correspond to the optimum conditions for the maximum degree of biodegradation to occur. The test calls for exposure of the test material to sludge for a period of up to 90 d, which is longer than the normal sludge retention time (25 to 30 d) in anaerobic digesters, although digesters at industrial sites can have much longer retention times.

The method applies to the following materials:

- natural and/or synthetic polymers, copolymers or mixtures thereof;
- plastic materials which contain additives such as plasticizers, colorants or other compounds;
- water-soluble polymers;
- materials which, under the test conditions, do not inhibit the microorganisms present in the inoculum. Inhibitory effects can be determined using an inhibition control or by another appropriate method (see e.g. ISO 13641). If the test material is inhibitory to the inoculum, a lower test concentration, another inoculum or a pre-exposed inoculum can be used.

## 2 Normative references

There are no normative references in this document.

**koniec náhľadu – text ďalej pokračuje v platenej verzii STN**