

STN	Korózia kovov a zliatin Zrýchlené cyklické skúšky vystavením pôsobeniu okyslenej soľnej hmly, suchým a mokrým podmienkam (ISO 16151: 2018)	STN EN ISO 16151 03 8219
------------	---	--

Corrosion of metals and alloys - Accelerated cyclic test with exposure to acidified salt spray, dry and wet conditions (ISO 16151:2018)

Táto norma obsahuje anglickú verziu európskej normy.
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 12/18

Obsahuje: EN ISO 16151:2018, ISO 16151:2018

Oznámením tejto normy sa ruší
STN EN ISO 16151 (03 8219) z augusta 2008

127680

EUROPEAN STANDARD

EN ISO 16151

NORME EUROPÉENNE

EUROPÄISCHE NORM

July 2018

ICS 77.060

Supersedes EN ISO 16151:2008

English Version

Corrosion of metals and alloys - Accelerated cyclic test with exposure to acidified salt spray, dry and wet conditions (ISO 16151:2018)

Corrosion des métaux et alliages - Essais cycliques accélérés avec exposition au brouillard salin acidifié, en conditions "sèches" et en conditions "humides" (ISO 16151:2018)

Korrosion von Metallen und Legierungen - Schnellprüfungen unter zyklisch wechselnder Beanspruchung mit saurem Salzsprühnebel, "trockenen" und "feuchten" Bedingungen (ISO 16151:2018)

This European Standard was approved by CEN on 30 May 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

EN ISO 16151:2018 (E)

Contents	Page
European foreword.....	3

European foreword

This document (EN ISO 16151:2018) has been prepared by Technical Committee ISO/TC 156 "Corrosion of metals and alloys" in collaboration with Technical Committee CEN/TC 262 "Metallic and other inorganic coatings, including for corrosion protection and corrosion testing of metals and alloys" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2019, and conflicting national standards shall be withdrawn at the latest by January 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 16151:2008.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 16151:2018 has been approved by CEN as EN ISO 16151:2018 without any modification.

INTERNATIONAL STANDARD

ISO
16151

Second edition
2018-05

Corrosion of metals and alloys — Accelerated cyclic test with exposure to acidified salt spray, dry and wet conditions

Corrosion des métaux et alliages — Essais cycliques accélérés avec exposition au brouillard salin acidifié, en conditions «sèches» et en conditions «humides»



Reference number
ISO 16151:2018(E)

© ISO 2018

ISO 16151:2018(E)**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Test solution	2
4.1 General.....	2
4.2 Method A.....	2
4.2.1 Neutral sodium chloride solution.....	2
4.2.2 Preparation of the acidified-salt solution.....	2
4.3 Method B.....	3
4.3.1 Preparation of the mixed salt solution.....	3
4.3.2 Preparation of the acidic solution.....	3
4.3.3 Preparation of the acidified-salt solution.....	3
5 Apparatus	3
6 Test specimens	5
7 Arrangement of the test specimen	5
8 Operating condition	6
9 Continuity of tests	8
10 Duration of the tests	8
11 Treatment of test specimens after test	8
11.1 General.....	8
11.2 Non-organic coated test specimens: metallic and/or inorganic coated.....	8
11.3 Organic coated test specimens.....	8
11.3.1 Scribed organic coated test specimens.....	8
11.3.2 Organic coated but not scribed test specimens.....	9
12 Evaluation of results	9
13 Test report	9
Annex A (informative) Relationship between amounts of acidic stock solution added to mixed salt solution and pH of the resulting acidified-salt solution	11
Annex B (informative) Typical apparatus for accelerated cyclic tests with exposure to acidified salt spray, dry and wet conditions	12
Annex C (informative) Method for evaluation of the corrosivity of the apparatus	14
Annex D (normative) Preparation of test specimens with organic coatings for testing	16
Annex E (normative) Required supplementary information for testing test specimens with organic coatings	17
Bibliography	18

ISO 16151:2018(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 156, *Corrosion of metals and alloys*.

This second edition cancels and replaces the first edition (ISO 16151:2005), which has been technically revised. The main technical changes are as follows:

- harmonization with ISO 9227;
- terms and definitions clause has been added.

Introduction

Corrosion of metallic materials, with or without corrosion protection, is influenced by many environmental factors, the importance of which may vary with the type of metallic material and with the type of environment. It is impossible, therefore, to design accelerated laboratory corrosion tests in such a way that all environmental factors influencing resistance to corrosion are taken into account. Laboratory tests are, therefore, designed to simulate the effects of the most important factors, which enhance the corrosion of metallic materials.

The accelerated corrosion-test methods described in this document are designed to simulate and enhance the environmental influence on a metallic material to outdoor climates, where exposure to acid rain and to salt-contaminated conditions occur and may promote corrosion. It has been prepared by reference to technical papers and reports (see the Bibliography).

The test methods involve cyclic exposure of test specimens to a mist of acidified-salt solution, to drying conditions, and to periods of high humidity. However, the methods are mainly intended for comparative testing and the results obtained do not permit far-reaching conclusions on the corrosion resistance of the tested metallic material under the whole range of environmental conditions in which they may be used. Nevertheless, the methods provide valuable information on the relative performance of materials exposed to salt and/or acid rain environments similar to those employed in the test.

Corrosion of metals and alloys — Accelerated cyclic test with exposure to acidified salt spray, dry and wet conditions

WARNING — This document may involve hazardous materials, operations and equipment. It does not purport to address all of the safety problems associated with its use. It is the responsibility of the user of this document to establish appropriate safety and health practices.

1 Scope

This document specifies two accelerated corrosion-test procedures, Methods A and B, for the comparative evaluation of metallic materials with or without permanent corrosion protection or temporary corrosion protection in outdoor salt and/or acid rain environments. It also specifies the apparatus used. The two tests involve cyclic exposure of the specimens to acidified salt spray, “dry” and “wet” conditions.

The particular advantages of the two tests over conventional accelerated tests, such as the neutral salt spray (NSS) test as specified in ISO 9227 lie in their better ability to reproduce the corrosion that occurs in outdoor salt and/or acid rain environments. They are also useful for evaluating cosmetic corrosion.

Method A is applicable to

- metals and their alloys,
- metallic coatings (cathodic),
- anodic oxide coatings, and
- organic coatings on metallic materials.

Method B is applicable to

- steel coated with anodic coatings, and
- steel coated with anodic coatings covered with conversion coatings.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1514, *Paints and varnishes — Standard panels for testing*

ISO 2808, *Paints and varnishes — Determination of film thickness*

ISO 4623-2:2016, *Paints and varnishes — Determination of resistance to filiform corrosion — Part 2: Aluminium substrates*

ISO 8044, *Corrosion of metals and alloys — Basic terms and definitions*

ISO 17872, *Paints and varnishes — Guidelines for the introduction of scribe marks through coatings on metallic panels for corrosion testing*

koniec náhľadu – text ďalej pokračuje v platenej verzii STN