

STN	Pigmenty a plnidlá Metódy dispergovania a hodnotenie dispergovateľnosti v plastoch Časť 4: Hodnotenie koloristických vlastností a ľahkosti dispergovania bielych pigmentov v polyetyléne pomocou dvojvalcového mlyna (ISO 23900-4: 2015)	STN EN ISO 23900-4 67 0562
------------	---	--

Pigments and extenders - Methods of dispersion and assessment of dispersibility in plastics - Part 4: Determination of colouristic properties and ease of dispersion of white pigments in polyethylene by two-roll milling (ISO 23900-4:2015)

Táto norma obsahuje anglickú verziu európskej normy.
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 02/19

Obsahuje: EN ISO 23900-4:2018, ISO 23900-4:2015

Oznámením tejto normy sa ruší
STN EN 13900-4 (67 0562) z októbra 2004

128177

EUROPEAN STANDARD

EN ISO 23900-4

NORME EUROPÉENNE

EUROPÄISCHE NORM

September 2018

ICS 87.060.10

Supersedes EN 13900-4:2004

English Version

Pigments and extenders - Methods of dispersion and
assessment of dispersibility in plastics - Part 4:
Determination of colouristic properties and ease of
dispersion of white pigments in polyethylene by two-roll
milling (ISO 23900-4:2015)

Pigments et matières de charge - Méthodes de dispersion et évaluation de l'aptitude à la dispersion dans les plastiques - Partie 4: Détermination des propriétés colorimétriques et de la facilité de dispersion des pigments blancs dans le polyéthylène par calandrage sur bicylindre (ISO 23900-4:2015)

Pigmente und Füllstoffe - Dispergierverfahren und Beurteilung der Dispergierbarkeit in Kunststoffen - Teil 4: Bestimmung der koloristischen Eigenschaften und der Dispergierhärte von Weißpigmenten in Polyethylen im Walztest (ISO 23900-4:2015)

This European Standard was approved by CEN on 18 August 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

EN ISO 23900-4:2018 (E)

Contents	Page
European foreword.....	3

European foreword

The text of ISO 23900-4:2015 has been prepared by Technical Committee ISO/TC 256 "Pigments, dyestuffs and extenders" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 23900-4:2018 by Technical Committee CEN/TC 298 "Pigments and extenders" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2019, and conflicting national standards shall be withdrawn at the latest by March 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13900-4:2004.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 23900-4:2015 has been approved by CEN as EN ISO 23900-4:2018 without any modification.

INTERNATIONAL STANDARD

ISO 23900-4

First edition
2015-05-01

Pigments and extenders — Methods of dispersion and assessment of dispersibility in plastics —

Part 4:

Determination of colouristic properties and ease of dispersion of white pigments in polyethylene by two-roll milling

*Pigments et matières de charge — Méthodes de dispersion et
évaluation de l'aptitude à la dispersion dans les plastiques —*

*Partie 4: Détermination des propriétés colorimétriques et de la
facilité de dispersion des pigments blancs dans le polyéthylène par
calandrage sur bicylindre*



Reference number
ISO 23900-4:2015(E)

© ISO 2015

ISO 23900-4:2015(E)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Materials	2
5.1 Polyethylene.....	2
5.2 Carbon black polyethylene masterbatch.....	2
6 Apparatus	2
7 Sampling	2
8 Procedure	2
8.1 Testing of colouristic properties in polyethylene in admixture with carbon black.....	2
8.1.1 Preparation of the mixture.....	2
8.1.2 Preparation of the test sample.....	3
8.1.3 Pressing.....	3
8.1.4 Photometric measurement.....	3
8.2 Testing of ease of dispersion.....	3
8.2.1 Preparation of the test samples.....	3
8.2.2 Pressing and photometric measurement.....	3
9 Evaluation	3
10 Test report	4
11 Precision	4

ISO 23900-4:2015(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT), see the following URL: [Foreword — Supplementary information](#).

The committee responsible for this document is ISO/TC 256, *Pigments, dyestuffs and extenders*.

ISO 23900 consists of the following parts, under the general title *Pigments and extenders — Methods of dispersion and assessment of dispersibility in plastics*:

- *Part 1: General introduction*
- *Part 2: Determination of colouristic properties and ease of dispersion in plasticized polyvinyl chloride by two-roll milling*
- *Part 3: Determination of colouristic properties and ease of dispersion of black and colour pigments in polyethylene by two-roll milling*
- *Part 4: Determination of colouristic properties and ease of dispersion of white pigments in polyethylene by two-roll milling*
- *Part 5: Determination by filter pressure value test*
- *Part 6: Determination by film test*

Pigments and extenders — Methods of dispersion and assessment of dispersibility in plastics —

Part 4:

Determination of colouristic properties and ease of dispersion of white pigments in polyethylene by two-roll milling

1 Scope

This part of ISO 23900 specifies a method of determining the colouristic properties of a test pigment in polyethylene (PE) relative to a standard, and the ease of dispersion DH_{PE} of pigments from the differences in tinting strength of dispersing colouring materials under various conditions.

The method is appropriate for use with white pigments.

The ease of dispersion determined in this way is valid only for the dispersion equipment, dispersion conditions and dispersion medium being used. The use of test conditions differing from those specified can give different results; this applies both to the absolute magnitude and to the relation between values of the ease of dispersion of various pigments. The subscript DH_{PE} is therefore used to designate the value obtained as specified in this part of ISO 23900.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 787-24:1985, *General methods of test for pigments and extenders — Part 24: Determination of relative tinting strength of coloured pigments and relative scattering power of white pigments — Photometric methods*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

ISO 18314-1¹⁾, *Analytical colorimetry — Part 1: Practical colour measurement*

koniec náhľadu – text ďalej pokračuje v platenej verzii STN

1) To be published.