

STN	Buničina, papier a lepenka Stanovenie primárnych aromatických amínov (PAA) vo vodnom výluhu pomocou LC / MS / MS metódy	STN EN 17163 50 7016
------------	--	--

Pulp, paper and board - Determination of primary aromatic amines (PAA) in a water extract by a LC-MS method

Táto norma obsahuje anglickú verziu európskej normy.
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 06/19

Obsahuje: EN 17163:2019

128615

EUROPEAN STANDARD

EN 17163

NORME EUROPÉENNE

EUROPÄISCHE NORM

February 2019

ICS 85.060

English Version

Pulp, paper and board - Determination of primary aromatic amines (PAA) in a water extract by a LC-MS method

Pâtes, papier et carton - Détermination des amines aromatiques primaires (AAP) dans un extrait aqueux par méthode LC-MS

Papier, Pappe und Faserstoff - Bestimmung von primären aromatischen Aminen in Wasserextrakten mittels LC-MS

This European Standard was approved by CEN on 26 November 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

EN 17163:2019 (E)

Contents	Page
European foreword	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Principle	5
4.1 General	5
4.2 Interferences	6
5 Apparatus	6
6 Reagents	6
7 Sample preparation	10
8 HPLC conditions	10
8.1 General	10
8.2 System example 1	11
8.3 System example 2	11
8.4 Example of MS conditions	12
8.5 HPLC calibration	12
8.6 Quality control	13
8.7 Confirmation of Identity	13
9 Calculation of the PAA concentrations in the Sample Extracts	13
10 Test report	13
Annex A (informative) Precision data	14
Bibliography	16

European foreword

This document (EN 17163:2019) has been prepared by Technical Committee CEN/TC 172 “Pulp, paper and board”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2019, and conflicting national standards shall be withdrawn at the latest by August 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

EN 17163:2019 (E)**Introduction**

Primary aromatic amines (PAAs) can occur in paper and board materials as residual basic chemicals for the production of azodyes and azo pigments. Furthermore, hydrolysis products of isocyanates especially from paper laminates may be a possible source.

A draft of a European Standard EN 13130-XX concerning the “Determination of Primary Aromatic Amines (PAAs) in Food Simulants” has been prepared by the standardization committee CEN/TC 194/SC1/TG9.

When preparing this standard it has been assessed by the laboratories participating that the photometric screening method described in part A of the draft of standard EN 13130-XX is not applicable for the examination of water extracts of paper and board materials due to interferences of extractable paper components which caused irreproducible test results.

Due to the advantages of the MS/MS-detection regarding selectivity and sensitivity the determination of primary aromatic amines by means of LC-MS/MS was found to be capable for water extracts of paper and board materials when preparing this standard.

1 Scope

This document describes two representative methods for the determination of the extractable amount of specific primary aromatic amines (PAA) in a water extract of paper, board and pulp samples by means of HPLC with MS/MS detection which basically differ concerning the choice of the mobile and stationary phases. Deviating from this standard further methods may be applicable if it can be shown that comparable results can be achieved. A validation should be carried out by each laboratory.

It is applicable for the determination of the 22 primary aromatic amines (PAA) mentioned in the annex of Directive 2002/61/EC of 19th July 2002 amending Council Directive 76/769/EEC relating to restrictions on the market and use of certain dangerous substances and preparations (azocolourants) which are classified as carcinogenic categories 1A and 1B according to the CLP regulation and aniline.

The method described by this standard should be also applicable for the determination of further primary aromatic amines (PAA). A validation for every further analyte has to be done by the laboratory using this method.

The extractable amount of a primary aromatic amine (PAA) is expressed in mg PAA per litre water extract. This method is suitable for the determination of PAA with a working range of about 0,001 mg/l – 0,020 mg/l water extract.

Deviating from this standard further methods may be applicable if it can be shown that comparable results can be achieved. A validation should be carried out by each laboratory.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 645, *Paper and board intended to come into contact with foodstuffs — Preparation of a cold water extract*

EN 647, *Paper and board intended to come into contact with foodstuffs — Preparation of a hot water extract*

koniec náhľadu – text ďalej pokračuje v platenej verzii STN