

STN	Pracovná expozícia Meranie prašnosti sypkých materiálov obsahujúcich alebo uvoľňujúcich vdychovateľné NOAA alebo iné vdychovateľné častice Časť 1: Požiadavky a výber skúšobných metód	STN EN 17199-1 83 3619
------------	---	--

Workplace exposure - Measurement of dustiness of bulk materials that contain or release respirable NOAA and other respirable particles - Part 1: Requirements and choice of test methods

Táto norma obsahuje anglickú verziu európskej normy.
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 07/19

Obsahuje: EN 17199-1:2019

129103

EUROPEAN STANDARD

EN 17199-1

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 2019

ICS 13.040.30

English Version

Workplace exposure - Measurement of dustiness of bulk materials that contain or release respirable NOAA and other respirable particles - Part 1: Requirements and choice of test methods

Exposition sur les lieux de travail - Mesurage du pouvoir de resuspension des matériaux en vrac contenant ou émettant des nano-objets et leurs agrégats et agglomérats (NOAA) ou autres particules en fraction alvéolaire - Partie 1: Exigences et choix des méthodes d'essai

Exposition am Arbeitsplatz - Messung des Staubungsverhaltens von Schüttgütern, die Nanoobjekte oder Submikrometerpartikel enthalten oder freisetzen - Teil 1: Anforderungen und Auswahl des Prüfverfahrens

This European Standard was approved by CEN on 8 February 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

EN 17199-1:2019 (E)

Contents		Page
European foreword		4
Introduction		5
1	Scope	7
2	Normative references	7
3	Terms and definitions	8
4	Symbols and abbreviations	9
5	Principle	10
5.1	General	10
5.2	Metric and measurand	12
5.3	Choice of time-resolving and size-resolving instruments and samplers	14
5.3.1	General	14
5.3.2	Determination of health related dustiness mass fractions	16
5.3.3	Determination of number-based dustiness indices and number-based emission rates	16
5.3.4	Determination of the number of modes and the modal aerodynamic equivalent diameter(s) of the time-averaged number-based particle size distribution	17
5.3.5	Determination of the number of modes and the modal aerodynamic equivalent diameters of the time-averaged particle mass-based particle size distribution	17
5.3.6	Morphological and chemical characterization of the collected airborne particles	18
6	General requirements	19
6.1	Conditioning of the test material	19
6.1.1	General	19
6.1.2	Conditioning specifications	19
6.1.3	As-received condition	19
6.2	Conditioning of the test equipment	19
6.3	Sampling from bulk material	20
6.4	Moisture content	20
6.5	Bulk density	20
6.6	Test procedure	20
6.7	Replicate tests	20
7	Test methods	21
7.1	Available test methods	21
7.1.1	General	21
7.1.2	Rotating drum and small rotating drum method	21
7.1.3	Vortex shaker	21
7.1.4	Continuous drop method	21
7.2	General considerations	22
7.3	Selection of the most appropriate test method	22
8	Evaluation of dustiness data	23
9	Test report	23
Annex A (normative) Determination of moisture content		25
A.1	Infrared dryer method	25

A.1.1 Principle	25
A.1.2 Procedure	25
A.2 Alternative method	26
Annex B (normative) Determination of bulk density of the test material in accordance to EN 15051-1	27
B.1 Equipment	27
B.2 Special requirements	27
B.3 Procedure	27
Annex C (informative) Report for electron microscopy	28
C.1 Methodology information	28
C.1.1 Description of collection substrate	28
C.1.2 Sampler for electron microscopy analysis	28
C.1.3 Preparation for EM analysis	28
C.1.4 General information about the microscope	28
C.2 Results of observations and recording of images and spectra	29
Bibliography	30

EN 17199-1:2019 (E)**European foreword**

This document (EN 17199-1:2019) has been prepared by Technical Committee CEN/TC 137 “Assessment of workplace exposure to chemical and biological agents”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2019 and conflicting national standards shall be withdrawn at the latest by September 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

The control of the emitted and released airborne NOAA and other respirable particles during the handling and transportation of bulk materials is an important consideration for workers' exposure and the design and operation of many industrial or research processes. It is therefore important to obtain information about the propensity of bulk materials to release NOAA and other particles and thus assist in assessing the risk for exposure to a hazardous material, especially if they penetrate to the alveolar region (respirable fraction).

Dustiness data have been recommended for nanomaterials exposure assessment by the Organisation for Economic Co-operation and Development [1]; these are also already in use as an input parameter in some control banding tools for nanomaterials or to predict the likelihood of exposure by modelling. Finally, dustiness data can provide the manufacturers of nanomaterials with information that can help to improve their products (e.g. by selecting less dusty nanomaterials) or the users to improve their processes or their technical prevention approaches.

Dustiness depends on a number of factors including:

- the physical state of the bulk material (e.g. powder, granules, pellets and moisture content),
- the physicochemical properties of the particles contained in the bulk material (e.g. particle size and shape, relevant density, type of coating, hydrophobicity and hydrophilicity properties, aggregation of particles),
- the environment (e.g. moisture, temperature),
- the condition of the bulk material,
- the type of aerosol generation (activation energy or energy input, time characteristics of the energy input),
- the interaction between particles during agitation (e.g. friction shearing, van der Waals forces), and
- the sampling and measurement configuration.

The aim of dustiness testing is to simulate typical powder processing and handling in order to enable a comparison of the relative dust release potential of different bulk materials. Data derived from dustiness testing can be used as input for qualitative or quantitative exposure assessment. Dustiness involves the application of a given type and amount of activation energy or energy input, to a stipulated amount of test material during a stipulated time, whereby particles are dispersed into the air and are described quantitatively. No single dustiness method is likely to represent and reproduce the various types of processing and handling used in the workplace. Therefore, there are a number of methods for the design of dustiness devices and different values will be obtained by different test methods. However, the test and the variables including the sampling and measurement configuration demand to be closely specified to ensure reproducibility.

Conventional dustiness methods for micrometre-size particles estimate the airborne dust generated in terms of dustiness mass fraction (e.g. respirable, thoracic, inhalable), given in mg/kg. The current EN 15051 standard series for conventional dustiness provides two methods: the rotating drum method and the continuous drop method. Although these methods are accepted standards for micrometre-size particles, the biological behaviour of NOAA, because of their small particle size and surface area, has raised the question whether the dustiness can be adequately characterized by their mass fraction only.

EN 17199-1:2019 (E)

Therefore, particle number concentration and particle size distribution are other important measurands for measuring and characterizing the dustiness of bulk material containing NOAA¹⁾. The test provided in this document is also applicable to powders not falling under the EC recommended nanomaterial definition, which nevertheless might release airborne NOAA during handling.

This document together with EN 17199-2 to EN 17199-5 establish test methods that measure the dustiness of bulk materials containing NOAA in terms of health related dustiness mass fraction, number-based dustiness index and number-based emission rate. In addition, it establishes test methods that characterize the aerosol from its particle size distribution and the morphology and chemical composition of its particles. It also gives guidance on the choice of a test method from four methods: the rotating drum, the continuous drop, the small rotating drum and the vortex shaker. These methods require different amount of test material and allow the application of a wide range of energy inputs to those materials. The rotating drum methods differ from the continuous drop and the vortex shaker methods. In the rotating drum, the bulk material is repeatedly dropped while in the continuous drop, it is dropped only once but continuously. In the vortex shaker, the bulk material is subjected to a much higher energy input. The principle of the rotating drum method is similar to that of the small rotating drum method.

This document was originally developed based on the results of pre-normative research [3]. This project investigated the dustiness of ten bulk materials (including nine bulk nanomaterials) with the intention to test as wide a range of bulk materials as possible in terms of magnitude of dustiness, chemical composition and primary particle size distribution as indicated by a high range in specific surface area.

Although dustiness can be considered as a factor determining the exposure, the results of the selected test method cannot be directly used as an estimate of workplace exposure in the intended application.

1) CEN ISO/TS 12025 [2] provides general methodology for the quantification of nano-object release from powders as a result of treatment, ranging from handling to high energy dispersion, by measuring aerosols liberated after a defined aerosolization procedure. However, it does not establish test methods.

1 Scope

This document provides the methodology for measuring and characterizing the dustiness of a bulk material that contains or releases respirable NOAA and other respirable particles. In addition, it specifies the environmental conditions, the sample handling procedure and the method of calculating and presenting the results. Guidance is given on the choice of method to be used.

The methodology described in this document enables:

- a) the quantification of dustiness in terms of health related dustiness mass fractions,
- b) the quantification of dustiness in terms of a number-based dustiness index and a number-based emission rate, and
- c) the characterization of the aerosol from its particle size distribution and the morphology and chemical composition of its particles.

NOTE 1 Currently, no number-based classification scheme in terms of particle number has been established for particle dustiness release. Eventually, when a large enough number of measurement data has been obtained, the intention is to revise this document and to introduce a number-based classification scheme.

This document is applicable to all bulk materials, including powders, granules or pellets, containing or releasing respirable NOAA and other respirable particles.

NOTE 2 The vortex shaker method specified in part 5 of this standard series has not yet been evaluated for pellets and granules.

NOTE 3 The rotating drum and continuous drop methods have not yet been evaluated for nanofibres and nanoplates.

This document does not provide methods for assessing the release of particles during handling or mechanical reduction by machining (e.g. crushing, cutting, sanding, sawing) of nanocomposites.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

CEN ISO/TS 80004-2, *Nanotechnologies - Vocabulary - Part 2: Nano-objects (ISO/TS 80004-2)*

EN 1540, *Workplace exposure - Terminology*

EN 13205-2, *Workplace exposure - Assessment of sampler performance for measurement of airborne particle concentrations - Part 2: Laboratory performance test based on determination of sampling efficiency*

EN 15051-1, *Workplace exposure - Measurement of the dustiness of bulk materials - Part 1: Requirements and choice of test methods*

EN 15051-2, *Workplace exposure - Measurement of the dustiness of bulk materials - Part 2: Rotating drum method*

EN 15051-3, *Workplace exposure - Measurement of the dustiness of bulk materials - Part 3: Continuous drop method*

EN 16897, *Workplace exposure - Characterization of ultrafine aerosols/nanoaerosols - Determination of number concentration using condensation particle counters*

EN 17199-1:2019 (E)

EN 17199-2, *Workplace exposure - Measurement of dustiness of bulk materials that contain or release respirable NOAA and other respirable particles - Part 2: Rotating drum method*

EN 17199-3, *Workplace exposure - Measurement of dustiness of bulk materials that contain or release respirable NOAA and other respirable particles - Part 3: Continuous drop method*

EN 17199-4, *Workplace exposure - Measurement of dustiness of bulk materials that contain or release respirable NOAA and other respirable particles - Part 4: Small rotating drum method*

EN 17199-5, *Workplace exposure - Measurement of dustiness of bulk materials that contain or release respirable NOAA and other respirable particles - Part 5: Vortex shaker method*

ISO 15900, *Determination of particle size distribution - Differential electrical mobility analysis for aerosol particles*

ISO 27891, *Aerosol particle number concentration - Calibration of condensation particle counters*

koniec náhľadu – text ďalej pokračuje v platenej verzii STN