

STN	Zvariteľné konštrukčné ocele na pevné pobrežné konštrukcie Technické dodacie podmienky Časť 1: Platne	STN EN 10225-1 42 0929
------------	--	--

Weldable structural steels for fixed offshore structures - Technical delivery conditions - Part 1: Plates

Táto norma obsahuje anglickú verziu európskej normy.
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 10/19

Obsahuje: EN 10225-1:2019

Spolu s STN EN 10225-2, STN EN 10225-3 a STN EN 10225-4 ruší
STN EN 10225 (42 0929) z januára 2010

129221

EUROPEAN STANDARD

EN 10225-1

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 2019

ICS 77.140.10

Supersedes EN 10225:2009

English Version

Weldable structural steels for fixed offshore structures - Technical delivery conditions - Part 1: Plates

Aciers de construction soudables destinés à la
fabrication de structures marines fixes - Conditions
techniques de livraison - Partie 1 : Tôles

Schweißgeeignete Baustähle für feststehende Offshore-
Konstruktionen - Technische Lieferbedingungen - Teil
1: Bleche

This European Standard was approved by CEN on 23 December 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

EN 10225-1:2019 (E)

Contents	Page
European foreword	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	7
4 Classification and designation	8
4.1 Classification.....	8
4.2 Designation	8
5 Information to be supplied by the purchaser	9
5.1 Mandatory information	9
5.2 Options.....	9
5.3 Example of an order	10
6 Manufacturing process	10
6.1 Steel manufacturing process	10
6.2 Qualification of personnel for NDT-activities.....	10
6.3 Delivery condition	10
6.4 Thickness limits	11
7 Requirements	11
7.1 General.....	11
7.2 Chemical composition	11
7.2.1 Heat analysis.....	11
7.2.2 Product analysis.....	11
7.2.3 Carbon equivalent values (CEV) and P_{cm}	12
7.3 Mechanical properties	12
7.3.1 General.....	12
7.3.2 Post weld heat treatment (PWHT)	12
7.3.3 Strain age tests.....	12
7.3.4 Through-thickness testing.....	12
7.3.5 Fracture mechanic testing.....	12
7.3.6 Prequalification for arctic areas.....	13
7.4 Technological properties.....	13
7.4.1 Cold forming characteristics of steel plate	13
7.4.2 Hot forming procedures for steel plate.....	13
7.4.3 Weldability data	13
7.5 Internal soundness and non-destructive testing	13
7.6 Surface quality	13
7.7 Dimensions, tolerances, mass	14
7.7.1 Dimensions and tolerances on dimensions and shape	14
7.7.2 Mass of steel.....	14
8 Inspection	14
8.1 General.....	14
8.2 Types of inspection documents	14
8.3 Summary of inspections	15
8.4 Intermediary supply	15

9	Frequency of testing and preparation of samples and test pieces.....	15
9.1	Frequency of test.....	15
9.1.1	Chemical analysis	15
9.1.2	Tensile test.....	15
9.1.3	Impact test.....	16
9.2	Selection and preparation of samples for product analysis.....	16
9.3	Location of samples and orientation of tensile test pieces.....	16
9.4	Location of samples and orientation of impact test pieces	16
9.5	Preparation of test pieces for mechanical tests.....	16
9.5.1	General	16
9.5.2	Preparation of tensile test pieces	16
9.5.3	Preparation of impact test pieces	16
10	Test methods.....	17
10.1	Chemical analysis	17
10.2	Mechanical tests.....	17
10.2.1	Test temperatures.....	17
10.2.2	Tensile test.....	17
10.2.3	Impact test.....	18
10.3	Visual inspection and dimensional check.....	18
10.4	Non-destructive tests	18
10.4.1	General	18
10.4.2	NDT for plates	18
10.5	Retests, sorting and reprocessing	19
11	Marking - Die stamping and paint marking.....	19
12	Options	19
Annex A	(normative when Option 1 is specified by the purchaser) Further details of steel manufacturing procedures to be supplied by the manufacturer.....	34
Annex B	(normative when Option 17 is specified by the purchaser) Weldability testing and mechanical testing of butt welds.....	35
Annex C	(normative when Option 17 is specified by the purchaser) Weldability testing - Bead-on-plate.....	48
Annex D	(normative when Option 17 is specified by the purchaser) Weldability testing - Controlled thermal severity tests (CTS)	51
Annex E	(normative when Option 15 is specified by the purchaser) Cold forming characteristics for steel plates.....	58
Annex F	(informative) Prequalification of steels for offshore structures operating in arctic areas	59
Annex G	(informative) List of options of EN 10225-1 to -4.....	60
Bibliography	62

EN 10225-1:2019 (E)**European foreword**

This document (EN 10225-1:2019) has been prepared by Technical Committee CEN/TC 459 "ECISS - European Committee for Iron and Steel Standardization"¹, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2019, and conflicting national standards shall be withdrawn at the latest by November 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document, together with EN 10225-2:2019, EN 10225-3:2019, and EN 10225-4:2019, supersedes EN 10225:2009.

This European Standard consists of the following parts, under the general title '*Weldable structural steels for fixed offshore structures – Technical delivery conditions*':

- Part 1: Plates
- Part 2: Sections
- Part 3: Hot finished hollow sections
- Part 4: Cold formed hollow sections

In comparison to the previous edition the following technical changes were made:

- split of the standard in four parts;
- the steel names were adapted to EN 10027-1;
- former grades of group 3 are no longer listed, new options with the same enhanced properties have been introduced (**Options 2 and 3**);
- an informative Annex F was added for the prequalification of steels for fixed offshore structures in arctic areas.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

¹ Through its subcommittee SC 3 "Structural steels other than reinforcements" (secretariat: DIN)

1 Scope

This document specifies requirements for weldable structural steels, in the form of plates, to be used in the fabrication of fixed offshore structures.

The following thickness limitations are given in this standard:

- S355NLO up to and including 200 mm;
- S355MLO, S420MLO, S460MLO, S500MLO up to and including 120 mm;
- S420QLO, S460QLO, S500QLO, S550QLO, S620QLO, S690QLO up to and including 150 mm.

Greater thicknesses can be agreed, provided the technical requirements of this European Standard are maintained.

This European Standard is applicable to steels for offshore structures, designed to operate in the offshore sector, including plate for structural hollow sections (see EN 10225-4). It does not apply to plates supplied for the fabrication of subsea pipelines, risers, process equipment, process piping and other utilities. It is primarily applicable to the North Sea Sector, but may also be applicable in other areas provided that due consideration is given to local conditions e.g. design temperature.

NOTE This document has an informative Annex F on the prequalification of steels for fixed offshore structures in arctic areas.

Minimum yield strengths up to 690 MPa are specified together with impact properties at temperatures down to $-40\text{ }^{\circ}\text{C}$.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1011-1, *Welding — Recommendations for welding of metallic materials — Part 1: General guidance for arc welding*

EN 10020, *Definition and classification of grades of steel*

EN 10021, *General technical delivery conditions for steel products*

EN 10027-1, *Designation systems for steels — Part 1: Steel names*

EN 10027-2, *Designation systems for steels — Part 2: Numerical system*

EN 10029, *Hot-rolled steel plates 3 mm thick or above — Tolerances on dimensions and shape*

EN 10051, *Continuously hot-rolled strip and plate/sheet cut from wide strip of non-alloy and alloy steels — Tolerances on dimensions and shape*

EN 10079, *Definition of steel products*

EN 10160, *Ultrasonic testing of steel flat product of thickness equal or greater than 6 mm (reflection method)*

EN 10225-1:2019 (E)

EN 10163-1, *Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections — Part 1: General requirements*

EN 10163-2, *Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections — Part 2: Plate and wide flats*

EN 10164, *Steel products with improved deformation properties perpendicular to the surface of the product — Technical delivery conditions*

EN 10168, *Steel products — Inspection documents — List of information and description*

EN 10204, *Metallic products — Types of inspection documents*

CEN/TR 10261, *Iron and steel — European standards for the determination of chemical composition*

EN ISO 148-1, *Metallic materials — Charpy pendulum impact test — Part 1: Test method (ISO 148-1)*

EN ISO 377, *Steel and steel products — Location and preparation of samples and test pieces for mechanical testing (ISO 377)*

EN ISO 643, *Steels — Micrographic determination of the apparent grain size (ISO 643)*

EN ISO 2566-1, *Steel — Conversion of elongation values — Part 1: Carbon and low alloy steels (ISO 2566-1)*

EN ISO 3452-1, *Non-destructive testing — Penetrant testing — Part 1: General principles (ISO 3452-1)*

EN ISO 4063, *Welding and allied processes — Nomenclature of processes and reference numbers (ISO 4063)*

EN ISO 4136, *Destructive tests on welds in metallic materials — Transverse tensile test (ISO 4136)*

EN ISO 4885, *Ferrous materials — Heat treatments — Vocabulary (ISO 4885)*

EN ISO 6507-1, *Metallic materials — Vickers hardness test — Part 1: Test method (ISO 6507-1)*

EN ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature (ISO 6892-1)*

EN ISO 6947, *Welding and allied processes — Welding positions (ISO 6947)*

EN ISO 9712, *Non-destructive testing — Qualification and certification of NDT personnel (ISO 9712)*

EN ISO 9934-1, *Non-destructive testing — Magnetic particle testing — Part 1: General principles (ISO 9934-1)*

EN ISO 14284, *Steel and iron — Sampling and preparation of samples for the determination of chemical composition (ISO 14284)*

EN ISO 15614-1, *Specification and qualification of welding procedures for metallic materials — Welding procedure test — Part 1: Arc and gas welding of steels and arc welding of nickel and nickel alloys (ISO 15614-1)*

ISO 11484, *Steel products — Employer's qualification system for non-destructive testing (NDT) personnel*

ISO 12135, *Metallic materials — Unified method of test for the determination of quasistatic fracture toughness*

ISO 15653, *Metallic materials — Method of test for the determination of quasistatic fracture toughness of welds*

koniec náhľadu – text ďalej pokračuje v platenej verzii STN