

STN	Skúšanie zatvrdnutého betónu Časť 3: Pevnosť v tlaku skúšobných telies	STN EN 12390-3 73 1302
------------	-----------------------------------------------------------------------------------------	------------------------------------------------

Testing hardened concrete - Part 3: Compressive strength of test specimens

Táto norma obsahuje anglickú verziu európskej normy.
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 12/19

Obsahuje: EN 12390-3:2019

Oznámením tejto normy sa ruší
STN EN 12390-3 (73 1302) z apríla 2010

129586

EUROPEAN STANDARD

EN 12390-3

NORME EUROPÉENNE

EUROPÄISCHE NORM

June 2019

ICS 91.100.30

Supersedes EN 12390-3:2009

English Version

Testing hardened concrete - Part 3: Compressive strength of test specimens

Essais pour béton durci - Partie 3 : Résistance à la
compression des éprouvettes

Prüfung von Festbeton - Teil 3: Druckfestigkeit von
Probekörpern

This European Standard was approved by CEN on 29 April 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

EN 12390-3:2019 (E)

Contents	Page
European foreword.....	3
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Principle	5
5 Apparatus.....	5
6 Test specimens.....	5
7 Procedure.....	6
7.1 Specimen preparation and positioning.....	6
7.2 Loading.....	6
7.3 Assessment of type of failure	7
8 Expression of results.....	7
9 Test report.....	7
10 Precision.....	11
Annex A Adjustment of test specimens.....	12
Annex B Procedure for testing specimens with dimensions which are outside the tolerances of the designated sizes of EN 12390-1	18

European foreword

This document (EN 12390-3:2019) has been prepared by Technical Committee CEN/TC 104 “Concrete and related products”, the secretariat of which is held by SN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2019, and conflicting national standards shall be withdrawn at the latest by December 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12390-3:2009.

It is recognized good practice to include measurement of density prior to the determination of compressive strength.

The methods for adjusting the ends of test specimens, given in Annex A, have been validated in a laboratory inter-comparison, part-funded by the EC under the Measurement and Testing Programme; contract MATI-CT-94-0043.

This standard is one of a series on testing concrete.

EN 12390, *Testing hardened concrete*, consists of the following parts:

- *Part 1: Shape, dimensions and other requirements of specimens and moulds;*
- *Part 2: Making and curing specimens for strength tests;*
- *Part 3: Compressive strength of test specimens;*
- *Part 4: Compressive strength – Specification for testing machines;*
- *Part 5: Flexural strength of test specimens;*
- *Part 6: Tensile splitting strength of test specimens;*
- *Part 7: Density of hardened concrete;*
- *Part 8: Depth of penetration of water under pressure;*
- *Part 11: Determination of the chloride resistance of concrete, unidirectional diffusion;*
- *Part 12: Determination of the potential carbonation resistance of concrete: Accelerated carbonation method (in preparation);*
- *Part 13: Determination of secant modulus of elasticity in compression;*
- *Part 14: Semi-adiabatic method for the determination of heat released by concrete during its hardening process;*
- *Part 15: Adiabatic method for the determination of heat released by concrete during its hardening process;*
- *Part 16: Determination of the shrinkage of concrete (in preparation);*

EN 12390-3:2019 (E)

- *Part 17: Determination of creep of concrete in compression (in preparation);*
- *Part 18: Determination of the chloride migration coefficient (in preparation).*

This edition includes the following significant technical changes with respect to EN 12390-3:2009:

- editorial revision;
- technical corrections;
- clarification of acceptable tolerances of test specimen size or diameter;
- clarification of procedure from when the specimen is removed from curing until being tested for strength.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This document specifies a method for the determination of the compressive strength of test specimens of hardened concrete.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 197-1, *Cement — Part 1: Composition, specifications and conformity criteria for common cements*

EN 12350-1, *Testing fresh concrete — Part 1: Sampling*

EN 12390-1, *Testing hardened concrete — Part 1: Shape, dimensions and other requirements for specimens and moulds*

EN 12390-2, *Testing hardened concrete — Part 2: Making and curing specimens for strength tests*

EN 12390-4, *Testing hardened concrete — Part 4: Compressive strength — Specification for testing machines*

EN 12390-7, *Testing hardened concrete — Part 7: Density of hardened concrete*

EN 12504-1, *Testing concrete in structures — Part 1: Cored specimens — Taking, examining and testing in compression*

ISO 3310-1, *Test sieves — Technical requirements and testing — Part 1: Test sieves of metal wire cloth*

koniec náhľadu – text ďalej pokračuje v platenej verzii STN