

STN	Plasty Určovanie dynamických mechanických vlastností Časť 1: Všeobecné princípy (ISO 6721-1: 2019)	STN EN ISO 6721-1 64 0615
------------	---	---

Plastics - Determination of dynamic mechanical properties - Part 1: General principles (ISO 6721-1:2019)

Táto norma obsahuje anglickú verziu európskej normy.
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 10/19

Obsahuje: EN ISO 6721-1:2019, ISO 6721-1:2019

Oznámením tejto normy sa ruší
STN EN ISO 6721-1 (64 0615) z novembra 2011

129611

EUROPEAN STANDARD

EN ISO 6721-1

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 2019

ICS 83.080.01

Supersedes EN ISO 6721-1:2011

English Version

Plastics - Determination of dynamic mechanical properties - Part 1: General principles (ISO 6721-1:2019)

Plastiques - Détermination des propriétés mécaniques
dynamiques - Partie 1: Principes généraux (ISO 6721-
1:2019)

Kunststoffe - Bestimmung dynamisch-mechanischer
Eigenschaften - Teil 1: Allgemeine Grundlagen (ISO
6721-1:2019)

This European Standard was approved by CEN on 8 June 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3

European foreword

This document (EN ISO 6721-1:2019) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2019, and conflicting national standards shall be withdrawn at the latest by November 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 6721-1:2011.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 6721-1:2019 has been approved by CEN as EN ISO 6721-1:2019 without any modification.

INTERNATIONAL STANDARD

ISO 6721-1

Fourth edition
2019-04

Plastics — Determination of dynamic mechanical properties —

Part 1: General principles

*Plastiques — Détermination des propriétés mécaniques
dynamiques —*

Partie 1: Principes généraux



Reference number
ISO 6721-1:2019(E)

© ISO 2019

**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Principle	9
5 Test apparatus	12
5.1 Type.....	12
5.2 Mechanical, electronic and recording systems.....	12
5.3 Temperature-controlled enclosure.....	12
5.4 Gas supply.....	12
5.5 Temperature-measurement device.....	12
5.6 Devices for measuring test specimen dimensions.....	12
6 Test specimens	12
6.1 General.....	12
6.2 Shape and dimensions.....	13
6.3 Preparation.....	13
7 Number of test specimens	13
8 Conditioning	13
9 Procedure	13
9.1 Test atmosphere.....	13
9.2 Measurement of specimen cross-section.....	13
9.3 Mounting the test specimens.....	13
9.4 Varying the temperature.....	13
9.5 Varying the frequency.....	14
9.6 Varying the dynamic-strain amplitude.....	14
10 Expression of results	14
11 Precision	15
12 Test report	15
Annex A (informative) Resonance curves	16
Annex B (informative) Deviations from linear behaviour	22
Bibliography	23

ISO 6721-1:2019(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*.

This fourth edition cancels and replaces the third edition (ISO 6721-1:2011), which has been technically revised. The main changes compared to the previous edition are as follows:

- the document has been revised editorially;
- normative references have been changed to undated and added as references into [Tables 4](#) and [5](#).

A list of all parts in the ISO 6721 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The methods specified in the first nine parts of ISO 6721 can be used for determining storage and loss moduli of plastics over a range of temperatures or frequencies by varying the temperature of the specimen or the frequency of oscillation. Plots of the storage or loss moduli, or both, are indicative of viscoelastic characteristics of the specimen. Regions of rapid changes in viscoelastic properties at particular temperatures or frequencies are normally referred to as transition regions. Furthermore, from the temperature and frequency dependencies of the loss moduli, the damping of sound and vibration of polymer or metal-polymer systems can be estimated.

Apparent discrepancies may arise in results obtained under different experimental conditions. Without changing the observed data, reporting in full (as described in the various parts of ISO 6721) the conditions under which the data were obtained will enable apparent differences observed in different studies to be reconciled.

The definitions of complex moduli apply exactly only to sinusoidal oscillations with constant amplitude and constant frequency during each measurement. On the other hand, measurements of small phase angles between stress and strain involve some difficulties under these conditions. Because these difficulties are not involved in some methods based on freely decaying vibrations and/or varying frequency near resonance, these methods are used frequently (see ISO 6721-2 and ISO 6721-3). In these cases, some of the equations that define the viscoelastic properties are only approximately valid.

Plastics — Determination of dynamic mechanical properties —

Part 1: General principles

1 Scope

The various parts of ISO 6721 specify methods for the determination of the dynamic mechanical properties of rigid plastics within the region of linear viscoelastic behaviour. This document specifies the definitions and describes the general principles including all aspects that are common to the individual test methods described in the subsequent parts.

Different deformation modes can produce results that are not directly comparable. For example, tensile vibration results in a stress which is uniform across the whole thickness of the specimen, whereas flexural measurements are influenced preferentially by the properties of the surface regions of the specimen.

Values derived from flexural-test data will be comparable to those derived from tensile-test data only at strain levels where the stress-strain relationship is linear and for specimens which have a homogeneous structure.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 4593, *Plastics — Film and sheeting — Determination of thickness by mechanical scanning*

ISO 6721-2, *Plastics — Determination of dynamic mechanical properties — Part 2: Torsion-pendulum method*

ISO 6721-3, *Plastics — Determination of dynamic mechanical properties — Part 3: Flexural vibration — Resonance-curve method*

ISO 6721-4, *Plastics — Determination of dynamic mechanical properties — Part 4: Tensile vibration — Non-resonance method*

ISO 6721-5, *Plastics — Determination of dynamic mechanical properties — Part 5: Flexural vibration — Non-resonance method*

ISO 6721-6, *Plastics — Determination of dynamic mechanical properties — Part 6: Shear vibration — Non-resonance method*

ISO 6721-7, *Plastics — Determination of dynamic mechanical properties — Part 7: Torsional vibration — Non-resonance method*

ISO 6721-8, *Plastics — Determination of dynamic mechanical properties — Part 8: Longitudinal and shear vibration — Wave-propagation method*

ISO 6721-9, *Plastics — Determination of dynamic mechanical properties — Part 9: Tensile vibration — Sonic-pulse propagation method*

ISO 6721-1:2019(E)

ISO 6721-10, *Plastics — Determination of dynamic mechanical properties — Part 10: Complex shear viscosity using a parallel-plate oscillatory rheometer*

ISO 6721-12, *Plastics — Determination of dynamic mechanical properties — Part 12: Compressive vibration — Non-resonance method*

koniec náhľadu – text ďalej pokračuje v platenej verzii STN