

STN	Potrubné systémy z plastov na beztlakovú podzemnú prepravu a akumuláciu nepitnej vody Skúšobná metóda na určenie dlhodobej pevnosti blokov v tlaku	STN EN 17151 64 3052
------------	---	--

Plastics piping systems for non-pressure underground conveyance and storage of non-potable water - Test method for determination of long-term compression strength of boxes

Táto norma obsahuje anglickú verziu európskej normy.
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 01/20

Obsahuje: EN 17151:2019

130218

EUROPEAN STANDARD

EN 17151

NORME EUROPÉENNE

EUROPÄISCHE NORM

August 2019

ICS 23.040.01

English Version

Plastics piping systems for non-pressure underground conveyance and storage of non-potable water - Test method for determination of long-term compression strength of boxes

Systèmes de canalisations en plastique pour le transport et le stockage souterrains sans pression de l'eau non potable - Méthode d'essai pour la détermination de la résistance à la compression à long terme des structures alvéolaires ultra-légères

Kunststoff-Rohrleitungssysteme für die drucklose unterirdische Entwässerung für Nicht-Trinkwasser - Prüfverfahren zur Bestimmung der Langzeitdruckfestigkeit von Versickerungsblöcken

This European Standard was approved by CEN on 19 October 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

EN 17151:2019 (E)

Contents		Page
European foreword		3
Introduction		4
1	Scope	5
2	Normative references	5
3	Terms and definitions	5
4	Symbols and units	6
5	Test method	7
6	Apparatus	7
7	Test sample	8
7.1	General	8
7.2	Number	8
7.3	Age	8
7.4	Conditioning	8
8	Procedures and calculations	8
8.1	Test method	8
8.2	Creep rupture test procedure	9
9	Test report	10
Annex A (informative) Test method for determining linear behaviour		12
A.1	Principle	12
A.2	Procedure	12
A.3	Calculations	13
Annex B (normative) Procedure for fitting creep rupture data and determining the LCL strength for a design life of 50 year		14
B.1	Requirements	14
B.2	Principles of the analysis	14
B.3	Analysis Method	15
Bibliography		17

European foreword

This document (EN 17151:2019) has been prepared by Technical Committee CEN/TC 155 “Plastics piping systems and ducting systems”, the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2020, and conflicting national standards shall be withdrawn at the latest by February 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

EN 17151:2019 (E)**Introduction**

This standard is intended to reflect the current state of knowledge of determining and predicting the long-term lifetime of products mentioned in the scope while maintaining reasonable testing times for producers and developers of these systems.

The products covered by this standard are part of storm water management systems.

CEN TC 155 is aware that these products are used in modular systems and that the long term compression strength determined by this standard applies to a single box and might not reflect the maximum allowable loads on an installed system.

Linearity is assumed to extrapolate the (log) load versus log time curve from the results of the creep rupture tests. The test described in Annex A is intended to demonstrate linearity over the extrapolated lifetime by testing at elevated temperatures.

This test is given as an informative annex due to limited practical experience and lack of reliability analyses. CEN TC 155 wants to encourage stakeholders to perform these tests before the next revision.

NOTE Linear behaviour of the boxes can be assumed when the difference in the slope between creep tests performed at 20 °C and at 70 °C as described in Annex A is small and therefore there has been no deviation from linear behaviour.

The test method follows the principles of ISO 9080 [1] and applies them to the testing of boxes.

CEN TC 155 is aware that including a not failed data point at 4 380 h in the calculation of LCL would bias the outcome in the lower 95 % confidence level (*LCL*) for the stress leading to a failure at 50 years.

1 Scope

This document specifies a test method for determining the long-term compression strength for a specified period on boxes made of thermoplastics materials for non-pressure underground conveyance and storage of non-potable water.

The document is applicable for boxes which maintain their linear behaviour over the specified period.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN ISO 3126, *Plastics piping systems — Plastics components — Determination of dimensions (ISO 3126)*

EN ISO 7500-1:2018, *Metallic materials — Calibration and verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Calibration and verification of the force-measuring system (ISO 7500-1:2018)*

koniec náhľadu – text ďalej pokračuje v platenej verzii STN