

<b>STN</b>	<b>Meď a zliatiny medi</b> <b>Skúška vírivým prúdom na meranie chýb</b> <b>bezšvových okrúhlych rúr z medi a zliatiny medi</b> <b>Časť 1: Skúška s priechodnou skúšobnou cievkou</b> <b>na vonkajšom povrchu</b>	<b>STN</b> <b>EN 1971-1</b>  42 0428
------------	--	---

Copper and copper alloys - Eddy current test for measuring defects on seamless round copper and copper alloy tubes - Part 1: Test with an encircling test coil on the outer surface

Táto norma obsahuje anglickú verziu európskej normy.  
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 05/20

Obsahuje: EN 1971-1:2019

Oznámením tejto normy sa ruší  
STN EN 1971-1 (42 0428) z júna 2012

**130844**

EUROPEAN STANDARD

EN 1971-1

NORME EUROPÉENNE

EUROPÄISCHE NORM

November 2019

ICS 23.040.15; 77.150.30

Supersedes EN 1971-1:2011

English Version

## Copper and copper alloys - Eddy current test for measuring defects on seamless round copper and copper alloy tubes - Part 1: Test with an encircling test coil on the outer surface

Cuivre et alliages de cuivre - Méthode de contrôle par courants de Foucault pour le mesurage des défauts des tubes ronds sans soudure en cuivre et alliages de cuivre - Partie 1 : Essai avec une bobine encerclante sur la paroi externe

Kupfer und Kupferlegierungen - Wirbelstromprüfung an Rohren zur Messung von Fehlern an nahtlos gezogenen runden Rohren aus Kupfer und Kupferlegierungen - Teil 1: Prüfung mit umfassender Spule auf der Außenseite

This European Standard was approved by CEN on 4 September 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

**Contents**

Page

<b>European foreword.....</b>	<b>3</b>
<b>Introduction .....</b>	<b>4</b>
<b>1 Scope.....</b>	<b>5</b>
<b>2 Normative references.....</b>	<b>5</b>
<b>3 Terms and definitions .....</b>	<b>5</b>
<b>4 General requirements .....</b>	<b>5</b>
<b>4.1 Personnel qualification.....</b>	<b>5</b>
<b>4.2 Condition of tube to be tested.....</b>	<b>5</b>
<b>4.3 Equipment .....</b>	<b>6</b>
<b>5 Reference standard tube .....</b>	<b>7</b>
<b>6 Acceptance criteria.....</b>	<b>8</b>
<b>6.1 Detection of local discontinuities by encircling coils systems.....</b>	<b>8</b>
<b>6.2 Detection of non-local discontinuities by encircling coils systems with lower detection levels .....</b>	<b>8</b>
<b>6.3 Other test methods .....</b>	<b>9</b>
<b>7 Instrument adjustment.....</b>	<b>9</b>
<b>Bibliography.....</b>	<b>10</b>

## **European foreword**

This document (EN 1971-1:2019) has been prepared by Technical Committee CEN/TC 133 “Copper and copper alloys”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2020, and conflicting national standards shall be withdrawn at the latest by May 2020.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 1971-1:2011.

The following modifications were implemented in this new edition of EN 1971-1:

— updated normative references.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

**EN 1971-1:2019 (E)****Introduction**

The eddy current test described in this document has the objective of detecting during production potential leaks and serious defects in seamless round copper and copper alloy tubes.

The eddy current test is able to detect material inhomogeneities and their positions throughout the length of tubes. The eddy current signals of material inhomogeneities are compared with reference signals of artificially produced test defects. It is possible to identify these inhomogeneities on the inner and outer surfaces as well as within the tube wall.

Since the distribution of eddy currents decreases as the distance from the test coil increases, the amplitude of defect signals also decreases with increasing distance from the test coil. Thus the eddy current test with encircling test coil on the outer surface is less sensitive to defects on the inner surface.

The purpose of this European Standard is not to define a method of measuring the actual extent of the material inhomogeneities as the signal amplitude is dependent on, amongst other factors, volume, form and position of the inhomogeneity.

Due to end effects, it is not possible to effectively test the ends of the tubes. The purchaser and the supplier could agree that the end effect may be overcome by cutting to length after testing.

## 1 Scope

This document specifies a procedure for the eddy current test with an encircling test coil for measuring defects on the outer surface of seamless round copper and copper alloy tubes.

NOTE The eddy current test method(s) required, together with the size range and acceptance level, are defined in the relevant product standard.

The choice of the method for eddy current test:

— with an encircling test coil on the outer surface according to EN 1971-1;

or

— with an internal probe on the inner surface according to EN 1971-2;

is at the discretion of the manufacturer if there are no other agreements between the purchaser and the supplier.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN ISO 9712, *Non-destructive testing - Qualification and certification of NDT personnel (ISO 9712)*

EN ISO 12718, *Non-destructive testing - Eddy current testing - Vocabulary (ISO 12718)*

**koniec náhľadu – text ďalej pokračuje v platenej verzii STN**