

<b>STN</b>	<b>Žiarové striekanie</b> <b>Skúška rúrkového povlaku ťahom</b>	<b>STN</b> <b>EN 17393</b>  03 8734
------------	--	--

Thermal spraying - Tubular coating tensile test

Táto norma obsahuje anglickú verziu európskej normy.  
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 11/20

Obsahuje: EN 17393:2020

**131742**

EUROPEAN STANDARD

**EN 17393**

NORME EUROPÉENNE

EUROPÄISCHE NORM

July 2020

ICS 25.220.20

English Version

**Thermal spraying - Tubular coating tensile test**

Projection thermique - Essai de traction

Thermisches Spritzen - Schichtzugversuch

This European Standard was approved by CEN on 17 May 2020.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

**EN 17393:2020 (E)****Contents**

Page

<b>European foreword</b> .....	<b>3</b>
<b>Introduction</b> .....	<b>4</b>
<b>1 Scope</b> .....	<b>5</b>
<b>2 Normative references</b> .....	<b>5</b>
<b>3 Terms and definitions</b> .....	<b>5</b>
<b>4 Testing equipment</b> .....	<b>6</b>
<b>5 Specimens</b> .....	<b>7</b>
5.1 <b>Shape of base samples</b> .....	<b>7</b>
5.2 <b>Preparation of the specimen to be sprayed</b> .....	<b>7</b>
5.3 <b>Specimen to be sprayed, preparation and coating</b> .....	<b>8</b>
5.4 <b>Determination of outer diameter</b> .....	<b>8</b>
5.5 <b>Number of specimens to be tested</b> .....	<b>8</b>
<b>6 Test procedure</b> .....	<b>8</b>
<b>7 Possible sources of fault during procedure</b> .....	<b>9</b>
<b>8 Evaluation</b> .....	<b>9</b>
<b>9 Test report</b> .....	<b>10</b>
<b>Annex A (informative) Test report for the tubular coating tensile (TCT) test according to EN 17393</b> .....	<b>11</b>
<b>A.1 General</b> .....	<b>11</b>
<b>A.2 TCT specimen</b> .....	<b>11</b>
<b>A.3 Surface preparation for spraying</b> .....	<b>11</b>
<b>A.4 Spraying procedure for TCT specimens — Component</b> .....	<b>11</b>
<b>A.5 Preparation of specimens for the tubular coating tensile (TCT) test</b> .....	<b>12</b>
<b>A.6 Testing of TCT specimens</b> .....	<b>12</b>
<b>A.7 Test results</b> .....	<b>13</b>
<b>Bibliography</b> .....	<b>14</b>

## **European foreword**

This document (EN 17393:2020) has been prepared by Technical Committee CEN/TC 240 “Thermal spraying and thermally sprayed coatings”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2021, and conflicting national standards shall be withdrawn at the latest by January 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

**EN 17393:2020 (E)****Introduction**

The determination of tensile strength of a thermally sprayed coating can be of substantial importance regarding product-supporting quality control as well as coating development and, moreover, can have an effect on important factors such as transfer efficiency, microstructure, surface quality, etc. Only a little effort is required to carry out the tubular coating tensile test (TCT). However, it provides reproducible values for the mechanical strength of sprayed coatings and gives information on influences resulting from spraying conditions.

Microscopic examinations of the fractured surface can provide further information on failure modes and support the quality assessment of the coating microstructure as well as the assessment of influences resulting from loads during the TCT test.

## 1 Scope

This document specifies the procedure for the determination of coating strength, and hence of cohesive strength in a tubular coating tensile test.

The test is intended to determine the tensile coating strength parallel to the spray layers (normal to the spray direction) and to identify differences in particle cohesion quality, as caused by defects as internal delamination at cracks or oxides between the spray particles or splats.

The tubular coating tensile test is suitable for sprayed coatings deposited using metallic materials (not carbides and ceramics).

The tubular coating tensile test is not suitable for fused sprayed coatings deposited using self-fluxing alloys.

The test supports quality assurance and is intended to be applied for the purpose of coating optimization by identifying the influences of coating parameters and spray materials on the coatings's quality. Furthermore, the coating in particular for cold sprayed coatings can be compared with the characteristics of similar solid materials and the coating's quality can be assessed.

This test is not recommended for thin coatings (coating thickness < 500 µm), since massive scattering of results is to be expected here. Due to the size of the specimen, it is particularly suitable to apply the tubular coating tensile test for coating processes that use a concentrated spray jet and a highly focused spray spot, as in the case of cold spraying, high velocity flame spraying (HVOF) or plasma spraying. Applying the tubular coating tensile test for coating processes that use a broad spray jet, such as flame spraying and arc spraying, may require special spraying measures, e.g. the use of a template to ensure a nearly vertical impingement angle.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN ISO 14916, *Thermal spraying — Determination of tensile adhesive strength (ISO 14916)*

EN ISO 14917, *Thermal spraying — Terminology, classification (ISO 14917)*

EN ISO 7500-1:2018, *Metallic materials — Calibration and verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Calibration and verification of the force-measuring system (ISO 7500-1:2018)*

**koniec náhľadu – text ďalej pokračuje v platenej verzii STN**