

STN	Náterové látky Praktické stanovenie obsahu neprchavých a prchavých látok počas nanášania (ISO 22516: 2019)	STN EN ISO 22516 67 3052
------------	---	--

Paints and varnishes - Practical determination of non-volatile and volatile matter content during application (ISO 22516:2019)

Táto norma obsahuje anglickú verziu európskej normy.
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 03/21

Obsahuje: EN ISO 22516:2020, ISO 22516:2019

132426

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 22516

December 2020

ICS 87.040

English Version

Paints and varnishes - Practical determination of non-volatile and volatile matter content during application (ISO 22516:2019)

Peintures et vernis - Détermination pratique de la matière non volatile et de la matière volatile pendant l'application (ISO 22516:2019)

Beschichtungsstoffe - Praxisnahe Bestimmung des Gehaltes an nichtflüchtigen und flüchtigen Anteilen während des Beschichtungsprozesses (ISO 22516:2019)

This European Standard was approved by CEN on 30 November 2020.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

EN ISO 22516:2020 (E)

Contents	Page
European foreword.....	3

European foreword

The text of ISO 22516:2019 has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 22516:2020 by Technical Committee CEN/TC 139 "Paints and varnishes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2021, and conflicting national standards shall be withdrawn at the latest by June 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 22516:2019 has been approved by CEN as EN ISO 22516:2020 without any modification.

INTERNATIONAL STANDARD

ISO
22516

First edition
2019-06

Paints and varnishes — Practical determination of non-volatile and volatile matter content during application

*Peintures et vernis — Détermination pratique de la matière non
volatile et de la matière volatile pendant l'application*



Reference number
ISO 22516:2019(E)

© ISO 2019

ISO 22516:2019(E)**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Apparatus and materials	2
6 Sampling	3
7 Procedure	3
7.1 General.....	3
7.2 Method A: Determination with aluminium foils.....	3
7.3 Method B: Determination with test panels.....	4
8 Evaluation	4
9 Precision	4
9.1 Repeatability limit (<i>r</i>).....	4
9.2 Reproducibility limit (<i>R</i>).....	5
10 Test report	5
Annex A (informative) Comments on precision	6
Bibliography	9

ISO 22516:2019(E)**Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

When applying coatings, the size or the size distribution of the generated drops is of great importance for the application result. By varying the application parameters, such as spraying energy and the rate of flow of the coating material as well as the technical properties such as solvent composition and rheological flow performance, the quality of the application result can be controlled. Also, climatic conditions during the application (e.g. temperature, relative humidity, and air falling speed) highly influence the result. By determining the non-volatile matter after application or after intermediate or final drying, it is possible to characterize the wet or dry application result and, consequently, to indirectly refer to the generated drop size distribution and the solvent emission during the application. By means of the calculated volatile matter, the sufficient intermediate drying of the respective coating is determined before applying an additional coating.

Paints and varnishes — Practical determination of non-volatile and volatile matter content during application

1 Scope

This document specifies a test method for the determination of non-volatile matter of coatings directly after application or after intermediate or final drying. In practice, the determination of volatile matter is applied particularly in regard to water-thinnable coatings which are re-coated with an additional coating material.

Furthermore, the method can be used to compare the efficiency of different application and drying methods.

The content of non-volatile or volatile matter of a product after application is no absolute variable but depends on the application and drying conditions applied during the test. Consequently, applying this method gives only relative values and not the real values for the content of non-volatile matter, due to solvent retention, thermal decomposition and evaporation of low-molecular contents.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1513, *Paints and varnishes — Examination and preparation of test samples*

ISO 1514, *Paints and varnishes — Standard panels for testing*

ISO 4618, *Paints and varnishes — Terms and definitions*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

koniec náhľadu – text ďalej pokračuje v platenej verzii STN