

<b>STN</b>	<b>Bodové trecie zváranie s premiešáním Hliník Časť 2: Navrhovanie zvarových spojov (ISO 18785-2: 2018)</b>	<b>STN EN ISO 18785-2</b>  05 2830
------------	---	--

Friction stir spot welding - Aluminium - Part 2: Design of weld joints (ISO 18785-2:2018)

Táto norma obsahuje anglickú verziu európskej normy.  
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 06/21

Obsahuje: EN ISO 18785-2:2021, ISO 18785-2:2018

**132622**

EUROPEAN STANDARD

EN ISO 18785-2

NORME EUROPÉENNE

EUROPÄISCHE NORM

January 2021

ICS 25.160.40

English Version

## Friction stir spot welding - Aluminium - Part 2: Design of weld joints (ISO 18785-2:2018)

Soudage par friction-malaxage par points - Aluminium  
- Partie 2: Conception des assemblages soudés (ISO  
18785-2:2018)

Rührreibpunktschweißen - Aluminium - Teil 2:  
Konstruktion der Schweißverbindung (ISO 18785-  
2:2018)

This European Standard was approved by CEN on 6 December 2020.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

**EN ISO 18785-2:2021 (E)**

<b>Contents</b>	<b>Page</b>
<b>European foreword.....</b>	<b>3</b>

## **European foreword**

The text of ISO 18785-2:2018 has been prepared by Technical Committee ISO/TC IIW "International Institute of Welding" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 18785-2:2021 by Technical Committee CEN/TC 121 "Welding and allied processes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2021, and conflicting national standards shall be withdrawn at the latest by July 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## **Endorsement notice**

The text of ISO 18785-2:2018 has been approved by CEN as EN ISO 18785-2:2021 without any modification.

# INTERNATIONAL STANDARD

# ISO 18785-2

First edition  
2018-11

---

---

## Friction stir spot welding — Aluminium —

### Part 2: Design of weld joints

*Soudage par friction-malaxage par points — Aluminium —  
Partie 2: Conception des assemblages soudés*



Reference number  
ISO 18785-2:2018(E)

© ISO 2018

**ISO 18785-2:2018(E)****COPYRIGHT PROTECTED DOCUMENT**

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>v</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Design requirements</b> .....	<b>1</b>
4.1 Documentation.....	1
4.2 Lap joint design.....	1
4.3 Additional information.....	4
4.3.1 Essential information.....	4
4.3.2 Spot weld variables.....	4
4.3.3 Inspection.....	4

## ISO 18785-2:2018(E)

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by the IIW, *International Institute of Welding*, Commission III, *Resistance welding, solid state welding and allied joining processes*.

Any feedback, question or request for official interpretation related to any aspect of this document should be directed to IIW via your national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

A list of all parts in the ISO 18785 series can be found on the ISO website.



## Introduction

Welding processes are widely used in the fabrication of engineered structures. During the second half of the twentieth century, fusion welding processes, wherein fusion is obtained by the melting of parent material and usually a filler metal, dominated the welding of large structures. In 1991, friction stir welding (FSW), which is carried out entirely in the solid phase (no melting), was invented.

Friction stir spot welding (FSSW) processes are spot-like variants of the FSW process. Unlike FSW, there is minimal or no traverse motion of the tool. In basic FSSW, the joint is created by plunging a rotating tool into the work piece and retracting the tool out of the overlapping sheets. Other FSSW variants include additional tool movements. Frictional heat is generated from the contact between the tool and the material to be welded resulting in softening of this material. The softened material is stirred to form a metallurgical connection which is aided by the forge action applied by the tool shoulder contacting the upper sheet surface.

The increasing use of FSSW has created the need for a FSSW standard in order to ensure that welding is carried out in the most effective way and that appropriate control is exercised over all aspects of the operation. The ISO 18785 series focuses on the FSSW of aluminium because, at the time this document was developed, the majority of commercial applications for FSW involved aluminium. Examples include railway cars, consumer products, food processing equipment, automotive components, aerospace structures, and marine vessels.

To be effective, welded structures should be free from serious problems in production and in service. To achieve that goal, it is necessary to provide controls from the design phase through material selection, fabrication, and inspection. For example, poor design can create serious and costly difficulties in the workshop, on site, or in service. Incorrect material selection can result in welding problems such as cracking. Welding procedures need to be correctly formulated and approved to avoid imperfections. To ensure the fabrication of a quality product, management needs to understand the sources of potential trouble and introduce appropriate quality and inspection procedures, and supervision should be implemented to ensure that the specified quality is achieved.



# Friction stir spot welding — Aluminium —

## Part 2: Design of weld joints

### 1 Scope

This document specifies the design requirements and provides design guidelines for friction stir spot welding.

In this document, the term "aluminium" refers to aluminium and its alloys.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2553, *Welding and allied processes — Symbolic representation on drawings — Welded joints*

ISO 18785-1, *Friction stir spot welding — Aluminium — Part 1: Vocabulary*

ISO 18785-5, *Friction stir spot welding — Aluminium — Part 5: Quality and inspection requirements*

**koniec náhľadu – text ďalej pokračuje v platenej verzii STN**