STN	Ropný a plynárenský priemysel Materiály na používanie v prostredí s obsahom sírovodíka pri produkcii ropy a plynu Časť 3: CRA (koróziovzdorné zliatiny) a iné zliatiny odolné proti tvoreniu trhlín (ISO 15156-3: 2020)	STN EN ISO 15156-3
		45 1500

Petroleum and natural gas industries - Materials for use in H2S-containing environments in oil and gas production - Part 3: Cracking-resistant CRAs (corrosion-resistant alloys) and other alloys (ISO 15156-3:2020)

Táto norma obsahuje anglickú verziu európskej normy. This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 05/21

Obsahuje: EN ISO 15156-3:2020, ISO 15156-3:2020

Oznámením tejto normy sa ruší STN EN ISO 15156-3 (45 1500) z februára 2016

132746

Úrad pre normalizáciu, metrológiu a skúšobníctvo Slovenskej republiky, 2021 Slovenská technická norma a technická normalizačná informácia je chránená zákonom č. 60/2018 Z. z. o technickej normalizácii.

EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

EN ISO 15156-3

November 2020

ICS 75.180.01

Supersedes EN ISO 15156-3:2015

English Version

Petroleum and natural gas industries - Materials for use in H2S-containing environments in oil and gas production -Part 3: Cracking-resistant CRAs (corrosion-resistant alloys) and other alloys (ISO 15156-3:2020)

Industries du pétrole et du gaz naturel - Matériaux pour utilisation dans des environnements contenant de l'hydrogène sulfuré (H2S) dans la production de pétrole et de gaz - Partie 3: ARC (alliages résistants à la corrosion) et autres alliages résistants à la fissuration (ISO 15156-3:2020) Erdöl- und Erdgasindustrie - Werkstoffe für den Einsatz in H2S-haltiger Umgebung bei der Öl- und Gasgewinnung - Teil 3: Hochlegierte Stähle (CRAs) und andere Legierungen (ISO 15156-3:2020)

This European Standard was approved by CEN on 12 October 2020.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

© 2020 CEN All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.

Ref. No. EN ISO 15156-3:2020 E

Contents	Page
European foreword	

European foreword

This document (EN ISO 15156-3:2020) has been prepared by Technical Committee ISO/TC 67 "Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries" in collaboration with Technical Committee CEN/TC 12 "Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries" the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2021, and conflicting national standards shall be withdrawn at the latest by May 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 15156-3:2015.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 15156-3:2020 has been approved by CEN as EN ISO 15156-3:2020 without any modification.

INTERNATIONAL STANDARD



Fourth edition 2020-11

Petroleum and natural gas industries — Materials for use in H_2 S-containing environments in oil and gas production —

Part 3: Cracking-resistant CRAs (corrosionresistant alloys) and other alloys

Industries du pétrole et du gaz naturel — Matériaux pour utilisation dans des environnements contenant de l'hydrogène sulfuré (H_2S) dans la production de pétrole et de gaz —

Partie 3: ARC (alliages résistants à la corrosion) et autres alliages résistants à la fissuration



Reference number ISO 15156-3:2020(E)



COPYRIGHT PROTECTED DOCUMENT

STN EN ISO 15156-3: 2021

ISO 15156-3:2020(E)

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Page

Contents

Forew	ord			iv
Introd	uction			vi
1	Scope			
2	Normative references			2
3	Terms and definitions			3
4	Symbols and abbreviated terms			5
5	Factors affecting the cracking-resistance of CRAs and other alloys in H ₂ S-containing environments			6
6	Qualif GHSC 6.1 6.2 6.3	fication a in H₂S-c General Evaluat 6.2.1 6.2.2 6.2.3 PREN	and selection of CRAs and other alloys with respect to SSC, SCC, and ontaining environments ion of materials properties Hardness of parent metals Cracking-resistance properties of welds Cracking-resistance properties associated with other fabrication methods	6 7 7 7 8 9
7	Purchasing information and marking7.1Information that should be supplied for material purchasing7.2Marking, labelling, and documentation		9 9	
Annex	A (nor Table	mative) <mark>A.1</mark> — G	Environmental cracking-resistant CRAs and other alloys (including uidance on the use of the materials selection tables)	11
Annex	B (nor	mative)	Qualification of CRAs for H ₂ S-service by laboratory testing	57
Annex	C (info	ormative]) Information that should be supplied for material purchasing	67
Annex	Annex D (informative) Nominated sets of test conditions			
Biblio	graphy	<i></i>		70

ISO 15156-3:2020(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries,* in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 12, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries,* in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fourth edition cancels and replaces the third edition (ISO 15156-3:2015), which has been technically revised. The main changes compared to the previous edition are as follows:

- <u>Table A.27</u> UNS S17400 (17-4PH SS) has new limits. The use of the alloy at the annotated environmental conditions is now limited to applications where sustained stress is no more than 50 % of SMYS;
- Table A.32 new limits and annotations for UNS N09946 separate from UNS N09945;
- <u>Table A.41</u> inclusion of UNS R55400 (new a-b Ti alloy);
- <u>Table A.3</u> UNS S20910 (Nitronic 50) note modifications;
- <u>Tables A.22</u>, <u>A.23</u>, <u>A.26</u> through <u>A.30</u>, and <u>A.33</u> temperature conversion corrections;
- <u>Table A.23</u> new note for maximum design tensile stress for UNS J91540;
- <u>Table A.32</u> newly added UNS N07718 (high strength Alloy 718, with two-step aging cycle, meeting API 6A CRA composition and a maximum hardness of 45 HRC) and UNS N09955 requirements and note letters designation changes on UNS N09925, N09935, N09945 and N09946;
- <u>Table A.40</u> title modification and note clarification;
- <u>Clause A.13</u> Cladding, overlays, and wear-resistant alloys modifications;
- <u>Table A.18</u> and <u>Table A.19</u> (Martensitic SS) remarks modifications;
- <u>Table A.24</u> Duplex SS Hot Isostatically Pressed (HIP) inclusion and remarks modification;

- the informative Annex D, "Materials chemical compositions and other information", has been removed due to copyright reasons;
- additions to the bibliography.

A list of all parts in the ISO 15156 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at <u>www.iso.org/members.html</u>.

ISO 15156-3:2020(E)

Introduction

The consequences of sudden failures of metallic oil and gas field components associated with their exposure to H_2S -containing production fluids led to the preparation of the first edition of NACE MR0175 which was published in 1975 by the National Association of Corrosion Engineers, now known as NACE International.

The original and subsequent editions of NACE MR0175 established limits of H_2S partial pressure above which precautions against sulfide stress cracking (SSC) were always considered necessary. They also provided guidance for the selection and specification of SSC-resistant materials when the H_2S thresholds were exceeded. In more recent editions, NACE MR0175 has also provided application limits for some corrosion-resistant alloys in terms of environmental composition and pH, temperature, and H_2S partial pressures.

In separate developments, the European Federation of Corrosion issued EFC Publication 16 in 1995 and EFC Publication 17 in 1996. These documents are generally complementary to those of NACE, though they differed in scope and detail.

In 2003, the publication of the ISO 15156 series and NACE MR0175/ISO 15156 was completed for the first time. These technically identical documents utilized the above sources to provide requirements and recommendations for materials qualification and selection for application in environments containing wet H_2S in oil and gas production systems. They are complemented by NACE TM0177 and NACE TM0284 test methods.

The revision of this document, i.e. ISO 15156, involves a consolidation of all changes agreed and published in the Technical Circular 1, ISO 15156-3:2015/Cir.1:2016, the Technical Circular 2, ISO 15156-3:2015/Cir.2:2018 and the Technical Circular 3, ISO 15156-3:2015/Cir.3:2019, published by the ISO 15156 series Maintenance Agency secretariat at DIN.

The changes were developed by, and approved by the ballot of, representative groups from within the oil and gas production industry. The great majority of these changes stem from issues raised by document users. A description of the process by which these changes were approved can be found at the ISO 15156 series maintenance website: www.iso.org/iso15156maintenance.

When found necessary by oil and gas production industry experts, future interim changes to this document will be processed in the same way and will lead to interim updates to this document in the form of Technical Corrigenda or Technical Circulars. Document users should be aware that such documents can exist and can impact the validity of the dated references in this document.

The ISO 15156 series Maintenance Agency at DIN was set up after approval by the ISO Technical Management Board given in document 34/2007. This document describes the makeup of the agency, which includes experts from NACE, EFC, and ISO/TC 67, and the process for approval of amendments. It is available from the ISO 15156 series maintenance website and from the ISO/TC 67 Secretariat. The website also provides access to related documents that provide more detail of the ISO 15156 series maintenance activities.

Petroleum and natural gas industries — Materials for use in H_2S -containing environments in oil and gas production —

Part 3: Cracking-resistant CRAs (corrosion-resistant alloys) and other alloys

WARNING — CRAs (corrosion-resistant alloys) and other alloys selected using this document are resistant to cracking in defined H_2S -containing environments in oil and gas production, but not necessarily immune to cracking under all service conditions. It is the equipment user's responsibility to select the CRAs and other alloys suitable for the intended service.

1 Scope

This document gives requirements and recommendations for the selection and qualification of CRAs (corrosion-resistant alloys) and other alloys for service in equipment used in oil and natural gas production and natural gas treatment plants in H_2S -containing environments whose failure can pose a risk to the health and safety of the public and personnel or to the environment. It can be applied to help avoid costly corrosion damage to the equipment itself. It supplements, but does not replace, the materials requirements of the appropriate design codes, standards, or regulations.

This document addresses the resistance of these materials to damage that can be caused by sulfide stress cracking (SSC), stress corrosion cracking (SCC), and galvanically induced hydrogen stress cracking (GHSC).

This document is concerned only with cracking. Loss of material by general (mass loss) or localized corrosion is not addressed.

Table 1 provides a non-exhaustive list of equipment to which this document is applicable, including exclusions.

This document applies to the qualification and selection of materials for equipment designed and constructed using load controlled design methods. For design utilizing strain-based design methods, see ISO 15156-1:2020, Clause 5.

This document is not necessarily suitable for application to equipment used in refining or downstream processes and equipment.

STN EN ISO 15156-3: 2021

ISO 15156-3:2020(E)

This document is applicable to materials used for the following equipment	Exclusions		
Drilling, well construction, and well-servicing equipment	Equipment exposed only to drilling fluids of con- trolled composition ^a		
	Drill bits		
	Blowout-preventer (BOP) shear blades ^b		
	Drilling riser systems		
	Work strings		
	Wireline and wireline equipment ^c		
	Surface and intermediate casing		
Wells including subsurface equipment, gas lift	Sucker rod pumps and sucker rods ^d		
equipment, wellheads, and christmas trees	Electric submersible pumps		
	Other artificial lift equipment		
	Slips		
Flow-lines, gathering lines, field facilities, and field processing plants	Crude oil storage and handling facilities operating at a total absolute pressure below 0.45 MPa (65 psi)		
Water-handling equipment	Water-handling facilities operating at a total absolute pressure below 0,45 MPa (65 psi)		
	Water injection and water disposal equipment		
Natural gas treatment plants	—		
Transportation pipelines for liquids, gases, and multi-phase fluids	Lines handling gas prepared for general commer- cial and domestic use		
For all equipment above	Components loaded only in compression		
See ISO 15156-2:2020, A.2.3.2.3 for more information.			
See ISO 15156-2:2020, A.2.3.2.1 for more information.			
Wireline lubricators and lubricator connecting devices are not excluded.			
d For sucker rod pumps and sucker rods, reference can be made	For sucker rod pumps and sucker rods, reference can be made to NACE MR0176.		

Table 1 — List of equipment

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6507-1, Metallic materials — Vickers hardness test — Part 1: Test method

ISO 6508-1, Metallic materials — Rockwell hardness test — Part 1: Test method

ISO 6892-1, Metallic materials — Tensile testing — Part 1: Method of test at room temperature

ISO 10423, Petroleum and natural gas industries — Drilling and production equipment — Wellhead and christmas tree equipment

ISO 11960, Petroleum and natural gas industries — Steel pipes for use as casing or tubing for wells

ISO 15156-1:2020, Petroleum and natural gas industries — Materials for use in H_2S -containing environments in oil and gas production — Part 1: General principles for selection of cracking-resistant materials

ISO 15156-2:2020, Petroleum and natural gas industries — Materials for use in H_2S -containing environments in oil and gas production — Part 2: Cracking-resistant carbon and low alloy steels, and the use of cast irons

ASTM A747/A747M¹), Standard Specification for Steel Castings, Stainless, Precipitation Hardening

ASTM E29, Standard Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

ASTM E562, Standard Test Method for Determining Volume Fraction by Systematic Manual Point Count

EFC Publication 17^{2} , Corrosion resistant alloys for oil and gas production: guidelines on general requirements and test methods for H_2S service

NACE CORROSION/95 Paper 47, Test methodology for elemental sulfur-resistant advanced materials for oil and gas field equipment

NACE TM0177:2016, Laboratory testing of metals for resistance to sulfide stress cracking and stress corrosion cracking in H_2S environments

SAE AMS-2430³), Shot Peening

SAE — ASTM, Metals and alloys in the Unified Numbering System

koniec náhľadu – text ďalej pokračuje v platenej verzii STN

¹⁾ www.astm.org

²⁾ www.efcweb.org

³⁾ www.sae.org