

<b>TNI</b>	<b>Priemyselné hnojivá Stanovenie obsahu prachu</b>	<b>TNI CEN/TR 14061</b>  65 4813
------------	---	--

Fertilizers - Determination of dust content

Táto technická normalizačná informácia obsahuje anglickú verziu CEN/TR 14061:2021.  
This Technical standard information includes the English version of CEN/TR 14061:2021.

Táto technická normalizačná informácia bola oznámená vo Vestníku ÚNMS SR č. 08/21

**133259**

**TECHNICAL REPORT****CEN/TR 14061****RAPPORT TECHNIQUE****TECHNISCHER BERICHT**

June 2021

ICS 65.080

Supersedes CR 14061:2000

English Version

**Fertilizers - Determination of dust content**

Engrais - Détermination de la teneur en poussière

Düngemittel - Bestimmung des Staubgehaltes

This Technical Report was approved by CEN on 23 May 2021. It has been drawn up by the Technical Committee CEN/TC 260.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

**CEN/TR 14061:2021 (E)**

<b>Contents</b>		<b>Page</b>
<b>European foreword</b> .....		<b>3</b>
<b>Introduction</b> .....		<b>4</b>
<b>1</b>	<b>Scope</b> .....	<b>5</b>
<b>2</b>	<b>Normative references</b> .....	<b>5</b>
<b>3</b>	<b>Terms and definitions</b> .....	<b>5</b>
<b>4</b>	<b>Symbols and abbreviated terms</b> .....	<b>5</b>
<b>4.1</b>	<b>Technical Symbols</b> .....	<b>5</b>
<b>4.2</b>	<b>Statistical symbols and abbreviations</b> .....	<b>6</b>
<b>5</b>	<b>Calculation of the spouting bed apparatus</b> .....	<b>6</b>
<b>5.1</b>	<b>Particle terminal velocity</b> .....	<b>6</b>
<b>5.2</b>	<b>Spouting section</b> .....	<b>7</b>
<b>5.3</b>	<b>Maximum spoutable bed height</b> .....	<b>7</b>
<b>5.4</b>	<b>Design of apparatus</b> .....	<b>7</b>
<b>5.5</b>	<b>Flowmeter</b> .....	<b>8</b>
<b>6</b>	<b>Initial testing</b> .....	<b>8</b>
<b>6.1</b>	<b>Determination of dust weight</b> .....	<b>8</b>
<b>6.2</b>	<b>Setting the test time</b> .....	<b>8</b>
<b>6.3</b>	<b>Preliminary ringtests</b> .....	<b>8</b>
<b>7</b>	<b>Conclusive ring test</b> .....	<b>9</b>
<b>7.1</b>	<b>General</b> .....	<b>9</b>
<b>7.2</b>	<b>Apparatus</b> .....	<b>9</b>
<b>7.3</b>	<b>Sample preparation</b> .....	<b>9</b>
<b>7.4</b>	<b>Procedure, test plan</b> .....	<b>9</b>
<b>7.5</b>	<b>Statistical methods</b> .....	<b>9</b>
<b>7.5.1</b>	<b>Statistical model</b> .....	<b>9</b>
<b>7.5.2</b>	<b>Outliers</b> .....	<b>9</b>
<b>7.5.3</b>	<b>Regression analysis</b> .....	<b>9</b>
<b>7.5.4</b>	<b>Correction for adapter-effect</b> .....	<b>9</b>
<b>7.5.5</b>	<b>ANOVA-analysis</b> .....	<b>9</b>
<b>7.6</b>	<b>Statistical analysis of test data</b> .....	<b>10</b>
<b>7.6.1</b>	<b>Deviation from test plan</b> .....	<b>10</b>
<b>7.6.2</b>	<b>Example — granulated NPK</b> .....	<b>10</b>
<b>7.6.3</b>	<b>Summary of ANOVA</b> .....	<b>14</b>
<b>8</b>	<b>Other methods</b> .....	<b>15</b>
<b>9</b>	<b>Conclusion</b> .....	<b>15</b>
<b>Annex A (informative) Method for the determination of dust potential</b> .....		<b>16</b>
<b>Annex B (informative) Optical methods for determination of fertilizer dust</b> .....		<b>22</b>
<b>Bibliography</b> .....		<b>23</b>

## **European foreword**

This document (CEN/TR 14061:2021) has been prepared by Technical Committee CEN/TC 260 “Fertilizers and liming materials”, the secretariat of which is held by DIN.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes CR 14061:2000.

Significant changes between this document and CR 14061:2000 are as follows:

- a) modification of the figures to contain neutral language;
- b) adaption to current principles and rules for structure and drafting.

This document is published by the European Committee for Standardization. It is published for information only and does not have the status of a European Standard.

The Annexes A and B are informative.

**CEN/TR 14061:2021 (E)****Introduction****0.1 General**

In production and handling of fertilizers dust generation is of great concern by both producers and users of the fertilizer products. For health and environmental reasons, it is of great interest to control and reduce the amount of dust generation. In the fertilizer industries there are a wide variety of apparatus for dust determination, most being used as “in-house” methods in plants and laboratories.

The content of this document was developed by CEN/TC 260/WG 2 between 1991 and 2000 in order to develop a standard dust test. A spouting bed apparatus was designed for gravimetric determination of dust, and after two preliminary ringtests a conclusive ringtest involving six laboratories was carried out. Not being able to develop a statistical significant method for the determination of dust, TC 260 decided by resolution 105/1997 to change the deliverable of this work item into a CEN Technical Report. The change of deliverable has been approved by CEN/BT with its resolution BT C172/1999.

**0.2 General background**

When handling fertilizer grains, dust is at every moment generated on the surface. The fertilizer thus contains more or less free dust, and has a potential for generating more dust (abrasion dust) when subject to subsequent handling.

In all existing gravitational test methods dust will be generated during the testing time, and the two types of dust will be measured simultaneously. The scope of the method is expressed in Annex A and the aim is to:

*“...specify a method for the determination of the **dust potential** of solid fertilizers and is applicable to granular and prilled fertilizers.*

*Dust particles, which cause reduced visibility in air are too small to be determined by this method.”*

**0.3 Background for choice of method**

Fluidized particle powders are generally divided into four characterizing groups (A, B, C, D) [1]. Group C particles are small, cohesive and are difficult to fluidize. Aeratable powders belong to group A, and many fluidized bed catalysts characterize this group. Sand typifies group B, in which inter-particle forces are negligible, in contrast with group A powders. Large and/or dense particles in general belong to group D, and fertilizer particles (2 mm to 4 mm) in air are in this group. A flow diagram can be used to broadly identify flow regimes appropriate to combinations of gas velocity and particle properties. It can be shown that the fertilizer system is in the lower part of the spouted bed regime.

A criterion that can be used to distinguish between group B and D is the numerical inequality that classifies a powder as spoutable if:

$$(\rho_p - \rho_f) \cdot d_p^{1,24} > 0,23$$

For a typical fertilizer this value will be about 1,4 and about 0,5 for an urea prill.

From previous experiments with other methods based on a fluidized bed and the above calculations, it was decided to base the method upon the spouted bed principle.

## **1 Scope**

This document is applicable to the determination of dust potential of solid fertilizer, obtained in prilling or granulation process. Compacted or crystalline materials were not considered.

## **2 Normative references**

There are no normative references in this document.

**koniec náhľadu – text ďalej pokračuje v platenej verzii STN**