

STN	Textílie Stanovenie zotavenia po pokrčení zloženej vzorky tkaniny meraním uhla zotavenia Časť 2: Metóda vertikálne zloženej vzorky (ISO 2313-2: 2021)	STN EN ISO 2313-2 80 0820
------------	--	---

Textiles - Determination of the recovery from creasing of a folded specimen of fabric by measuring the angle of recovery - Part 2: Method of the vertically folded specimen (ISO 2313-2:2021)

Táto norma obsahuje anglickú verziu európskej normy.
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 09/21

Obsahuje: EN ISO 2313-2:2021, ISO 2313-2:2021

Spolu s STN EN ISO 2313-1 ruší
STN EN 22313 (80 0820) zo septembra 1995

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 2313-2

June 2021

ICS 59.080.30

Supersedes EN 22313:1992

English Version

**Textiles - Determination of the recovery from creasing of a
folded specimen of fabric by measuring the angle of
recovery - Part 2: Method of the vertically folded specimen
(ISO 2313-2:2021)**

Textiles - Détermination de l'auto-défroissabilité d'une
échantillon d'étoffe pliée, par mesurage de l'angle
rémanent après pliage - Partie 2: Méthode de
l'échantillon pliée verticalement (ISO 2313-2:2021)

Textilien - Bestimmung des
Knittererholungsvermögens eines Prüflings durch
Messung des Knittererholungswinkels - Teil 2:
Verfahren mit vertikaler Faltenkante des Prüflings (ISO
2313-2:2021)

This European Standard was approved by CEN on 18 May 2021.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

EN ISO 2313-2:2021 (E)

Contents	Page
European foreword.....	3

European foreword

This document (EN ISO 2313-2:2021) has been prepared by Technical Committee ISO/TC 38 "Textiles" in collaboration with Technical Committee CEN/TC 248 "Textiles and textile products" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2021, and conflicting national standards shall be withdrawn at the latest by December 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 22313:1992.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 2313-2:2021 has been approved by CEN as EN ISO 2313-2:2021 without any modification.

INTERNATIONAL STANDARD

ISO
2313-2

First edition
2021-05

Textiles — Determination of the recovery from creasing of a folded specimen of fabric by measuring the angle of recovery —

Part 2: Method of the vertically folded specimen

*Textiles — Détermination de l'auto-défroissabilité d'une éprouvette
d'étoffe pliée, par mesurage de l'angle rémanent après pliage —*

Partie 2: Méthode de l'éprouvette pliée verticalement



Reference number
ISO 2313-2:2021(E)

© ISO 2021

ISO 2313-2:2021(E)**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Apparatus	2
6 Sampling and preparation of specimens	3
7 Atmosphere for conditioning and testing	5
8 Test procedure	5
9 Expression of results	6
10 Test report	6
Annex A (informative) Example of automatic tester	7

ISO 2313-2:2021(E)**Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 24, *Conditioning atmospheres and physical tests for textile fabrics*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 248, *Textiles and textile products*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

A list of all parts in the ISO 2313 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Creases in textile fabrics diminish at varying rates on the removal of the creasing forces. The magnitude of the crease recovery angle is an indication of the ability of a fabric to recover from accidental creasing.

The suitable method can be chosen according to the type or end-use of textile fabrics. The test results obtained by different methods are not comparable.

Textiles — Determination of the recovery from creasing of a folded specimen of fabric by measuring the angle of recovery —

Part 2: Method of the vertically folded specimen

1 Scope

This document specifies a method for determining crease recovery angle of fabric specimen while placing it in such a way that the folded line is vertical to horizontal plane for a specified time after removal of creasing load.

This document is applicable for all kinds of textile fabrics.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 139, *Textiles — Standard atmospheres for conditioning and testing*

koniec náhľadu – text ďalej pokračuje v platenej verzii STN