

STN	Kontinuálne lakované kovy Skúšobné metódy Časť 9: Odolnosť pri ponorení do vody	STN EN 13523-9 03 8761
------------	--	--

Coil coated metals - Test methods - Part 9: Resistance to water immersion

Táto norma obsahuje anglickú verziu európskej normy.
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 04/22

Obsahuje: EN 13523-9:2022

Oznámením tejto normy sa ruší
STN EN 13523-9 (03 8761) z novembra 2014

134648

EUROPEAN STANDARD

EN 13523-9

NORME EUROPÉENNE

EUROPÄISCHE NORM

February 2022

ICS 25.220.60

Supersedes EN 13523-9:2014

English Version

Coil coated metals - Test methods - Part 9: Resistance to water immersion

Tôles prélaquées - Méthodes d'essai - Partie 9 :
Résistance à l'immersion dans l'eau

Bandbeschichtete Metalle - Prüfverfahren - Teil 9:
Beständigkeit gegen Eintauchen in Wasser

This European Standard was approved by CEN on 19 December 2021.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

EN 13523-9:2022 (E)

Contents		Page
European foreword		3
1	Scope	5
2	Normative references	5
3	Terms and definitions	5
4	Principle	5
5	Apparatus	6
6	Materials	6
7	Sampling	6
8	Test panels	6
9	Procedure	6
9.1	Scribing of test panels and immersion	6
9.2	Assessment	7
9.2.1	General	7
9.2.2	Blistering	7
9.2.3	Corrosion creep	7
10	Expression of results	7
11	Precision	8
12	Test report	8
Annex A (normative) Scribing of test panels		9
Bibliography		10

European foreword

This document (EN 13523-9:2022) has been prepared by Technical Committee CEN/TC 139 “Paints and varnishes”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2022, and conflicting national standards shall be withdrawn at the latest by August 2022.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13523-9:2014.

The main changes are:

- a) EN ISO 3696 has been added to 6.1 as reference for the deionised water;
- b) a remark concerning the assessment of organic coated steel substrates having multiple metallic phases in zinc based coating has been added to Clause 10;
- c) “test specimen” has been harmonized to “test panel” in the entire text;
- d) the list of the existing parts of EN 13523 has been updated;
- e) the text has been editorially revised and the normative references have been updated.

The EN 13523 series, *Coil coated metals — Test methods*, consists of the following parts:

- *Part 0: General introduction*
- *Part 1: Film thickness*
- *Part 2: Gloss*
- *Part 3: Colour difference and metamerism — Instrumental comparison*
- *Part 4: Pencil hardness*
- *Part 5: Resistance to rapid deformation (impact test)*
- *Part 6: Adhesion after indentation (cupping test)*
- *Part 7: Resistance to cracking on bending (T-bend test)*
- *Part 8: Resistance to salt spray (fog)*
- *Part 9: Resistance to water immersion*
- *Part 10: Resistance to fluorescent UV radiation and water condensation*
- *Part 11: Resistance to solvents (rubbing test)*
- *Part 12: Resistance to scratching*

EN 13523-9:2022 (E)

- *Part 13: Resistance to accelerated ageing by the use of heat*
- *Part 14: Chalking (Helmen method)*
- *Part 16: Resistance to abrasion*
- *Part 17: Adhesion of strippable films*
- *Part 18: Resistance to staining*
- *Part 19: Panel design and method of atmospheric exposure testing*
- *Part 20: Foam adhesion*
- *Part 21: Evaluation of outdoor exposed panels*
- *Part 22: Colour difference — Visual comparison*
- *Part 23: Resistance to humid atmospheres containing sulfur dioxide*
- *Part 24: Resistance to blocking and pressure marking*
- *Part 25: Resistance to humidity*
- *Part 26: Resistance to condensation of water*
- *Part 27: Resistance to humid poultice (Cataplasma test)*
- *Part 29: Resistance to environmental soiling (Dirt pick-up and striping)*

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This document specifies the procedure for determining the resistance to water immersion of an organic coating on a metallic substrate.

The test is applicable to all kinds of organic coatings, including metallics and embossed, textured, pearlescent and printed coatings. The results of the test give an indication of the resistance of the coil coated metal to water.

The method is not intended to reproduce any particular condition of condensation.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 13523-0, *Coil coated metals — Test methods — Part 0: General introduction*

EN 23270, *Paints and varnishes and their raw materials — Temperatures and humidities for conditioning and testing (ISO 3270)*

EN 60454-2, *Pressure-sensitive adhesive tapes for electrical purposes — Part 2: Methods of test (IEC 60454-2)*

EN ISO 3696:1995, *Water for analytical laboratory use — Specification and test methods (ISO 3696:1987)*

EN ISO 4628-2, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 2: Assessment of degree of blistering (ISO 4628-2)*

EN ISO 4628-8:2012, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 8: Assessment of degree of delamination and corrosion around a scribe or other artificial defect (ISO 4628-8:2012)*

EN ISO 17872, *Paints and varnishes — Guidelines for the introduction of scribe marks through coatings on metallic panels for corrosion testing (ISO 17872)*

koniec náhľadu – text ďalej pokračuje v platenej verzii STN