

STN	Plasty Etylén-vinylacetátové (EVAC) kopolyméry termoplastov Stanovenie obsahu vinylacetátu (ISO 8985: 2022)	STN EN ISO 8985 64 3302
------------	--	---

Plastics - Ethylene/vinyl acetate copolymer (EVAC) thermoplastics - Determination of vinyl acetate content (ISO 8985:2022)

Táto norma obsahuje anglickú verziu európskej normy.
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 04/22

Obsahuje: EN ISO 8985:2022, ISO 8985:2022

Oznámením tejto normy sa ruší
STN EN ISO 8985 (64 3302) z novembra 2000

134654

EUROPEAN STANDARD

EN ISO 8985

NORME EUROPÉENNE

EUROPÄISCHE NORM

February 2022

ICS 83.080.20

Supersedes EN ISO 8985:1998

English Version

Plastics - Ethylene/vinyl acetate copolymer (EVAC)
thermoplastics - Determination of vinyl acetate content
(ISO 8985:2022)

Plastiques - Copolymères éthylène/acétate de vinyle
(EVAC) thermoplastiques - Dosage de l'acétate de
vinyle (ISO 8985:2022)

Kunststoffe - Ethylen-Vinylacetat-Copolymer (EVAC)-
Thermoplasten - Bestimmung des Vinylacetatgehalts
(ISO 8985:2022)

This European Standard was approved by CEN on 25 December 2021.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

EN ISO 8985:2022 (E)

Contents	Page
European foreword.....	3

European foreword

This document (EN ISO 8985:2022) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2022, and conflicting national standards shall be withdrawn at the latest by August 2022.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 8985:1998.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 8985:2022 has been approved by CEN as EN ISO 8985:2022 without any modification.

INTERNATIONAL STANDARD

ISO 8985

Third edition
2022-01

Plastics — Ethylene/vinyl acetate copolymer (EVAC) thermoplastics — Determination of vinyl acetate content

*Plastiques — Copolymères éthylène/acétate de vinyle (EVAC)
thermoplastiques — Dosage de l'acétate de vinyle*



Reference number
ISO 8985:2022(E)

© ISO 2022

ISO 8985:2022(E)**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Reference methods	1
4.1 Reference method 1: Hydrolysis and back titration.....	1
4.1.1 Principle.....	1
4.1.2 Reagents.....	2
4.1.3 Apparatus.....	2
4.1.4 Procedure.....	3
4.1.5 Expression of results.....	3
4.1.6 Test report.....	4
4.2 Reference method 2: Saponification and potentiometric titration.....	4
4.2.1 Principle.....	4
4.2.2 Reagents.....	4
4.2.3 Apparatus.....	4
4.2.4 Procedure.....	5
4.2.5 Expression of results.....	6
4.2.6 Test report.....	6
4.3 Reference method 3: Measurement of oxygen.....	6
4.3.1 Principle.....	6
4.3.2 Apparatus.....	6
4.3.3 procedure.....	7
4.3.4 Sampling.....	11
4.3.5 Calibration.....	11
4.3.6 Calculation of vinyl acetate content.....	12
4.3.7 Test report.....	12
5 Examples of test methods	12
5.1 Method using infrared spectrometry.....	12
5.1.1 Principle.....	12
5.1.2 Apparatus and materials.....	12
5.1.3 Procedure.....	13
5.1.4 Expression of results.....	15
5.1.5 Test report.....	16
5.2 Acidimetric method.....	16
5.2.1 Principle.....	16
5.2.2 Reagents and materials.....	16
5.2.3 Apparatus.....	17
5.2.4 Procedure.....	17
5.2.5 Expression of results.....	18
5.2.6 Test report.....	18
5.3 Iodometric method.....	19
5.3.1 Principle.....	19
5.3.2 Reagents.....	19
5.3.3 Apparatus.....	19
5.3.4 Procedure.....	19
5.3.5 Expression of results.....	20
5.3.6 Test report.....	20
5.4 Thermogravimetry method.....	20
5.4.1 Principle.....	20
5.4.2 Apparatus.....	21
5.4.3 Test specimens.....	21
5.4.4 Calibration.....	21

ISO 8985:2022(E)

5.4.5	Procedure	21
5.4.6	Test report	22
Bibliography		23

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 8985:1998), which has been technically revised.

The main changes compared to the previous edition are as follows:

- the normative references have been updated to the latest version;
- the mandatory terms and definitions clause has been added (see [Clause 3](#));
- a “thermogravimetry test method” has been added;
- infrared spectrometer has been modified to be Fourier infrared spectrometer;
- the example of infrared spectrum has been modified from transmission to absorbance;
- the example of calibration curve has been modified.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Plastics — Ethylene/vinyl acetate copolymer (EVAC) thermoplastics — Determination of vinyl acetate content

SAFETY PRECAUTIONS — Persons using this document should be familiar with normal laboratory practice, if applicable. This document does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices.

1 Scope

This document specifies two categories of method for the determination of the vinyl acetate (VAC) content of ethylene/vinyl acetate (EVAC) copolymer, for use in the designation of such copolymers according to ISO 21301-1. One category is referred to as “reference methods”, the other as “test methods”.

The “reference methods” are used to calibrate the method used for the determination of the vinyl acetate content of ethylene/vinyl acetate copolymers.

The “test methods” are other methods which can be used for the determination if they are calibrated using one of the reference methods described in [Clause 4](#), provided they show a certain permissible repeatability.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 472, *Plastics — Vocabulary*

ISO 4799, *Laboratory glassware — Condensers*

ISO 11358-1:2014, *Plastics — Thermogravimetry (TG) of polymers — Part 1: General principles*

koniec náhľadu – text ďalej pokračuje v platenej verzii STN