# Spojovacie súčiastky Systémy elektrolytického pokovovania (ISO 4042: 2022) STN EN ISO 4042 02 1008

Fasteners - Electroplated coating systems (ISO 4042:2022)

Táto norma obsahuje anglickú verziu európskej normy. This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 08/22

Obsahuje: EN ISO 4042:2022, ISO 4042:2022

Oznámením tejto normy sa ruší STN EN ISO 4042 (02 1008) z mája 2019



### EUROPEAN STANDARD NORME EUROPÉENNE

**EN ISO 4042** 

EUROPÄISCHE NORM

June 2022

ICS 21.060.01

Supersedes EN ISO 4042:2018

#### **English Version**

#### Fasteners - Electroplated coating systems (ISO 4042:2022)

Fixations - Systèmes de revêtements électrolytiques (ISO 4042: 2022)

Verbindungselemente - Galvanisch aufgebrachte Überzugsysteme (ISO 4042: 2022)

This European Standard was approved by CEN on 4 February 2022.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

#### EN ISO 4042:2022 (E)

Contents	Page
European foreword	9
EUFOPEAN 10FeWOFU	

EN ISO 4042:2022 (E)

#### **European foreword**

This document (EN ISO 4042:2022) has been prepared by Technical Committee ISO/TC 2 "Fasteners" in collaboration with Technical Committee CEN/TC 185 "Fasteners" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2022, and conflicting national standards shall be withdrawn at the latest by December 2022.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 4042:2018.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

#### **Endorsement notice**

The text of ISO 4042:2022 has been approved by CEN as EN ISO 4042:2022 without any modification.

## INTERNATIONAL STANDARD

ISO 4042

Fourth edition 2022-06

## Fasteners — Electroplated coating systems

Fixations — Systèmes de revêtements électrolytiques





#### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Co	ntent	S	Page
Fore	word		v
Intr	oductio	n	vi
1	Scop	e	1
2	-	native references	
3		ns and definitions	
	_		
4	4.1	eral characteristics of the coating	
	4.2	Build-up of basic electroplated coating systems	
	4.3	Coating systems and coating processes	
	4.4	Internal hydrogen embrittlement	
		4.4.1 General	
		4.4.2 Fasteners with hardness up to 360 HV	
		4.4.3 Fasteners with hardness above 360 HV and up to 390 HV	5
		4.4.4 Fasteners with hardness above 390 HV	5
		4.4.5 Fasteners in accordance with ISO 898-1, ISO 898-2 and ISO 898-3	
		4.4.6 Case-hardened fasteners and fasteners with threads rolled after heat	
		treatment	
		4.4.8 Fasteners with bainitic structure	
	4.5	Baking	
_		osion protection and testing	
5	5.1	General	<b>9</b>
	5.2	Neutral salt spray test (NSS) for zinc-based coating systems	
	5.3	Sulfur dioxide test (Kesternich test)	11
	5.4	Bulk handling, automatic processes such as feeding and/or sorting, storage and transport	
6	Dime	ensional requirements and testing	12
	6.1	General	
	6.2	Fasteners with ISO metric thread	
		6.2.1 Coating thickness	
		6.2.2 Gaugeability and assemblability	
	6.3	Other fastenersTest methods for thickness determination	
	6.4		
7		nanical and physical properties and testing	
	7.1 7.2	General Appearance	
	7.2 7.3	Corrosion resistance related to temperature	
	7.4	Torque/clamp force relationship	
	7.5	Determination of hexavalent chromium	
8	Appl	icability of tests	17
	8.1	General	
	8.2	Tests mandatory for each lot	
	8.3	Tests for in-process control	
	8.4	Tests to be performed when specified by the purchaser	
9		gnation system	
	9.1	General Control of all attractions of all attractions are strong from the control of all attractions of all attractions are strong from the control of a strong from the	
	9.2 9.3	Designation of electroplated coating systems for the order	18
	7.3	Examples of designation of hexavalent chromium free electroplated coating systems for fasteners	20
	9.4	Designation of fasteners with electroplated coating systems for labelling	

10	Ordering requirements for electroplating	21
11	Storage conditions	22
Annex	x A (informative) Design and assembly aspects for joints with coated fasteners	23
Annex	<b>B</b> (informative) <b>Hydrogen embrittlement consideration</b>	31
Annex	C (informative) Corrosion protection related to zinc coatings with chromate conversion coatings	36
Annex	x D (informative) Coating thickness and thread clearance for ISO metric threads	37
Annex	E (informative) Coating systems tested in accordance with ISO 9227, NSS — Evaluation of cabinet corrosivity for the neutral salt spray test	44
Annex	F (informative) Obsolete designation codes for electroplated coating systems on fasteners according to ISO 4042:1999	54
Biblio	graphy	57

#### **Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see <a href="www.iso.org/directives">www.iso.org/directives</a>).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see <a href="https://www.iso.org/patents">www.iso.org/patents</a>).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see <a href="https://www.iso.org/iso/foreword.html">www.iso.org/iso/foreword.html</a>.

This document was prepared by Technical Committee ISO/TC 2, *Fasteners*, Subcommittee SC 14, *Surface coatings*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 185, *Fasteners*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fourth edition cancels and replaces the third edition (ISO 4042:2018), which has been technically revised. The main changes are as follows:

- in <u>Clause 1</u>, a statement has been added that the requirements of this document for electroplated fasteners have precedence over other documents dealing with electroplating;
- all references to ISO 2081 and ISO 19598 have been removed because ISO 4042 is a self-containing document for the purpose of fasteners;
- in 4.4, the measures to prevent internal hydrogen embrittlement for nuts, flat washers and case-hardened screws have been completely revised;
- in 6.4, the reference areas for thickness determination have been more clearly specified;
- wording in the whole document has been improved to be more accurate, especially for complex topics.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at <a href="https://www.iso.org/members.html">www.iso.org/members.html</a>.

#### Introduction

ISO 4042:1999 was completely revised to take into account new developments related to hexavalent chromium free passivations, application of sealants and top coats, requirements for functional properties as well as results of research work to minimize the risk of hydrogen embrittlement. This revision was published in 2018.

The last editions of ISO 2081:2018 as well as ISO 19598:2016, which are general standards for electroplating, are not adequate to cover the requirements for electroplated fasteners dealt with in ISO 4042, especially with regard to hydrogen embrittlement and baking. Therefore, a new revision of ISO 4042:2018 was necessary to delete all references to these two general standards to avoid any contradictions.

For electroplated nuts, flat washers, and case-hardened screws, measures to mitigate the risk of hydrogen embrittlement, especially in relation to baking, have been revised to be consistent with revisions of ISO 898-2 and ISO 2702, and to reflect findings from the latest research works. For electroplated flat washers in accordance with ISO 898-3, it is generally accepted that tensile stress resulting from intended and unintended bending in service may increase the risk of hydrogen embrittlement. An appropriate test method to simulate such a scenario is currently under investigation.

#### Fasteners — Electroplated coating systems

#### 1 Scope

This document specifies requirements for steel fasteners with electroplated coatings and coating systems. The requirements related to dimensional properties also apply to fasteners made of copper or copper alloys.

It also specifies requirements and gives recommendations to minimize the risk of hydrogen embrittlement, see  $\frac{4.4}{2}$  and  $\frac{1}{2}$  and  $\frac$ 

It mainly applies to fasteners with zinc and zinc alloy coating systems (zinc, zinc-nickel, zinc-iron) and cadmium, primarily intended for corrosion protection and other functional properties:

- with or without conversion coating,
- with or without sealant,
- with or without top coat,
- with or without lubricant (integral lubricant and/or subsequently added lubricant).

Specifications for other electroplated coatings and coating systems (tin, tin-zinc, copper-tin, copper-silver, copper, silver, copper-zinc, nickel, nickel-chromium, copper-nickel, copper-nickel-chromium) are included in this document only for dimensional requirements related to fasteners with ISO metric threads.

The requirements of this document for electroplated fasteners take precedence over other documents dealing with electroplating.

This document applies to steel bolts, screws, studs and nuts with ISO metric thread, to other threaded fasteners and to non-threaded fasteners such as washers, pins, clips and rivets.

NOTE Electroplating is also applied to stainless steel fasteners, e.g. for the purpose of lubrication in order to avoid galling.

Information for design and assembly of coated fasteners is given in Annex A.

This document does not specify requirements for properties such as weldability or paintability.

#### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1456, Metallic and other inorganic coatings — Electrodeposited coatings of nickel, nickel plus chromium, copper plus nickel and of copper plus nickel plus chromium

ISO 1463, Metallic and oxide coatings — Measurement of coating thickness — Microscopical method

ISO 1502, ISO general-purpose metric screw threads — Gauges and gauging

ISO 1891-2, Fasteners — Terminology — Part 2: Vocabulary and definitions for coatings

ISO 2082, Metallic and other inorganic coatings — Electroplated coatings of cadmium with supplementary treatments on iron or steel

ISO 2093, Electroplated coatings of tin — Specification and test methods

ISO 2177, Metallic coatings — Measurement of coating thickness — Coulometric method by anodic dissolution

 ${\tt ISO~2178, Non-magnetic~coatings~on~magnetic~substrates -- \textit{Measurement of coating thickness} -- \textit{Magnetic~method}}$ 

ISO 3497, Metallic coatings — Measurement of coating thickness — X-ray spectrometric methods

ISO 3613, Metallic and other inorganic coatings — Chromate conversion coatings on zinc, cadmium, aluminium-zinc alloys and zinc-aluminium alloys — Test methods

ISO 4521, Metallic and other inorganic coatings — Electrodeposited silver and silver alloy coatings for engineering purposes — Specification and test methods

ISO 8991, Designation system for fasteners

ISO 9227, Corrosion tests in artificial atmospheres — Salt spray tests

ISO 15330, Fasteners — Preloading test for the detection of hydrogen embrittlement — Parallel bearing surface method

ISO 15726, Metallic and other inorganic coatings — Electrodeposited zinc alloys with nickel, cobalt or iron

ISO 16047, Fasteners — Torque/clamp force testing

ISO 16228, Fasteners — Types of inspection documents

ISO 21968, Non-magnetic metallic coatings on metallic and non-metallic basis materials — Measurement of coating thickness — Phase-sensitive eddy-current method

ASME B18.6.3, Machine Screws, Tapping Screws, and Metallic Drive Screws (Inch Series)

#### koniec náhľadu – text ďalej pokračuje v platenej verzii STN