STN

#### Tavivá na mäkké spájkovanie Skúšobné metódy Časť 6: Stanovenie obsahu a zisťovanie prítomnosti halogenidov (s výnimkou fluoridov) (ISO 9455-6: 2022)

STN EN ISO 9455-6

05 5707

Soft soldering fluxes - Test methods - Part 6: Determination and detection of halide (excluding fluoride) content (ISO 9455-6:2022)

Táto norma obsahuje anglickú verziu európskej normy. This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 03/23

Obsahuje: EN ISO 9455-6:2022, ISO 9455-6:2022

Oznámením tejto normy sa ruší STN EN ISO 9455-6 (05 5707) z augusta 2001

### EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

EN ISO 9455-6

December 2022

ICS 25.160.50

Supersedes EN ISO 9455-6:1997

#### **English Version**

### Soft soldering fluxes - Test methods - Part 6: Determination and detection of halide (excluding fluoride) content (ISO 9455-6:2022)

Flux de brasage tendre - Méthodes d'essai - Partie 6: Dosage et détection des halogénures (à l'exception des fluorures) (ISO 9455-6:2022) Flussmittel zum Weichlöten - Prüfverfahren - Teil 6: Bestimmung und Nachweis des Halogenidgehaltes (außer Fluorid) (ISO 9455-6:2022)

This European Standard was approved by CEN on 29 November 2022.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

#### EN ISO 9455-6:2022 (E)

Contents	Page
European foreword	2
EUFOPEAN 10FEWOFU	

EN ISO 9455-6:2022 (E)

#### **European foreword**

This document (EN ISO 9455-6:2022) has been prepared by Technical Committee ISO/TC 44 "Welding and allied processes" in collaboration with Technical Committee CEN/TC 121 "Welding and allied processes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2023, and conflicting national standards shall be withdrawn at the latest by June 2023.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 9455-6:1997.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

#### **Endorsement notice**

The text of ISO 9455-6:2022 has been approved by CEN as EN ISO 9455-6:2022 without any modification.

# INTERNATIONAL STANDARD

ISO 9455-6

Second edition 2022-12

## Soft soldering fluxes — Test methods —

Part 6:

## Determination and detection of halide (excluding fluoride) content

Flux de brasage tendre — Méthodes d'essai —

Partie 6: Dosage et détection des halogénures (à l'exception des fluorures)



Reference number ISO 9455-6:2022(E)

ISO 9455-6:2022(E)



#### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

#### ISO 9455-6:2022(E)

Co	ntent	ts	Page
Fore	eword		iv
1	Scop	pe	1
2	Nori	mative references	1
3	Terms and definitions		
4	Method A: Potentiometric method (Reference method)		
	4.1	Principle	
	4.2	Reagents	
	4.3	Apparatus	
	4.4	Procedure	
_	4.5	Calculation of results	
5		hod B: Titration method for halide (excluding fluoride) content of water-soluble es	
	5.1	Principle Principle	
	5.2	Reagents	
	5.3	Apparatus	
	5.4	Procedure	
	5.5	Standardization of the ammonium thiocyanate solution $(5.2.2)$	
	5.6	Calculation of results	
6		hod C: Titration method for the determination of halide (excluding fluoride)	
		tent of water-soluble fluxes containing phosphates	
	6.1	Principle	
	6.2 6.3	ReagentsApparatus	
	6.4	Procedure	
	6.5	Standardization of the ammonium thiocyanate solution (6.2.2)	
	6.6	Calculation of results	7
7	Met	hod D: Qualitative test for the presence of ionic halides in flux	7
	7.1	Principle	7
	7.2	Reagents	
	7.3	Apparatus	
	7.4	Procedure	
		7.4.1 Preparation of flux test solution	
•	-	•	
8	<b>Prec</b> 8.1	cision	
	8.2	General Method A	
	8.3	Method B	
	8.4	Method C	
9	Test	t report	10
Ann	ex A (n	ormative) Method for standardizing the silver nitrate solution	12
		hy	

#### ISO 9455-6:2022(E)

#### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see <a href="www.iso.org/directives">www.iso.org/directives</a>).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see <a href="https://www.iso.org/patents">www.iso.org/patents</a>).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see <a href="https://www.iso.org/iso/foreword.html">www.iso.org/iso/foreword.html</a>.

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 12, *Soldering materials*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 121, *Welding and allied processes*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 9455-6:1995), of which it constitutes a minor revision. The changes are as follows:

- <u>Clause 2</u> has been updated;
- new <u>Clause 3</u>, Terms and definitions, has been inserted;
- the coding of the fluxes has been updated in accordance with ISO 9454-1:2016;
- 4.2, 5.2, 6.2 and A.3 restructured;
- notes changed to body text in 4.4, 5.4, 5.6, 6.4 and 7.4.1.4;
- title added to <u>Table 1</u>;
- formulae numbered;
- minor editorial changes.

A list of all parts in the ISO 9455 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at <a href="https://www.iso.org/members.html">www.iso.org/members.html</a>. Official interpretations of ISO/TC 44 documents, where they exist, are available from this page: <a href="https://committee.iso.org/sites/tc44/home/interpretation.html">https://committee.iso.org/sites/tc44/home/interpretation.html</a>.

### Soft soldering fluxes — Test methods —

#### Part 6:

## Determination and detection of halide (excluding fluoride) content

#### 1 Scope

This document specifies three quantitative methods for the determination of the ionic halide (excluding fluoride) content of soldering fluxes. Halides are calculated as chlorides. A useful qualitative test method for the detection of ionic halides is also described.

Method A is a potentiometric titration method for the determination of halide (excluding fluoride) content and is applicable to flux classes 1 and 2, defined in ISO 9454-1. This method, which is considered the reference method for these fluxes, is suitable for halide contents generally within the range of 0,05 % mass fraction to 2 % mass fraction in the non-volatile matter of the flux.

Method B is a titration method for the determination of the total halide (excluding fluoride) content of water-soluble fluxes. It is applicable to flux classes 2122 to 2124, 3112 to 3114 and 3212 to 3214, as defined in ISO 9454-1.

Method C is a titration method for the determination of the halide (excluding fluoride) content of water-soluble fluxes containing phosphates and is applicable to flux class 331, as defined in ISO 9454-1.

Method D is a qualitative test, using silver chromate test paper, for the presence of ionic halides. The technique can be used for all classes of flux.

#### 2 Normative references

There are no normative references in this document.

koniec náhľadu – text ďalej pokračuje v platenej verzii STN