

|            |   |  |
|------------|---|--|
| <b>STN</b> | <b>Jemná keramika (špeciálna keramika, špeciálna<br/>technická keramika)<br/>Weibullova štatistika pre údaje o sile<br/>(ISO 20501: 2019)</b> | <b>STN<br/>EN ISO 20501</b><br><br>72 7598 |
|------------|---|--|

Fine ceramics (advanced ceramics, advanced technical ceramics) - Weibull statistics for strength data (ISO 20501:2019)

Táto norma obsahuje anglickú verziu európskej normy.  
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 03/23

Obsahuje: EN ISO 20501:2022, ISO 20501:2019

Oznámením tejto normy sa ruší  
STN EN 843-5 (72 7513) z mája 2007

**136522**

EUROPEAN STANDARD

**EN ISO 20501**

NORME EUROPÉENNE

EUROPÄISCHE NORM

December 2022

ICS 81.060.30

Supersedes EN 843-5:2006

English Version

**Fine ceramics (advanced ceramics, advanced technical ceramics) - Weibull statistics for strength data (ISO 20501:2019)**

Céramiques techniques - Analyse statistique de Weibull des données de résistance à la rupture (ISO 20501:2019)

Hochleistungskeramik - Weibullstatistik von Festigkeitswerten (ISO 20501:2019)

This European Standard was approved by CEN on 20 December 2022.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

**EN ISO 20501:2022 (E)**

| <b>Contents</b>               | <b>Page</b> |
|-------------------------------|-------------|
| <b>European foreword.....</b> | <b>3</b>    |

## **European foreword**

The text of ISO 20501:2019 has been prepared by Technical Committee ISO/TC 206 "Fine ceramics" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 20501:2022 by Technical Committee CEN/TC 184 "Advanced technical ceramics" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2023, and conflicting national standards shall be withdrawn at the latest by June 2023.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 843-5:2006.

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

## **Endorsement notice**

The text of ISO 20501:2019 has been approved by CEN as EN ISO 20501:2022 without any modification.

# INTERNATIONAL STANDARD

# ISO 20501

Second edition  
2019-03

---

---

## **Fine ceramics (advanced ceramics, advanced technical ceramics) — Weibull statistics for strength data**

*Céramiques techniques — Analyse statistique de Weibull des données  
de résistance à la rupture*



Reference number  
ISO 20501:2019(E)

© ISO 2019

**ISO 20501:2019(E)****COPYRIGHT PROTECTED DOCUMENT**

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

|   |           |
|---|-----------|
| <b>Foreword</b> .....   | <b>iv</b> |
| <b>Introduction</b> .....   | <b>v</b>  |
| <b>1 Scope</b> .....  | <b>1</b>  |
| <b>2 Normative references</b> .....   | <b>1</b>  |
| <b>3 Terms and definitions</b> .....  | <b>1</b>  |
| 3.1 Defect populations.....   | 1         |
| 3.2 Mechanical testing.....   | 3         |
| 3.3 Statistical terms.....  | 3         |
| 3.4 Weibull distributions.....  | 4         |
| <b>4 Symbols</b> .....  | <b>5</b>  |
| <b>5 Significance and use</b> .....   | <b>6</b>  |
| <b>6 Method A: maximum likelihood parameter estimators for single flaw populations</b> .....        | <b>7</b>  |
| 6.1 General.....  | 7         |
| 6.2 Censored data.....  | 8         |
| 6.3 Likelihood functions.....   | 8         |
| 6.4 Bias correction.....  | 8         |
| 6.5 Confidence intervals.....   | 10        |
| <b>7 Method B: maximum likelihood parameter estimators for competing flaw populations</b> .....     | <b>13</b> |
| 7.1 General.....  | 13        |
| 7.2 Censored data.....  | 14        |
| 7.3 Likelihood functions.....   | 14        |
| <b>8 Procedure</b> .....  | <b>15</b> |
| 8.1 Outlying observations.....  | 15        |
| 8.2 Fractography.....   | 15        |
| 8.3 Graphical representation.....   | 16        |
| <b>9 Test report</b> .....  | <b>18</b> |
| <b>Annex A (informative) Converting to material-specific strength distribution parameters</b> ..... | <b>19</b> |
| <b>Annex B (informative) Illustrative examples</b> .....  | <b>21</b> |
| <b>Annex C (informative) Test specimens with unidentified fracture origin</b> .....                 | <b>28</b> |
| <b>Annex D (informative) Fortran program</b> .....  | <b>31</b> |
| <b>Bibliography</b> .....   | <b>36</b> |

## ISO 20501:2019(E)

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 206, *Fine ceramics*.

This second edition cancels and replaces the first edition (ISO 20501:2003), which has been technically revised. It also incorporates the Technical Corrigendum ISO 20501:2003/Cor.1:2009.

The main changes compared to the previous edition are as follows:

- the terms and definitions in [Clause 3](#) have been updated and modified;
- a method to treat a higher number of specimens ( $N > 120$ ) has been introduced for method A: maximum likelihood parameter estimators for single flaw populations;
- in [Annex D](#), example codes have been added for calculating the maximum likelihood parameters of the Weibull distribution with modern analysis software.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).



## **Introduction**

Measurements of the strength at failure are taken for one of two reasons: either for a comparison of the relative quality of two materials regarding fracture strength, or the prediction of the probability of failure for a structure of interest. This document permits estimates of the distribution parameters which are needed for either. In addition, this document encourages the integration of mechanical property data and fractographic analysis.



# Fine ceramics (advanced ceramics, advanced technical ceramics) — Weibull statistics for strength data

## 1 Scope

This document covers the reporting of uniaxial strength data and the estimation of probability distribution parameters for advanced ceramics which fail in a brittle fashion. The failure strength of advanced ceramics is treated as a continuous random variable. Typically, a number of test specimens with well-defined geometry are brought to failure under well-defined isothermal loading conditions. The load at which each specimen fails is recorded. The resulting failure stresses are used to obtain parameter estimates associated with the underlying population distribution.

This document is restricted to the assumption that the distribution underlying the failure strengths is the two-parameter Weibull distribution with size scaling. Furthermore, this document is restricted to test specimens (tensile, flexural, pressurized ring, etc.) that are primarily subjected to uniaxial stress states. [Subclauses 6.4](#) and [6.5](#) outline methods of correcting for bias errors in the estimated Weibull parameters, and to calculate confidence bounds on those estimates from data sets where all failures originate from a single flaw population (i.e. a single failure mode). In samples where failures originate from multiple independent flaw populations (e.g. competing failure modes), the methods outlined in [6.4](#) and [6.5](#) for bias correction and confidence bounds are not applicable.

## 2 Normative references

There are no normative references in this document.

**koniec náhľadu – text ďalej pokračuje v platenej verzii STN**