# STN

# Kovové materiály Skúška rázom v ohybe Charpyho metódou (V-vrub) Prístrojová skúšobná metóda (ISO 14556: 2023)

**STN EN ISO 14556** 

42 0378

Metallic materials - Charpy V-notch pendulum impact test - Instrumented test method (ISO 14556:2023)

Táto norma obsahuje anglickú verziu európskej normy. This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 07/23

Obsahuje: EN ISO 14556:2023, ISO 14556:2023

Oznámením tejto normy sa ruší STN EN ISO 14556 (42 0378) z apríla 2016

# EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

**EN ISO 14556** 

May 2023

ICS 77.040.10

Supersedes EN ISO 14556:2015

## **English Version**

# Metallic materials - Charpy V-notch pendulum impact test - Instrumented test method (ISO 14556:2023)

Matériaux métalliques - Essai de flexion par choc sur éprouvette Charpy à entaille en V - Méthode d'essai instrumenté (ISO 14556:2023) Metallische Werkstoffe - Kerbschlagbiegeversuch nach Charpy (V-Kerb) - Instrumentiertes Prüfverfahren (ISO 14556:2023)

This European Standard was approved by CEN on 16 April 2023.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

# EN ISO 14556:2023 (E)

Contents	Page
European foreword	3

EN ISO 14556:2023 (E)

# **European foreword**

This document (EN ISO 14556:2023) has been prepared by Technical Committee ISO/TC 164 "Mechanical testing of metals" in collaboration with Technical Committee CEN/TC 459/SC 1 "Test methods for steel (other than chemical analysis)" the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2023, and conflicting national standards shall be withdrawn at the latest by November 2023.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 14556:2015.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

## **Endorsement notice**

The text of ISO 14556:2023 has been approved by CEN as EN ISO 14556:2023 without any modification.

# INTERNATIONAL STANDARD

ISO 14556

Third edition 2023-05

# Metallic materials — Charpy V-notch pendulum impact test — Instrumented test method

Matériaux métalliques — Essai de flexion par choc sur éprouvette Charpy à entaille en V — Méthode d'essai instrumenté





# **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Foreword	Con	tents	Page
2       Normative references       1         3       Terms and definitions       1         3.1       Characteristic values of force (see Figure 2)       2         3.2       Characteristic values of impact energy       2         4       Symbols and abbreviated terms       3         5       Principle       3         6       Apparatus       4         6.1       Testing machine       4         6.2       Instrumentation and calibration       4         6.2.1       Traceable measurement       4         6.2.2       Force measurement       4         6.2.3       Calibration       5         6.2.4       Displacement measurement       5         6.2.5       Recording apparatus       6         6.2.5       Recording apparatus       6         6.2.6       Calibration interval       6         7       Test piece       6         8       Test procedure       6         9       Expression of results       6         9.1       General       6         9.2       Evaluation of the force-displacement curve       7         9.3       Determination of the characteristic values of displacement	Fore	ord	iv
3 Terms and definitions 3.1 Characteristic values of force (see Figure 2) 3.2 Characteristic values of displacement (see Figure 2) 3.3 Characteristic values of impact energy  4 Symbols and abbreviated terms  5 Principle 6 Apparatus 6.1 Testing machine 6.2 Instrumentation and calibration 6.2.1 Traceable measurement 6.2.2 Force measurement 6.2.3 Calibration 6.2.4 Displacement measurement 6.2.5 Recording apparatus 6.2.6 Calibration interval 6.2.6 Calibration interval 6.2.6 Calibration interval 6.2.7 Test piece 6 Test procedure 9 Expression of results 9.1 General 9.2 Evaluation of the characteristic values of force 9.4 Determination of the characteristic values of displacement 7 Determination of the characteristic values of impact energy 9.5 Determination of the characteristic values of impact energy 9.7 Test report 9.8 Annex A (informative) Examples of instrumented strikers 11 Annex B (informative) Examples of support block for the calibration of ductile fracture surface 12 Annex C (informative) Instrumented Charpy V-notch pendulum impact testing of miniature test pieces 14	1	Scope	1
3 Terms and definitions 3.1 Characteristic values of force (see Figure 2) 3.2 Characteristic values of displacement (see Figure 2) 3.3 Characteristic values of impact energy  4 Symbols and abbreviated terms  5 Principle 6 Apparatus 6.1 Testing machine 6.2 Instrumentation and calibration 6.2.1 Traceable measurement 6.2.2 Force measurement 6.2.3 Calibration 6.2.4 Displacement measurement 6.2.5 Recording apparatus 6.2.6 Calibration interval 6.2.6 Calibration interval 6.2.6 Calibration interval 6.2.7 Test piece 6 Test procedure 9 Expression of results 9.1 General 9.2 Evaluation of the characteristic values of force 9.4 Determination of the characteristic values of displacement 7 Determination of the characteristic values of impact energy 9.5 Determination of the characteristic values of impact energy 9.7 Test report 9.8 Annex A (informative) Examples of instrumented strikers 11 Annex B (informative) Examples of support block for the calibration of ductile fracture surface 12 Annex C (informative) Instrumented Charpy V-notch pendulum impact testing of miniature test pieces 14	2	Normative references	1
5 Principle 3 6 Apparatus 4 6.1 Testing machine 4 6.2 Instrumentation and calibration 4 6.2.1 Traceable measurement 4 6.2.2 Force measurement 5 6.2.4 Displacement measurement 5 6.2.5 Recording apparatus 6 6.2.6 Calibration 5 6.2.6 Calibration 6 7 Test piece 6 8 Test procedure 6 9 Expression of results 6 9.1 General 6 9.2 Evaluation of the force-displacement curve 7 9.3 Determination of the characteristic values of force 7 9.4 Determination of the characteristic values of impact energy 9 10 Test report 9 Annex A (informative) Examples of instrumented strikers 11 Annex B (informative) Example of support block for the calibration of a 2 mm striker 12 Annex C (informative) Formulae for the estimation of the proportion of ductile fracture surface 13 Annex D (normative) Instrumented Charpy V-notch pendulum impact testing of miniature test pieces 14	3	<ul> <li>3.1 Characteristic values of force (see Figure 2)</li> <li>3.2 Characteristic values of displacement (see Figure 2)</li> </ul>	
6 Apparatus	4	Symbols and abbreviated terms	3
6.1 Testing machine 6.2 Instrumentation and calibration 4.6.2.1 Traceable measurement 4.6.2.2 Force measurement 4.6.2.3 Calibration 5.6.2.4 Displacement measurement 6.2.5 Recording apparatus 6.2.6 Calibration interval 6.2.6 Calibration interval 6.2.7 Test piece 6.2.8 Test procedure 6.2.9 Expression of results 6.2.1 General 6.22 Evaluation of the force-displacement curve 7.2 Evaluation of the characteristic values of force 9.1 General 9.2 Evaluation of the characteristic values of force 7.9 Supermination of the characteristic values of displacement 7.9 Supermination of the characteristic values of impact energy 9.1 Test report 9.1 Test report 9.2 Nanex A (informative) Examples of instrumented strikers 11 Annex B (informative) Example of support block for the calibration of a 2 mm striker 12 Annex C (informative) Formulae for the estimation of the proportion of ductile fracture surface 13 Annex D (normative) Instrumented Charpy V-notch pendulum impact testing of miniature test pieces 14	5	Principle	3
8 Test procedure 6 9 Expression of results 6 9.1 General 6 9.2 Evaluation of the force-displacement curve 7 9.3 Determination of the characteristic values of force 7 9.4 Determination of the characteristic values of displacement 7 9.5 Determination of the characteristic values of impact energy 9  10 Test report 9  Annex A (informative) Examples of instrumented strikers 11  Annex B (informative) Formulae for the estimation of the proportion of ductile fracture surface 13  Annex D (normative) Instrumented Charpy V-notch pendulum impact testing of miniature test pieces 14	6	6.1 Testing machine 6.2 Instrumentation and calibration 6.2.1 Traceable measurement 6.2.2 Force measurement 6.2.3 Calibration 6.2.4 Displacement measurement 6.2.5 Recording apparatus	
9 Expression of results 6 9.1 General 6 9.2 Evaluation of the force-displacement curve 7 9.3 Determination of the characteristic values of force 7 9.4 Determination of the characteristic values of displacement 7 9.5 Determination of the characteristic values of impact energy 9  10 Test report 9  Annex A (informative) Examples of instrumented strikers 11  Annex B (informative) Example of support block for the calibration of a 2 mm striker 12  Annex C (informative) Formulae for the estimation of the proportion of ductile fracture surface 13  Annex D (normative) Instrumented Charpy V-notch pendulum impact testing of miniature test pieces 14	7	Test piece	6
9.1 General 6 9.2 Evaluation of the force-displacement curve 7 9.3 Determination of the characteristic values of force 7 9.4 Determination of the characteristic values of displacement 7 9.5 Determination of the characteristic values of impact energy 9  10 Test report 9  Annex A (informative) Examples of instrumented strikers 11  Annex B (informative) Example of support block for the calibration of a 2 mm striker 12  Annex C (informative) Formulae for the estimation of the proportion of ductile fracture surface 13  Annex D (normative) Instrumented Charpy V-notch pendulum impact testing of miniature test pieces 14	8	Test procedure	6
Annex A (informative) Examples of instrumented strikers	9	9.1 General	6 7 7
Annex B (informative) Example of support block for the calibration of a 2 mm striker 12  Annex C (informative) Formulae for the estimation of the proportion of ductile fracture surface 13  Annex D (normative) Instrumented Charpy V-notch pendulum impact testing of miniature test pieces 14	10	Test report	9
Annex C (informative) Formulae for the estimation of the proportion of ductile fracture surface	Anne	A (informative) Examples of instrumented strikers	11
Surface	Anne	B (informative) Example of support block for the calibration of a 2 mm stri	ker12
test pieces14		surface	13
		test pieces	14

### **Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see <a href="www.iso.org/directives">www.iso.org/directives</a>).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see <a href="https://www.iso.org/patents">www.iso.org/patents</a>).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see <a href="https://www.iso.org/iso/foreword.html">www.iso.org/iso/foreword.html</a>.

This document was prepared by Technical Committee ISO/TC 164, *Mechanical testing of metals*, Subcommittee SC 4, *Fatigue, fracture and toughness testing,* in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 459/SC 1, *Test methods for steel (other than chemical analysis)*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 14556:2015), which has been technically revised.

The main changes are as follows:

- in <u>Clause 1</u>, a sentence was added to state that results shall not be directly used in design calculations;
- in <u>Clause 4</u>, the symbol  $K_p$  (potential energy of the pendulum hammer) was added; the symbol KV (absorbed energy) was changed to  $K_V$ ;
- in 6.1 and D.2.1, the application of the "dynamic force adjustment" was added;
- in <u>6.2.3</u>, a generic statement about the stiffness of the support block was removed;
- in <u>6.2.5</u>, the possibility of directly determining characteristic values from printed graphs was removed;
- in <u>Clauses 7</u> and 8, statements referring to <u>Annex D</u> when testing miniature test pieces were added;
- in <u>9.2</u>, the characteristic values of force that can be evaluated from curves of Type A and B were changed;
- in 9.3, it is now specified that  $F_{\rm m}$  is determined after general yield;
- in <u>Figure 2</u>, force-displacement curves in columns 3 (actual recording) were replaced with betterquality ones;

- in <u>Clause 10</u>, a requirement to report the type of test piece (standard, subsize, or miniature) was added;
- in <u>Annex A</u>, it was clarified that those shown are examples of instrumented strikers;
- in Annex D, alternative miniature test pieces were removed;
- in <u>D.2.1</u>, the deviation range between  $W_t$  and  $K_V$  was changed from  $\pm 0.5$  J to  $\pm 10$  % of  $K_V$ ;
- in <u>D.3.1</u>, dimensions for the standard miniature test piece were added; test temperature requirements were removed; the test report section was removed;
- in the Bibliography, a new reference, [8], was added.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at <a href="https://www.iso.org/members.html">www.iso.org/members.html</a>.

# Metallic materials — Charpy V-notch pendulum impact test — Instrumented test method

## 1 Scope

This document specifies a method of instrumented Charpy V-notch pendulum impact testing on metallic materials and the requirements concerning the measurement and recording equipment.

With respect to the Charpy pendulum impact test described in ISO 148-1, this test provides further information on the fracture behaviour of the product under impact testing conditions.

The results of instrumented Charpy test analyses are not directly transferable to structures or components and shall not be directly used in design calculations or safety assessments.

NOTE General information about instrumented impact testing can be found in References [1] to [5].

#### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 148-1, Metallic materials — Charpy pendulum impact test — Part 1: Test method

ISO 148-2, Metallic materials — Charpy pendulum impact test — Part 2: Verification of testing machines

koniec náhľadu – text ďalej pokračuje v platenej verzii STN