

<b>STN</b>	<b>Zvariteľné konštrukčné ocele na pevné pobrežné konštrukcie Technické dodacie podmienky Časť 3: Duté profily dokončené za tepla</b>	<b>STN EN 10225-3+A1</b>
		42 0929

Weldable structural steels for fixed offshore structures - Technical delivery conditions - Part 3: Hot finished hollow sections

Táto norma obsahuje anglickú verziu európskej normy.  
This standard includes the English version of the European Standard.

Táto norma bola označená vo Vestníku ÚNMS SR č. 07/23

Obsahuje: EN 10225-3:2019+A1:2023

Oznámením tejto normy sa ruší  
STN EN 10225-3 (42 0929) z novembra 2019

**137220**

**EUROPEAN STANDARD**  
**NORME EUROPÉENNE**  
**EUROPÄISCHE NORM**

**EN 10225-3:2019+A1**

May 2023

ICS 77.140.10

Supersedes EN 10225-3:2019

English Version

**Weldable structural steels for fixed offshore structures -  
 Technical delivery conditions - Part 3: Hot finished hollow  
 sections**

Aciérs de construction soudables destinés à la  
 fabrication de structures marines fixes - Conditions  
 techniques de livraison - Partie 3 : Profils creux finis à  
 chaud

Schweißgeeignete Baustähle für feststehende Offshore-  
 Konstruktionen - Technische Lieferbedingung - Teil 3:  
 Warmgefertigte Hohlprofile

This European Standard was approved by CEN on 23 December 2018 and includes Amendment approved by CEN on 17 April 2023.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
 COMITÉ EUROPÉEN DE NORMALISATION  
 EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

**EN 10225-3:2019+A1:2023 (E)**

Contents	Page
<b>European foreword .....</b>	<b>5</b>
<b>1 Scope.....</b>	<b>7</b>
<b>2 Normative references.....</b>	<b>7</b>
<b>3 Terms and definitions .....</b>	<b>9</b>
<b>4 Classification and designation .....</b>	<b>11</b>
<b>4.1 Classification.....</b>	<b>11</b>
<b>4.2 Designation .....</b>	<b>11</b>
<b>5 Information to be supplied by the purchaser.....</b>	<b>12</b>
<b>5.1 Mandatory information .....</b>	<b>12</b>
<b>5.2 Options.....</b>	<b>12</b>
<b>5.3 Example of an order.....</b>	<b>12</b>
<b>6 Manufacturing process .....</b>	<b>13</b>
<b>6.1 Steel manufacturing process .....</b>	<b>13</b>
<b>6.2 Structural hollow section manufacturing process.....</b>	<b>13</b>
<b>6.3 Qualification of personnel for NDT activities .....</b>	<b>13</b>
<b>6.4 Delivery condition .....</b>	<b>13</b>
<b>7 Requirements.....</b>	<b>13</b>
<b>7.1 General.....</b>	<b>13</b>
<b>7.2 Chemical composition .....</b>	<b>14</b>
<b>7.2.1 Heat analysis.....</b>	<b>14</b>
<b>7.2.2 Product analysis .....</b>	<b>14</b>
<b>7.2.3 Carbon equivalent values (CEV) and <math>P_{cm}</math> .....</b>	<b>14</b>
<b>7.3 Mechanical properties .....</b>	<b>14</b>
<b>7.3.1 General.....</b>	<b>14</b>
<b>7.3.2 Post weld heat treatment (PWHT) .....</b>	<b>14</b>
<b>7.3.3 Through thickness testing .....</b>	<b>15</b>
<b>7.3.4 Flattening test .....</b>	<b>15</b>
<b>7.3.5 Prequalification for arctic areas.....</b>	<b>15</b>
<b>7.4 Weldability data .....</b>	<b>15</b>
<b>7.5 Internal soundness and non-destructive testing .....</b>	<b>15</b>
<b>7.5.1 Non-destructive testing of the weld seam of HFW hollow sections .....</b>	<b>15</b>
<b>7.5.2 Non-destructive testing of seamless hollow sections for longitudinal imperfections.....</b>	<b>15</b>
<b>7.5.3 Laminar discontinuities of hollow sections .....</b>	<b>16</b>
<b>7.6 Surface quality .....</b>	<b>16</b>
<b>7.7 Dimensions, tolerances, mass .....</b>	<b>16</b>
<b>7.7.1 Dimensions and tolerances on dimensions and shape .....</b>	<b>16</b>
<b>7.7.2 Mass of steel.....</b>	<b>16</b>
<b>8 Inspection .....</b>	<b>17</b>
<b>8.1 General.....</b>	<b>17</b>
<b>8.2 Types of inspection documents .....</b>	<b>17</b>
<b>8.3 Summary of inspections .....</b>	<b>18</b>
<b>8.4 Intermediary supply .....</b>	<b>18</b>
<b>9 Frequency of testing and preparation of samples and test pieces.....</b>	<b>18</b>
<b>9.1 Frequency of test.....</b>	<b>18</b>
<b>9.1.1 Chemical analysis.....</b>	<b>18</b>

<b>9.1.2</b>	<b>Tensile test and impact test .....</b>	<b>19</b>
<b>9.1.3</b>	<b>Testing the weld seam of welded hollow sections .....</b>	<b>19</b>
<b>9.1.4</b>	<b>Testing of the corner regions for rectangular hollow sections .....</b>	<b>19</b>
<b>9.2</b>	<b>Selection and preparation of samples for product analysis .....</b>	<b>19</b>
<b>9.3</b>	<b>Location of samples and orientation of tensile test pieces .....</b>	<b>19</b>
<b>9.4</b>	<b>Location of samples and orientation of impact test pieces .....</b>	<b>20</b>
<b>9.5</b>	<b>Preparation of test pieces for mechanical tests .....</b>	<b>20</b>
<b>9.5.1</b>	<b>General .....</b>	<b>20</b>
<b>9.5.2</b>	<b>Preparation of tensile test pieces .....</b>	<b>20</b>
<b>9.5.3</b>	<b>Preparation of impact test pieces .....</b>	<b>20</b>
<b>10</b>	<b>Test methods .....</b>	<b>21</b>
<b>10.1</b>	<b>Chemical analysis .....</b>	<b>21</b>
<b>10.2</b>	<b>Mechanical tests .....</b>	<b>21</b>
<b>10.2.1</b>	<b>Test temperatures .....</b>	<b>21</b>
<b>10.2.2</b>	<b>Tensile test .....</b>	<b>21</b>
<b>10.2.3</b>	<b>Impact test .....</b>	<b>22</b>
<b>10.3</b>	<b>Visual inspection and dimensional check .....</b>	<b>22</b>
<b>10.4</b>	<b>Non-destructive tests .....</b>	<b>22</b>
<b>10.4.1</b>	<b>General .....</b>	<b>22</b>
<b>10.4.2</b>	<b>NDT for the weld seam of HFW hollow sections .....</b>	<b>22</b>
<b>10.4.3</b>	<b>Full peripheral NDT for seamless hollow sections .....</b>	<b>23</b>
<b>10.4.4</b>	<b>Ultrasonic testing for laminar imperfections .....</b>	<b>23</b>
<b>10.4.5</b>	<b>NDT for surface quality .....</b>	<b>23</b>
<b>10.5</b>	<b>Retests, sorting and reprocessing .....</b>	<b>23</b>
<b>11</b>	<b>Marking and bundling .....</b>	<b>23</b>
<b>11.1</b>	<b>Die stamping and paint marking .....</b>	<b>23</b>
<b>11.2</b>	<b>Bundling .....</b>	<b>23</b>
<b>12</b>	<b>Options .....</b>	<b>24</b>
<b>Annex A</b>	<b>(normative when Option 1 is specified by the purchaser) Further details of steel manufacturing procedures to be supplied by the manufacturer .....</b>	<b>37</b>
<b>Annex B</b>	<b>(normative when Option 17 is specified by the purchaser) Weldability testing and mechanical testing of butt welds .....</b>	<b>38</b>
<b>B.1</b>	<b>General requirements .....</b>	<b>38</b>
<b>B.2</b>	<b>Welding processes and procedure .....</b>	<b>38</b>
<b>B.3</b>	<b>Butt-weld requirements .....</b>	<b>39</b>
<b>B.3.1</b>	<b>General .....</b>	<b>39</b>
<b>B.3.2</b>	<b>Test piece dimensions .....</b>	<b>39</b>
<b>B.3.3</b>	<b>Bevel detail .....</b>	<b>40</b>
<b>B.3.4</b>	<b>Welding processes .....</b>	<b>40</b>
<b>B.3.5</b>	<b>Nominal heat input .....</b>	<b>40</b>
<b>B.3.6</b>	<b>Heat treatment .....</b>	<b>41</b>
<b>B.3.7</b>	<b>Dehydrogenation of test pieces .....</b>	<b>41</b>
<b>B.4</b>	<b>Mechanical testing .....</b>	<b>42</b>
<b>B.4.1</b>	<b>General .....</b>	<b>42</b>
<b>B.4.2</b>	<b>Charpy V-notch impact tests .....</b>	<b>43</b>

**EN 10225-3:2019+A1:2023 (E)**

<b>B.4.3 Fracture mechanic test .....</b>	<b>44</b>
<b>B.4.4 Macrohardness .....</b>	<b>45</b>
<b>B.4.5 Cross-weld tensile test .....</b>	<b>46</b>
<b>Annex C (normative when Option 17 is specified by the purchaser) Weldability testing - Bead-on-plate.....</b>	<b>51</b>
<b>C.1 General.....</b>	<b>51</b>
<b>C.2 Test material dimension .....</b>	<b>51</b>
<b>C.3 Welding method .....</b>	<b>51</b>
<b>C.4 Test condition .....</b>	<b>51</b>
<b>C.5 Specific test requirements: macrosection and hardness tests .....</b>	<b>52</b>
<b>Annex D (normative when Option 17 is specified by the purchaser) Weldability testing – Controlled thermal severity tests (CTS) .....</b>	<b>54</b>
<b>D.1 General.....</b>	<b>54</b>
<b>D.2 Test block dimensions .....</b>	<b>54</b>
<b>D.3 General welding details .....</b>	<b>54</b>
<b>D.3.1 Anchor welds .....</b>	<b>54</b>
<b>D.3.2 Test welds .....</b>	<b>54</b>
<b>D.4 Evaluation of the test welds .....</b>	<b>55</b>
<b>D.5 Hardness testing.....</b>	<b>55</b>
<b>Annex E (informative) Prequalification of steels for offshore structures operating in arctic areas .....</b>	<b>61</b>
<b>Bibliography.....</b>	<b>62</b>

## European foreword

This document (EN 10225-3:2019+A1:2023) has been prepared by Technical Committee CEN/TC 459/SC 3 "Structural steels other than reinforcements", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2023, and conflicting national standards shall be withdrawn at the latest by November 2023.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

EN 10225-3:2019, together with EN 10225-1:2019, EN 10225-2:2019, and EN 10225-4:2019, superseded EN 10225:2009.

This document EN 10225-3:2019+A1:2023 supersedes EN 10225-3:2019.

This document includes Amendment 1 approved by CEN on 7 April 2023.

The start and finish of text introduced or altered by amendment is indicated in the text by tags  .

This European Standard consists of the following parts, under the general title '*Weldable structural steels for fixed offshore structures – Technical delivery conditions*':

- Part 1: Plates
- Part 2: Sections
- Part 3: Hot finished hollow sections
- Part 4: Cold formed welded hollow sections

In comparison to the previous edition EN 10225:2009 the following technical changes were made:

- split of the standard in four parts;
- the steel names were adapted to EN 10027-1;
- former grades of group 3 are no longer listed, new options with the same enhanced properties have been introduced (*Options 2 and 3*);
- an informative Annex E was added for the prequalification of steels for fixed offshore structures in arctic areas.

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

**EN 10225-3:2019+A1:2023 (E)**

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

## 1 Scope

This document specifies requirements for weldable structural steels made of hot finished seamless and high frequency welded hollow sections to be used in the fabrication of fixed offshore structures.

The following thickness limitations are given in this standard:

- for seamless hollow sections up to and including 65 mm;
- for HFW hollow sections up to and including 25,4 mm.

Greater thicknesses can be agreed, provided the technical requirements of this European Standard are maintained.

This European Standard is applicable to steels for offshore structures, designed to operate in the offshore sector but not to steels supplied for the fabrication of subsea pipelines, risers, process equipment, process piping and other utilities. It is primarily applicable to the North Sea Sector, but may also be applicable in other areas provided that due consideration is given to local conditions e.g. design temperature.

NOTE This document has an informative Annex E on the prequalification of steels for fixed offshore structures in arctic areas.

Minimum yield strengths up to 770 MPa are specified together with impact properties at temperatures down to -40 °C.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1011-1, *Welding — Recommendations for welding of metallic materials — Part 1: General guidance for arc welding*

EN 10020, *Definition and classification of grades of steel*

EN 10021, *General technical delivery conditions for steel products*

EN 10027-1, *Designation systems for steels — Part 1: Steel names*

EN 10027-2, *Designation systems for steels — Part 2: Numerical system*

EN 10079, *Definition of steel products*

EN 10164, *Steel products with improved deformation properties perpendicular to the surface of the product — Technical delivery conditions*

EN 10168, *Steel products — Inspection documents — List of information and description*

EN 10204, *Metallic products — Types of inspection documents*

EN 10210-2, *Hot finished structural hollow sections of non-alloy and fine grain steels — Part 2: Tolerances, dimensions and sectional properties*

CEN/TR 10261, *Iron and steel — European standards for the determination of chemical composition*

**EN 10225-3:2019+A1:2023 (E)**

EN ISO 148-1, *Metallic materials — Charpy pendulum impact test — Part 1: Test method (ISO 148-1)*

EN ISO 377, *Steel and steel products — Location and preparation of samples and test pieces for mechanical testing (ISO 377)*

EN ISO 643, *Steels — Micrographic determination of the apparent grain size (ISO 643)*

EN ISO 2566-1, *Steel — Conversion of elongation values — Part 1: Carbon and low alloy steels (ISO 2566-1)*

EN ISO 4063, *Welding and allied processes — Nomenclature of processes and reference numbers (ISO 4063)*

EN ISO 4136, *Destructive tests on welds in metallic materials — Transverse tensile test (ISO 4136)*

EN ISO 4885, *Ferrous materials — Heat treatments — Vocabulary (ISO 4885)*

EN ISO 6507-1, *Metallic materials — Vickers hardness test — Part 1: Test method (ISO 6507-1)*

EN ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature (ISO 6892-1)*

EN ISO 6947, *Welding and allied processes — Welding positions (ISO 6947)*

EN ISO 8492, *Metallic materials — Tube — Flattening test (ISO 8492)*

EN ISO 9712, *Non-destructive testing — Qualification and certification of NDT personnel (ISO 9712)*

EN ISO 10893-2, *Non-destructive testing of steel tubes — Part 2: Automated eddy current testing of seamless and welded (except submerged arc-welded) steel tubes for the detection of imperfections (ISO 10893-2)*

EN ISO 10893-3, *Non-destructive testing of steel tubes — Part 3: Automated full peripheral flux leakage testing of seamless and welded (except submerged arc-welded) ferromagnetic steel tubes for the detection of longitudinal and/or transverse imperfections (ISO 10893-3)*

EN ISO 10893-5, *Non-destructive testing of steel tubes — Part 5: Magnetic particle inspection of seamless and welded ferromagnetic steel tubes for the detection of surface imperfections (ISO 10893-5)*

EN ISO 10893-8, *Non-destructive testing of steel tubes — Part 8: Automated ultrasonic testing of seamless and welded steel tubes for the detection of laminar imperfections (ISO 10893-8)*

EN ISO 10893-9, *Non-destructive testing of steel tubes — Part 9: Automated ultrasonic testing for the detection of laminar imperfections in strip/plate used for the manufacture of welded steel tubes (ISO 10893-9)*

EN ISO 10893-10, *Non-destructive testing of steel tubes — Part 10: Automated full peripheral ultrasonic testing of seamless and welded (except submerged arc-welded) steel tubes for the detection of longitudinal and/or transverse imperfections (ISO 10893-10)*

EN ISO 10893-11, *Non-destructive testing of steel tubes — Part 11: Automated ultrasonic testing of the weld seam of welded steel tubes for the detection of longitudinal and/or transverse imperfections (ISO 10893-11)*

EN ISO 14284, *Steel and iron — Sampling and preparation of samples for the determination of chemical composition (ISO 14284)*

EN ISO 15614-1, *Specification and qualification of welding procedures for metallic materials — Welding procedure test — Part 1: Arc and gas welding of steels and arc welding of nickel and nickel alloys (ISO 15614-1)*

ISO 11484, *Steel products — Employer's qualification system for non-destructive testing (NDT) personnel*

ISO 12135, *Metallic materials — Unified method of test for the determination of quasistatic fracture toughness*

ISO 15653, *Metallic materials — Method of test for the determination of quasistatic fracture toughness of welds*

**koniec náhľadu – text ďalej pokračuje v platenej verzii STN**