

STN	Plastové kompozity vystužené vláknami Stanovenie tlakových vlastností v rovine výstuže (ISO 14126: 2023)	STN EN ISO 14126 64 0668
------------	---	--

Fibre-reinforced plastic composites - Determination of compressive properties in the in-plane direction (ISO 14126:2023)

Táto norma obsahuje anglickú verziu európskej normy.
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 12/23

Obsahuje: EN ISO 14126:2023, ISO 14126:2023

Oznámením tejto normy sa ruší
STN EN ISO 14126 (64 0668) z októbra 2001

137878



EUROPEAN STANDARD

EN ISO 14126

NORME EUROPÉENNE

EUROPÄISCHE NORM

October 2023

ICS 83.120

Supersedes EN ISO 14126:1999, EN ISO
14126:1999/AC:2002

English Version

Fibre-reinforced plastic composites - Determination of compressive properties in the in-plane direction (ISO 14126:2023)

Composites plastiques renforcés de fibres -
Détermination des caractéristiques en compression
dans le plan (ISO 14126:2023)

Faserverstärkte Kunststoffe - Bestimmung der
Druckeigenschaften in der Laminebene (ISO
14126:2023)

This European Standard was approved by CEN on 5 October 2023.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

EN ISO 14126:2023 (E)

Contents	Page
European foreword.....	3

European foreword

This document (EN ISO 14126:2023) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by SIS.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2024, and conflicting national standards shall be withdrawn at the latest by April 2024.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 14126:1999, EN ISO 14126:1999/AC:2002.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Endorsement notice

The text of ISO 14126:2023 has been approved by CEN as EN ISO 14126:2023 without any modification.

**INTERNATIONAL
STANDARD**

**ISO
14126**

Second edition
2023-10

**Fibre-reinforced plastic composites —
Determination of compressive
properties in the in-plane direction**

*Composites plastiques renforcés de fibres — Détermination des
caractéristiques en compression dans le plan*



Reference number
ISO 14126:2023(E)

© ISO 2023

ISO 14126:2023(E)**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Principle	3
5 Apparatus	4
5.1 Test machine.....	4
5.1.1 General.....	4
5.1.2 Speed of testing.....	4
5.1.3 Load measurement.....	4
5.2 Strain measurement.....	4
5.3 Micrometer.....	5
5.4 Loading fixtures.....	5
5.4.1 General.....	5
5.4.2 Method 1: Shear loading.....	5
5.4.3 Method 2: Combined loading.....	7
6 Test specimens	8
6.1 Shape and dimensions.....	8
6.1.1 Type A specimen.....	8
6.1.2 Type B specimen.....	9
6.2 Preparation.....	10
6.2.1 General.....	10
6.2.2 End-tab material.....	10
6.2.3 Application of end tabs to specimens.....	10
6.2.4 Machining the specimens.....	10
6.3 Checking specimen quality.....	10
6.4 Anisotropy.....	11
7 Number of test specimens	11
8 Conditioning	11
9 Procedures	11
10 Expression of results	13
10.1 Compressive strength calculation.....	13
10.2 Compressive modulus calculation.....	13
10.3 Compressive failure strain calculation.....	14
10.4 Statistical parameters.....	14
10.5 Significant figures.....	14
11 Precision	14
12 Test report	15
Annex A (normative) Alignment of specimen and loading train	16
Annex B (normative) Specimen preparation	17
Annex C (informative) Compression fixtures for method 1	19
Annex D (informative) Compression fixtures for method 2	21
Annex E (informative) Euler buckling criteria	25
Annex F (informative) Predicted tab length	26

ISO 14126:2023(E)

Annex G (informative) Recommendations for strain and bending measurements using digital image correlation (DIC)	27
Bibliography	30

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 13, *Composites and reinforcement fibres*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 14126:1999), which has been technically revised.

The main changes are as follows:

- a new normative [Annex A](#), alignment of specimen and loading train, has been added and subsequent annexes have been renumbered;
- [Annex B](#), specimen preparation, is now normative to emphasise the importance of producing good quality specimens;
- two new informative [Annexes F](#) and [G](#) have been added.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

ISO 14126:2023(E)

Introduction

This document, originally published in 1999, was based on ISO 8515^[1] with the scope extended from glass-fibre reinforcement to include all fibre-reinforced plastic composites, such as composites based on carbon and aramid fibres. Other source documents consulted included ASTM D 3410^[2], SACMA SRM1^[3], prEN 2850^[4], CRAG 400^[5], DIN 65380^[6] and JIS K7076^[7]. Several different types of anti-buckling fixtures/loading jigs, different materials and different specimen sizes are covered by these source documents, although all are parallel-sided coupons. New or modified geometry support jigs are still being developed, for example in JIS K7018^[8].

This document harmonizes and rationalizes the current situation by:

- a) concentrating on the quality of the test by limiting the maximum bending strain allowable (i.e. 10 % between 10 % and 90 % of the maximum load, as recommended by ASTM), so that an axial-load case can be assumed;
- b) standardizing on two related specimen designs, one principally for aerospace type unidirectional pre-impregnated materials (i.e. Type A) and one for other materials/formats (i.e. Types B1/B2). The chosen specimen design can be used with different loading fixtures;
- c) defining acceptable failure criteria (e.g. avoiding within grip failures);
- d) including an equation for determining the specimen minimum thickness to avoid Euler buckling proposed by ASTM for harmonization purposes (taken from ASTM D 3410^[2] in a modified form);
- e) allowing any design of support/loading fixture to be used that meets the above bending requirements, using different principles of loading (i.e. essentially shear and combined loading);
- f) ensuring that the test specimen and loading/support fixture are well aligned (see [Annex A](#));
- g) concentrating on the quality of specimen preparation (see [Annex B](#));
- h) including guidance on the use of digital image correlation (DIC) for strain and bending measurements (see [Annex G](#));

NOTE 1 Compression properties measured in the through-thickness direction (direction 3 in [Figure 1](#)) are covered by ISO 20975-1^[9].

NOTE 2 Compression properties of rigid plastics having only unaligned short (<7,5 mm) fibres or no fibre content [rather than long (>7,5 mm) discontinuous or continuous fibres] is covered by ISO 604^[10].

Fibre-reinforced plastic composites — Determination of compressive properties in the in-plane direction

1 Scope

1.1 This document specifies methods for determining the compressive properties, in directions parallel to the plane of lamination, of fibre-reinforced plastic composites, based on thermosetting or thermoplastic matrices. The compressive properties are of interest for specifications and quality-control purposes. The test specimens are machined from a flat test plate, or from suitable finished or semi-finished products.

1.2 Two loading methods and two types of specimen are described.

The loading methods are:

- Method 1: provides shear loading of the specimen (gauge length unsupported)
- Method 2: provides combined loading of the specimen (gauge length unsupported)

NOTE For tabbed specimens loaded using method 2, load is transferred through a combination of end-loading and shear-loading through the tabs.

The specimen designs are:

- Type A specimen: rectangular cross-section, fixed thickness, end-tabbed (mainly for aerospace style prepregates (~ 0,125 mm ply thickness))
- Type B specimen: rectangular cross-section, range of thicknesses, untabbed or end-tabbed, two specimen sizes are available (B1 and B2).

The Type A specimen is used for unidirectionally or biaxially reinforced materials tested in the fibre direction, where the fibres are normally either aligned continuous or aligned long (>7,5 mm) discontinuous. The Type B1 and B2 specimens are used for multi-directional aligned; mat, fabric and other multi-directionally reinforced materials where the fibre structure is more complex and/or coarser.

1.3 This document gives criteria for checking that the combination of test method and specimen design result in valid failures. It is noted that alternative test method/specimen combinations will not necessarily give the same result.

1.4 The methods specify required dimensions for the specimen. Tests carried out on specimens of other dimensions, or on specimens that are prepared under different conditions, can produce results that are not comparable. Other factors, such as the speed of testing, the support fixture used and the conditioning of the specimens, can influence the results.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 1268 (all parts), *Fibre-reinforced plastics — Methods of producing test plate*

ISO 14126:2023(E)

ISO 2602, *Statistical interpretation of test results — Estimation of the mean — Confidence interval*

ISO 7500-1, *Metallic materials — Calibration and verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Calibration and verification of the force-measuring system*

ISO 9513, *Metallic materials — Calibration of extensometer systems used in uniaxial testing*

ISO 23788, *Metallic materials — Verification of the alignment of fatigue testing machines*

ASTM E 1012, *Standard practice for verification of testing frame and specimen alignment under tensile and compressive axial force application*

koniec náhľadu – text ďalej pokračuje v platenej verzii STN