

STN	Potrúbné systémy z plastov pre beztlakovú podzemnú dopravu povrchovej vody Nemäkčený polyvinylchlorid (PVC-U), polypropylén (PP) a polyetylén (PE) Časť 2: Požiadavky na cestné vpusty	STN EN 17670-2 64 3239
------------	---	--

Plastics piping systems for non-pressure underground conveyance of surface water - Unplasticized poly(vinyl chloride) (PVC-U), polypropylene (PP) and polyethylene (PE) - Part 2: Specification for road gullies

Táto norma obsahuje anglickú verziu európskej normy.
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 12/23

Obsahuje: EN 17670-2:2023

137902



EUROPEAN STANDARD

EN 17670-2

NORME EUROPÉENNE

EUROPÄISCHE NORM

November 2023

ICS 23.040.20; 93.030

English Version

Plastics piping systems for non-pressure underground conveyance of surface water - Unplasticized poly(vinyl chloride) (PVC-U), polypropylene (PP) and polyethylene (PE) - Part 2: Specification for road gullies

Systèmes de canalisations en plastique pour le transport souterrain sans pression des eaux de surface - Poly(chlorure de vinyle) non plastifié (PVC-U), en polypropylène (PP) et en polyéthylène (PE) - Partie 2 : Spécifications relatives aux bouches d'égout

Kunststoff-Rohrleitungssysteme für die drucklose unterirdische Ableitung von Niederschlagswasser - Weichmacherfreies Polyvinylchlorid (PVC-U), Polypropylen (PP) und Polyethylen (PE) - Teil 2: Anforderungen an Straßenabläufe

This European Standard was approved by CEN on 2 July 2023.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

EN 17670-2:2023 (E)

Contents	Page
European foreword	4
Introduction	5
1 Scope	6
2 Normative references	7
3 Terms and definitions	9
4 Symbols and abbreviations	19
4.1 Symbols	19
4.2 Abbreviations	20
5 Material	20
5.1 General	20
5.2 Compound/formulation for road gully bases	20
5.3 Compound/formulation for road gully risers	21
5.4 Compound/formulation for transition pieces	22
5.5 Compound/formulation for telescopic adaptors	22
5.6 Use of reworked material and recyclates	23
5.7 Sealing ring retaining components	23
6 General characteristics	23
6.1 Appearance	23
6.2 Colour	23
7 Geometrical characteristics	23
7.1 General	23
7.2 Dimensions of road gullies	23
7.3 Dimensions of back inlet and outlet connections to pipework	24
7.4 Depth of water seal	24
7.5 Sand trap volume	24
8 Mechanical characteristics	24
9 Physical characteristics	26
9.1 General	26
9.2 Factory fabricated components	26
10 Performance requirements	27
10.1 General performance	27
10.2 Characterization of rotationally moulded and blow moulded product submitted for performance testing	29
11 Sealing rings	29
12 Adhesives for PVC-U	29
13 Gully tops	29
14 Marking and additional documentation	29
14.1 General	29
14.2 Marking of road gullies or road gully bases	29
14.3 Minimum marking of components other than road gullies or road gully bases	30
14.4 Additional documentation	31
Annex A (normative) Test method for durability	32

A.1	General	32
A.2	Test procedure	32
A.3	Material characteristics	33
Annex B (normative)	Test method for impact resistance of road gullies or road gully bases	36
B.1	Test equipment	36
B.2	Test procedure	36
Annex C (normative)	Utilization of reworked material and recyclates	37
Annex D (normative)	Test method for structural integrity of road gully bases or assemblies	41
Annex E (normative)	Test method for dynamic loading	42
E.1	General	42
E.2	Principle	42
E.3	Apparatus (accuracy of test equipment)	45
E.4	Parallel plates	45
E.5	Supporting element	45
E.6	Dimensional measuring device	45
E.7	Load measuring device	45
E.8	Test sample	45
E.9	Conditioning	45
E.10	Procedure	45
E.11	Requirements	46
E.12	Background to dynamic test parameters	46
E.13	Test report	47
Annex F (informative)	Relationship between system performance and tested characteristics	48
Bibliography		49

EN 17670-2:2023 (E)**European foreword**

This document (EN 17670-2:2023) has been prepared by Technical Committee CEN/TC 155 “Plastics piping systems and ducting systems”, the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2024, and conflicting national standards shall be withdrawn at the latest by November 2025.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document is a supplementary standard for System Standards for plastics piping systems of a particular material for a specified application. There are a number of such System Standards.

System Standards are based on the results of the work being undertaken in ISO/TC 138 “Plastics pipes, fittings and valves for the transport of fluids”, which is a Technical Committee of the International Organization for Standardization (ISO).

They are supported by separate standards on test methods, to which references are made throughout the System Standard.

Product complying with this document are intended to collect and transfer surface water into a drain or sewer system

EN 17670 consists of the following parts under the general title *Plastics piping systems for non-pressure underground conveyance of surface water — Unplasticized poly(vinyl chloride) (PVC-U), polypropylene (PP) and polyethylene (PE)*

- *Part 1: Specification for manholes and inspection chambers* (under development);
- *Part 2: Specification for road gullies* (this document);
- *Part 3: Assessment of conformity* (CEN/TS to be developed).

Any feedback and questions on this document should be directed to the users’ national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Introduction

Road gullies for surface water have been used for many years and due to the increased requirements for surface water drainage, they are becoming more important as part of an integrated surface water management system.

The products covered by this document are intended for use as part of surface water management systems.

Road gullies intended for full encapsulation in concrete are not covered by this document.

Infiltration gullies and gullies with non-tight joints are not covered by this document.

EN 17670-2:2023 (E)

1 Scope

This document specifies the definitions and requirements for unplasticized poly(vinyl chloride) (PVC-U), polypropylene (PP), polypropylene with mineral modifier (PP-MD) or polyethylene (PE) road gullies intended for use in non-pressure underground drains and sewers for surface water having a maximum depth of 4 m from ground level to the lowest point of the internal surface of the road gully. Road gullies complying with this document are intended to be used in pedestrian or vehicular traffic areas outside the building structure.

NOTE 1 Products complying with this document can also be used in non-traffic areas.

NOTE 2 Road gullies can be subject to national regulation which limit the maximum installation depth and / or local provisions. The installer checks for compliance prior to installation.

Road gullies complying with this document are made from a prescribed set of components that are manufactured from unplasticized poly(vinyl chloride) (PVC-U), polypropylene (PP), polypropylene with mineral modifier (PP-MD) or polyethylene (PE) and assembled together.

Road gullies complying with this document may be equipped with optional devices (e.g. removable sand or silt bucket, leaf separator etc.), however the performance of these optional devices is not covered within the scope of this document.

Road gully components can be manufactured by various methods e.g. extrusion, injection moulding, rotational moulding, low-pressure moulding, blow moulding, thermoforming or fabricated.

NOTE 3 Products complying with this document can be installed in underground applications without additional static calculation.

NOTE 4 The complete road gully assembly can also include non-plastic items (near surface or surface components for example) which are not covered by this document.

NOTE 5 The complete road gully assembly can be supplied with covers, frame covers and gratings complying with the relevant part of EN 124 which are not covered by this document. However, reference is made to this document for geometrical characteristics where applicable.

NOTE 6 Road gullies can be site assembled from different components, but can also be manufactured as a single unit.

This document covers:

- road gullies with or without sand / silt trap;
- road gullies with or without water seal preventing odour release;
- road gullies where the traffic load will or will not be carried by the complete gully (resp. “Direct loaded gullies” or “Indirect loaded gullies”).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 124 (series), *Gully tops and manhole tops for vehicular and pedestrian areas*

EN 681-1, *Elastomeric seals — Materials requirements for pipe joint seals used in water and drainage applications — Part 1: Vulcanized rubber*

EN 681-2, *Elastomeric seals — Materials requirements for pipe joint seals used in water and drainage applications — Part 2: Thermoplastic elastomers*

EN 681-3, *Elastomeric seals — Materials requirements for pipe joint seals used in water and drainage applications — Part 3: Cellular materials of vulcanized rubber*

EN 681-4, *Elastomeric seals — Materials requirements for pipe joint seals used in water and drainage applications — Part 4: Cast polyurethane sealing elements*

EN 1401-1, *Plastics piping systems for non-pressure underground drainage and sewerage — Unplasticized poly(vinyl chloride) (PVC-U) — Part 1: Specifications for pipes, fittings and the system*

EN 1852-1, *Plastics piping systems for non-pressure underground drainage and sewerage — Polypropylene (PP) — Part 1: Specifications for pipes, fittings and the system*

EN 12099, *Plastics piping systems — Polyethylene piping materials and components — Determination of volatile content*

EN 12666-1, *Plastics piping systems for non-pressure underground drainage and sewerage Polyethylene (PE) — Part 1: Specifications for pipes, fittings and the system*

EN 13476-2, *Plastics piping systems for non-pressure underground drainage and sewerage — Structured-wall piping systems of unplasticized poly(vinyl chloride) (PVC-U), polypropylene (PP) and polyethylene (PE) — Part 2: Specifications for pipes and fittings with smooth internal and external surface and the system, Type A*

EN 13476-3, *Plastics piping systems for non-pressure underground drainage and sewerage — Structured-wall piping systems of unplasticized poly(vinyl chloride) (PVC-U), polypropylene (PP) and polyethylene (PE) — Part 3: Specifications for pipes and fittings with smooth internal and profiled external surface and the system, Type B*

EN 13598-1, *Plastics piping systems for non-pressure underground drainage and sewerage — Unplasticized poly(vinyl chloride) (PVC-U), polypropylene (PP) and polyethylene (PE) — Part 1: Specifications for ancillary fittings including shallow chambers*

EN 13598-2:2020, *Plastics piping systems for non-pressure underground drainage and sewerage — Unplasticized poly(vinyl chloride) (PVC-U), polypropylene (PP) and polyethylene (PE) — Part 2: Specifications for manholes and inspection chambers*

EN 14758-1, *Plastics piping systems for non-pressure underground drainage and sewerage — Polypropylene with mineral modifiers (PP-MD) — Part 1: Specifications for pipes, fittings and the system*

EN 17670-2:2023 (E)

EN ISO 580, *Plastics piping and ducting systems — Injection-moulded thermoplastics fittings — Methods for visually assessing the effects of heating (ISO 580)*

EN ISO 1043-1, *Plastics — Symbols and abbreviated terms — Part 1: Basic polymers and their special characteristics (ISO 1043-1)*

EN ISO 1133-1, *Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics — Part 1: Standard method (ISO 1133-1)*

EN ISO 1158, *Plastics — Vinyl chloride homopolymers and copolymers — Determination of chlorine content (ISO 1158)*

EN ISO 1183-1, *Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method (ISO 1183-1)*

EN ISO 1183-2, *Plastics — Methods for determining the density of non-cellular plastics — Part 2: Density gradient column method (ISO 1183-2)*

EN ISO 2507-1, *Thermoplastics pipes and fittings — Vicat softening temperature — Part 1: General test method (ISO 2507-1)*

EN ISO 3126, *Plastics piping systems — Plastics components — Determination of dimensions (ISO 3126)*

EN ISO 3127, *Thermoplastics pipes — Determination of resistance to external blows — Round-the-clock method (ISO 3127)*

EN ISO 3451-1, *Plastics — Determination of ash — Part 1: General methods (ISO 3451-1)*

EN ISO 3451-5, *Plastics — Determination of ash — Part 5: Poly(vinyl chloride) (ISO 3451-5)*

EN ISO 11357-6, *Plastics — Differential scanning calorimetry (DSC) — Part 6: Determination of oxidation induction time (isothermal OIT) and oxidation induction temperature (dynamic OIT) (ISO 11357-6)*

EN ISO 13229, *Thermoplastics piping systems for non-pressure applications — Unplasticized poly(vinyl chloride) (PVC-U) pipes and fittings — Determination of the viscosity number and K-value (ISO 13229)*

EN ISO 13254, *Thermoplastics piping systems for non-pressure applications — Test method for watertightness (ISO 13254)*

EN ISO 13259, *Thermoplastics piping systems for underground non-pressure applications — Test method for leaktightness of elastomeric sealing ring type joints (ISO 13259)*

EN ISO 13263, *Thermoplastics piping systems for non-pressure underground drainage and sewerage — Thermoplastics fittings — Test method for impact strength (ISO 13263)*

ISO 13266:2022, *Thermoplastics piping systems for non-pressure underground drainage and sewerage — Thermoplastics shafts or risers for inspection chambers and manholes — Determination of resistance against surface and traffic loading*

ISO 13267:2010, *Thermoplastics piping systems for non-pressure underground drainage and sewerage — Thermoplastics inspection chamber and manhole bases — Test methods for buckling resistance*

ISO 13268, *Thermoplastics piping systems for non-pressure underground drainage and sewerage — Thermoplastics shafts or risers for inspection chambers and manholes — Determination of ring stiffness*

koniec náhľadu – text ďalej pokračuje v platenej verzii STN

Note 1 to entry: Road gullies are not intended for man entry.

Note 2 to entry: Road gullies can be either direct loaded or indirect loaded.

3.5

direct loaded road gully

DRG

road gully where the traffic load is transferred by the body of the gully, to the soil

Note 1 to entry: An example of a DRG is shown in Figure 1.

Note 2 to entry: Typically, DRG's are installed at a maximum depth of 2 m.