

| | | |
|------------|---|---|
| STN | Nositeľné elektronické zariadenia a technológie Časť 201-2: Elektronické textílie Metódy merania základných vlastností vodivých tkanín a izolačných materiálov Oprava AC | STN EN IEC 63203-201-2/AC 35 9350 |
|------------|---|---|

Wearable electronic devices and technologies - Part 201-2: Electronic textile - Measurement methods for basic properties of conductive fabrics and insulation materials

Táto norma obsahuje anglickú verziu európskej normy.
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 02/24

Obsahuje: EN IEC 63203-201-2:2022/AC:2023, IEC 63203-201-2:2022/COR1:2023

138123

Úrad pre normalizáciu, metrológiu a skúšobníctvo Slovenskej republiky, 2024
Slovenská technická norma a technická normalizačná informácia je chránená zákonom č. 60/2018 Z. z. o technickej normalizácii v znení neskorších predpisov.

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

**EN IEC 63203-201-
2:2022/AC:2023-12**

December 2023

ICS 59.080.80; 59.080.30

English Version

**Wearable electronic devices and technologies - Part 201-2:
Electronic textile - Measurement methods for basic properties of
conductive fabrics and insulation materials
(IEC 63203-201-2:2022/COR1:2023)**

Technologies et dispositifs électroniques prêts-à-porter -
Partie 201-2: Textile électronique - Méthodes de mesure
des propriétés fondamentales des étoffes conductrices et
des matériaux isolants
(IEC 63203-201-2:2022/COR1:2023)

Tragbare elektronische Geräte und Technologien - Teil 201-
2: Elektronische Textilien - Messverfahren für die
grundlegenden Eigenschaften von leitfähigen Textilien und
Isolationswerkstoffen
(IEC 63203-201-2:2022/COR1:2023)

This corrigendum becomes effective on 8 December 2023 for incorporation in the English language version of the EN.



European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Endorsement notice

The text of the corrigendum IEC 63203-201-2:2022/COR1:2023 was approved by CENELEC as EN IEC 63203-201-2:2022/AC:2023-12 without any modification.

IEC 63203-201-2:2022/COR1:2023
© IEC 2023

– 1 –

INTERNATIONAL ELECTROTECHNICAL COMMISSION
COMMISSION ÉLECTROTECHNIQUE INTERNATIONALE

IEC 63203-201-2
Edition 1.0 2022-04

IEC 63203-201-2
Édition 1.0 2022-04

**WEARABLE ELECTRONIC DEVICES
AND TECHNOLOGIES –**

**TECHNOLOGIES ET DISPOSITIFS
ÉLECTRONIQUES PRÊTS-À-PORTER –**

**Part 201-2: Electronic textile – Measurement
methods for basic properties of conductive
fabrics and insulation materials**

**Partie 201-2: Textile électronique – Méthodes de
mesure des propriétés fondamentales des
étoffes conductrices et des matériaux isolants**

CORRIGENDUM 1

Corrections to the French version appear after the English text.

Les corrections à la version française sont données après le texte anglais.

Figure 2, Figure 3, Figure 4, and Figure 5

Replace the existing keys of the above figures (excluding values or symbols):

- 1 stretchable substrate
- 2 stretchable conductor
- 3 stretchable insulator

with the following new key:

- 1 non-conductive fabric as substrate
- 2 conductive fabric
- 3 cover insulation material

6.1.3.2.1 Procedure

Replace the existing list item a) with the following new list item a):

- a) Test specimens should be prepared as shown in Figure 2. The test specimens consist of a substrate, a rectangular **conductive fabric** of 70 mm × 210 mm, and a cover insulation layer of 70 mm × 70 mm.

The test specimen substrate shall have a margin of at least 5 mm on each side of the edges of the conductor. Dimensional errors of ±1 mm are allowed for **conductive fabric** and cover insulation layer.

6.1.3.3.1 Procedure

Replace the existing third paragraph with the following new third paragraph:

Place a 25 mm diameter electrode on the test specimen insulator layer at a pressure of 1 kg/cm² (the area of 25 mm diameter circle is 4,9 cm²; that is, the weight of the electrode is 4,9 kg). The electrode is placed at least 10 mm away from the edge of the insulator layer. Measure the breakdown voltage between electrode and **conductive fabric** with an electric breakdown tester conforming to IEC 60243-1:2013. Apply AC voltage, gradually increase the voltage and read the voltage value at which the dielectric breakdown occurs. At least five points are measured and the maximum, minimum and average values and breakdown mode of each test are recorded.

6.1.3.5.1 Procedure

Replace the existing second paragraph with the following new second paragraph:

Hold the test specimen on a horizontal insulation table with the substrate side facing upward. Place a 25 mm diameter electrode on the test specimen insulator layer at a pressure of 1 kg/cm² (the area of 25 mm diameter is 4,9 cm²; that is, the weight of the electrode is 4,9 kg). The electrode is placed at least 15 mm away from the edge of the substrate. Measure the breakdown voltage between electrode and **conductive fabric** with an electric breakdown tester conforming to IEC 60243-1:2013. Apply AC voltage, gradually increase the voltage and read the voltage value at which the dielectric breakdown occurs. At least five points are measured and the maximum, minimum and average values and breakdown mode of each test are recorded.

