

STN	Potrúbné systémy z plastov na zásobovanie vodou a na tlakové kanalizačné potrubia a stoky Polyetylén (PE) Časť 1: Všeobecne	STN EN 12201-1 64 3041
------------	--	--

Plastics piping systems for water supply, and for drains and sewers under pressure - Polyethylene (PE) - Part 1: General

Táto norma obsahuje anglickú verziu európskej normy.
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 04/24

Obsahuje: EN 12201-1:2024

Oznámením tejto normy sa ruší
STN EN 12201-1 (64 3041) z apríla 2012

138455

Úrad pre normalizáciu, metrológiu a skúšobníctvo Slovenskej republiky, 2024
Slovenská technická norma a technická normalizačná informácia je chránená zákonom č. 60/2018 Z. z. o technickej normalizácii v znení neskorších predpisov.

EUROPEAN STANDARD

EN 12201-1

NORME EUROPÉENNE

EUROPÄISCHE NORM

January 2024

ICS 23.040.20

Supersedes EN 12201-1:2011

English Version

Plastics piping systems for water supply, and for drains and sewers under pressure - Polyethylene (PE) - Part 1: General

Systèmes de canalisations en plastique pour
l'alimentation en eau et pour les branchements et les
collecteurs d'assainissement avec pression -
Polyéthylène (PE) - Partie 1: Généralités

Kunststoff-Rohrleitungssysteme für die
Wasserversorgung und für Entwässerungs- und
Abwasserdruckleitungen - Polyethylen (PE) - Teil 1:
Allgemeines

This European Standard was approved by CEN on 10 December 2023.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

EN 12201-1:2024 (E)

Contents	Page
European foreword	3
Introduction	5
1 Scope	6
2 Normative references	6
3 Terms and definitions	8
3.1 Geometrical characteristics	8
3.2 Material definitions	10
3.3 Definitions related to material characteristics	11
3.4 Definitions related to service conditions	12
3.5 Definitions related to joints	13
4 Symbols and abbreviated terms	13
4.1 Symbols	13
4.2 Abbreviated terms	14
5 Material	14
5.1 Material of the components	14
5.2 Compound	15
5.2.1 Additives and pigments	15
5.2.2 Colour	15
5.2.3 Characteristics	15
5.3 Fusion compatibility for PE 80, PE 100 and PE 100 RC materials	20
5.4 Classification and designation	20
6 Effect on water quality	21
Annex A (normative) Pressure reduction coefficients	22
Annex B (informative) Resistance to rapid crack propagation	23
B.1 General	23
B.2 Initiation	23
B.3 Parameters governing propagation/arrest	23
B.4 Test methods	24
Annex C (informative) Additional information related to the installation of PE100-RC systems for conventional and non-conventional installations	25
C.1 Pipe material	25
C.2 Installation conditions	26
Bibliography	28

European foreword

This document (EN 12201-1:2024) has been prepared by Technical Committee CEN/TC 155 “Plastics piping systems and ducting systems”, the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2024, and conflicting national standards shall be withdrawn at the latest by July 2024.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12201-1:2011.

System Standards are based on the results of the work being undertaken in ISO/TC 138 “Plastics pipes, fittings and valves for the transport of fluids”, which is a Technical Committee of the International Organization for Standardization (ISO).

They are supported by separate standards on test methods to which references are made throughout the System Standard.

The System Standards are consistent with general standards on functional requirements and on recommended practice for installation.

EN 12201 consists of the following parts:

- EN 12201-1, *Plastics piping systems for water supply, and for drains and sewers under pressure — Polyethylene (PE) — Part 1: General* (this document);
- EN 12201-2, *Plastics piping systems for water supply, and for drains and sewers under pressure — Polyethylene (PE) — Part 2: Pipes*;
- EN 12201-3, *Plastics piping systems for water supply, and for drains and sewers under pressure — Polyethylene (PE) — Part 3: Fittings*;
- EN 12201-4, *Plastics piping systems for water supply, and for drains and sewers under pressure — Polyethylene (PE) — Part 4: Valves for water supply systems*;
- EN 12201-5, *Plastics piping systems for water supply, and for drains and sewers under pressure — Polyethylene (PE) — Part 5: Fitness for purpose of the system*.

In addition, the following document provides guidance on the assessment of conformity:

- CEN/TS 12201-7, *Plastics piping systems for water supply, and for drainage and sewerage under pressure — Polyethylene (PE) — Part 7: Guidance for the assessment of conformity*.

The revision of this System Standard has been carried out to add the PE 100-RC type materials with enhanced resistance to slow crack growth. Annex C discusses the performance of this type of material and gives additional information for non-conventional installation techniques. The size range has been increased to 3 000 mm diameter, test methods have been updated, and new test methods have been added for PE 100-RC materials.

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

EN 12201-1:2024 (E)

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Introduction

This document specifies the requirements for a piping system and its components made from polyethylene (PE). The piping system is intended to be used for water supply intended for human consumption, including the conveyance of raw water prior to treatment, drains and sewers under pressure, vacuum sewer systems, and water for other purposes.

In respect of potential adverse effects on the quality of water intended for human consumption, caused by the products covered by the EN 12201 series:

- this document provides no information as to whether the products may be used without restriction in any of the Member States of the EU or EFTA;

NOTE Attention is drawn to the presence of national regulations and testing arrangements in relation to products intended for use in water supply to ensure fitness for contact with drinking water.

Requirements and test methods for components of the piping system are specified in EN 12201-2, EN 12201-3 and EN 12201-4.

Characteristics for fitness for purpose of the system are covered in EN 12201-5 [1]. CEN/TS 12201-7 [2] gives guidance for assessment of conformity.

This part of EN 12201 covers the general aspects of the plastics piping system.

EN 12201-1:2024 (E)

1 Scope

This document specifies materials and the general aspects of polyethylene (PE) pressure piping systems (mains and service pipes) for buried or above ground applications, intended for the conveyance of water for human consumption, raw water prior to treatment, drains and sewers under pressure, vacuum sewer systems, and water for other purposes, with the exception of industrial application.

NOTE 1 For PE components intended for the conveyance of water intended for human consumption and raw water prior to treatment attention is drawn to Clause 6 of this document. Components manufactured for water for other purposes, drains and sewers, and vacuum systems are possibly not suitable for water supply for human consumption.

NOTE 2 Industrial application is covered by EN ISO 15494 [6].

The intended use includes sea outfalls, laid in water and pipes suspended below bridges.

It also specifies the test parameters for the test methods referred to in this document.

In conjunction with EN 12201-2, EN 12201-3, EN 12201-4 and EN 12201-5, this document is applicable to PE pipes, fittings and valves, their joints and joints with components of PE and other materials intended to be used under the following conditions:

- a) allowable operating pressure, PFA, up to 25 bar ¹;
- b) an operating temperature of 20 °C as a reference temperature.

NOTE 3 For applications operating at constant temperatures greater than 20 °C and up to and including 50 °C, see Annex A.

The EN 12201 series covers a range of allowable operating pressures and gives requirements concerning colours.

NOTE 4 It is the responsibility of the purchaser or specifier to make the appropriate selections from these aspects, taking into account their particular requirements and any relevant national guidance or regulations and installation practices or codes.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12201-2:2024, *Plastics piping systems for water supply, and for drains and sewers under pressure — Polyethylene (PE) — Part 2: Pipes*

EN 12201-3, *Plastics piping systems for water supply, and for drains and sewers under pressure — Polyethylene (PE) — Part 3: Fittings*

EN 12201-4, *Plastics piping systems for water supply, and for drains and sewers under pressure — Polyethylene (PE) — Part 4: Valves for water supply systems*

EN 12099, *Plastics piping systems — Polyethylene piping materials and components — Determination of volatile content*

EN ISO 472, *Plastics — Vocabulary (ISO 472)*

¹ 1 bar = 0,1 MPa = 10⁵ Pa; 1 MPa = 1 N/mm².

- EN ISO 1043-1, *Plastics — Symbols and abbreviated terms — Part 1: Basic polymers and their special characteristics (ISO 1043-1)*
- EN ISO 1133-1, *Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics — Part 1: Standard method (ISO 1133-1)*
- EN ISO 1167-1, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 1: General method (ISO 1167-1)*
- EN ISO 1167-2, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 2: Preparation of pipe test pieces (ISO 1167-2)*
- EN ISO 1183-1, *Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method (ISO 1183-1)*
- EN ISO 1183-2, *Plastics — Methods for determining the density of non-cellular plastics — Part 2: Density gradient column method (ISO 1183-2)*
- EN ISO 6259-1, *Thermoplastics pipes — Determination of tensile properties — Part 1: General test method (ISO 6259-1)*
- EN ISO 6259-3, *Thermoplastics pipes — Determination of tensile properties — Part 3: Polyolefin pipes (ISO 6259-3)*
- EN ISO 9080, *Plastics piping and ducting systems — Determination of the long-term hydrostatic strength of thermoplastics materials in pipe form by extrapolation (ISO 9080)*
- EN ISO 11357-6, *Plastics — Differential scanning calorimetry (DSC) — Part 6: Determination of oxidation induction time (isothermal OIT) and oxidation induction temperature (dynamic OIT) (ISO 11357-6)*
- EN ISO 12162, *Thermoplastics materials for pipes and fittings for pressure applications — Classification, designation and design coefficient (ISO 12162)*
- EN ISO 13477, *Thermoplastics pipes for the conveyance of fluids — Determination of resistance to rapid crack propagation (RCP) — Small-scale steady-state test (S4 test) (ISO 13477)*
- EN ISO 15512, *Plastics — Determination of water content (ISO 15512)*
- EN ISO 16871, *Plastics piping and ducting systems — Plastics pipes and fittings — Method for exposure to direct (natural) weathering (ISO 16871)*
- ISO 6964, *Polyolefin pipes and fittings — Determination of carbon black content by calcination and pyrolysis — Test method*
- ISO 11413:2019, *Plastics pipes and fittings — Preparation of test piece assemblies between a polyethylene (PE) pipe and an electrofusion fitting*
- ISO 11414:2009, *Plastics pipes and fittings — Preparation of polyethylene (PE) pipe/pipe or pipe/fitting test piece assemblies by butt fusion*
- ISO 13479:2022, *Polyolefin pipes for the conveyance of fluids — Determination of resistance to crack propagation — Test method for slow crack growth on notched pipes*

EN 12201-1:2024 (E)

ISO 13953, *Polyethylene (PE) pipes and fittings — Determination of the tensile strength and failure mode of test pieces from a butt-fused joint*

ISO 13954, *Plastics pipes and fittings — Peel decohesion test for polyethylene (PE) electrofusion assemblies of nominal outside diameter greater than or equal to 90 mm*

ISO 16770, *Plastics — Determination of environmental stress cracking (ESC) of polyethylene — Full-notch creep test (FNCT)*

ISO 18488, *Polyethylene (PE) materials for piping systems — Determination of Strain Hardening Modulus in relation to slow crack growth — Test method*

ISO 18489:2015, *Polyethylene (PE) materials for piping systems — Determination of resistance to slow crack growth under cyclic loading — Cracked Round Bar test method*

ISO 18553, *Method for the assessment of the degree of pigment or carbon black dispersion in polyolefin pipes, fittings and compounds*

koniec náhľadu – text ďalej pokračuje v platenej verzii STN