

STN	Ropný a plynárenský priemysel vrátane nízkouhlíkovej energie Cementy a materiály na cementovanie sond Časť 5: Určenie zmršťovania a rozťažnosti na tvorbu kvality cementu sond (ISO 10426-5: 2024)	STN EN ISO 10426-5 45 1501
------------	---	--

Oil and gas industries including lower carbon energy - Cements and materials for well cementing - Part 5: Determination of shrinkage and expansion of well cement formulations (ISO 10426-5:2024)

Táto norma obsahuje anglickú verziu európskej normy.
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 12/24

Obsahuje: EN ISO 10426-5:2024, ISO 10426-5:2024

Oznámením tejto normy sa ruší
STN EN ISO 10426-5 (45 1501) z apríla 2006

139684



EUROPEAN STANDARD

EN ISO 10426-5

NORME EUROPÉENNE

EUROPÄISCHE NORM

October 2024

ICS 75.020; 91.100.10

Supersedes EN ISO 10426-5:2005

English Version

Oil and gas industries including lower carbon energy -
Cements and materials for well cementing - Part 5:
Determination of shrinkage and expansion of well cement
formulations (ISO 10426-5:2024)

Industries du pétrole et du gaz, y compris les énergies à faible teneur en carbone - Ciments et matériaux pour la cimentation des puits - Partie 5: Détermination du retrait et de l'expansion des formulations de ciments pour puits (ISO 10426-5:2024)

Öl- und Gasindustrie einschließlich kohlenstoffarmer Energieträger - Zemente und Materialien für die Zementation von Tiefbohrungen - Teil 5: Bestimmung der Schrumpfung und Quellung von Bohrloch-Zementmischungen bei atmosphärischem Druck (ISO 10426-5:2024)

This European Standard was approved by CEN on 22 September 2024.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

EN ISO 10426-5:2024 (E)

Contents	Page
European foreword.....	3

European foreword

This document (EN ISO 10426-5:2024) has been prepared by Technical Committee ISO/TC 67 "Oil and gas industries including lower carbon energy" in collaboration with Technical Committee CEN/TC 12 "Oil and gas industries including lower carbon energy" the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2025, and conflicting national standards shall be withdrawn at the latest by April 2025.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 10426-5:2005.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Endorsement notice

The text of ISO 10426-5:2024 has been approved by CEN as EN ISO 10426-5:2024 without any modification.



International Standard

ISO 10426-5

Oil and gas industries including lower carbon energy — Cements and materials for well cementing —

Part 5: Determination of shrinkage and expansion of well cement formulations

Industries du pétrole et du gaz, y compris les énergies à faible teneur en carbone — Ciments et matériaux pour la cimentation des puits —

Partie 5: Détermination du retrait et de l'expansion des formulations de ciments pour puits

**Second edition
2024-09**

ISO 10426-5:2024(en)**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

ISO 10426-5:2024(en)

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Determination of shrinkage or expansion under conditions of free access to water at atmospheric pressure — Annular ring test	2
4.1 General.....	2
4.2 Apparatus.....	2
4.2.1 Mould.....	2
4.2.2 Water curing bath.....	4
4.2.3 Temperature-measuring system.....	4
4.2.4 Atmospheric-pressure consistometer.....	5
4.2.5 Micrometer.....	5
4.3 Procedure.....	5
4.3.1 Preparation of the mould.....	5
4.3.2 Preparation of slurry.....	6
4.3.3 Filling of the mould.....	6
4.3.4 Test period.....	6
4.4 Measurement and calculations.....	7
5 Determination of shrinkage or expansion under impermeable condition at atmospheric pressure — Annular ring test in a re-sealable bag	9
5.1 General.....	9
5.2 Apparatus.....	9
5.2.1 General.....	9
5.2.2 Re-sealable bag.....	10
5.3 Procedure.....	10
5.4 Measurement and calculations.....	10
6 Determination of bulk shrinkage or expansion under impermeable condition and atmospheric pressure — Membrane test	10
6.1 General.....	10
6.2 Apparatus.....	11
6.2.1 Membrane.....	11
6.2.2 Water curing bath.....	11
6.2.3 Temperature-measuring system.....	11
6.2.4 Electronic scales.....	11
6.3 Procedure.....	11
6.3.1 Preparation of the membrane.....	11
6.3.2 Preparation of slurry.....	11
6.3.3 Filling of the membrane.....	11
6.3.4 Curing.....	11
6.4 Measurement and calculations.....	12
Annex A (informative) Determination of stress generated by expansion at elevated pressure and temperature	14
Annex B (informative) Determination of shrinkage or expansion under conditions of free access to water at elevated pressure — Annular ring test	20
Bibliography	22

ISO 10426-5:2024(en)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 67, *Oil and gas industries including lower carbon energy*, Subcommittee SC 3, *Drilling and completion fluids, well cements and treatment fluids*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 12, *Oil and gas industries including lower carbon energy*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 10426-5:2004), which has been technically revised.

The main changes are as follows:

- addition of the Introduction, with background information on expansion and shrinkage;
- addition of annular ring test under impermeable conditions at atmospheric pressure;
- inclusion of an informative annex describing a method to determine the stress generated by expansion under confined conditions at elevated temperature and pressure;
- inclusion of an informative annex describing the annular ring test at elevated pressure.

A list of all parts in the ISO 10426 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

ISO 10426-5:2024(en)

Introduction

When Portland cement reacts with water, there is an overall reduction in the absolute volume of components:

$$V_c + V_w > V_{ch} \quad (1)$$

where

V_c is the volume of cement;

V_w is the volume of water;

V_{ch} is the volume of cement hydrates.

In this document the absolute volume decrease $[(V_c + V_w) - V_{ch}]$ is referred to as hydration shrinkage, although in other documents it can also be referred to as chemical shrinkage, total chemical contraction, or hydration volume reduction.

Depending on the exposure conditions, presence of external stresses during setting and, most importantly, access to external water, the hydration shrinkage may lead to bulk shrinkage of the set cement.

The change in the sample dimensions is referred to as bulk shrinkage or expansion. Bulk shrinkage and expansion of the cement refer to the result of the measurement of a linear dimensional change or volume change. The volume to which all volume changes are related is the volume of the slurry immediately after mixing and emplacement in the experimental equipment. For small values of shrinkage or expansion, typically the case in well cement systems, the fractional volume dimensional change can be approximated as 3 times the fractional linear dimensional change.

Bulk shrinkage may cause:

- formation of a micro-annulus, potentially affecting cement evaluation logs;
- loss of zonal isolation leading to crossflow or sustained casing pressure;
- lack of a hydraulic seal when using cement inflatable packers;
- poor sealing of abandonment plugs.

Additives are available that can overcome the effects of hydration shrinkage and generate bulk expansion of set cement. In plug applications, bulk expansion of cement generates stress at the cement-rock or cement-formation interface. A method of measuring the stress generated by expansion in a plug-type geometry is given in [Annex A](#).

In this document, SI units are used; and where practical, U.S. customary units are included in brackets for information.

This document is based on API Technical Report 10TR 2.

Oil and gas industries including lower carbon energy — Cements and materials for well cementing —

Part 5:

Determination of shrinkage and expansion of well cement formulations

1 Scope

This document provides the methods for the testing of well cement formulations to determine the dimension changes during the curing process (cement hydration) at atmospheric and elevated pressure and the stress generated by expansion in a confined environment under elevated temperature and pressure.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

API Specification 10A, *Cements and Materials for Well Cementing*

API Recommended Practice 10B-2, *Recommended Practice for Testing Well Cements*

koniec náhľadu – text ďalej pokračuje v platenej verzii STN