

STN	Pracovná expozícia Meranie prašnosti sypkých materiálov Časť 2: Metóda rotačného bubna	STN EN 15051-2 83 3618
------------	---	--

Workplace exposure - Measurement of the dustiness of bulk materials - Part 2: Rotating drum method

Táto norma obsahuje anglickú verziu európskej normy.
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 03/26

Obsahuje: EN 15051-2:2025

Oznámením tejto normy sa ruší
STN EN 15051-2+A1 (83 3618) z júna 2017

142045



EUROPEAN STANDARD

EN 15051-2

NORME EUROPÉENNE

EUROPÄISCHE NORM

December 2025

ICS 13.040.30

Supersedes EN 15051-2:2013+A1:2016

English Version

Workplace exposure - Measurement of the dustiness of bulk materials - Part 2: Rotating drum method

Exposition sur les lieux de travail - Mesurage du
pouvoir de resuspension des matériaux pulvérulents
en vrac - Partie 2 : Méthode du tambour rotatif

Exposition am Arbeitsplatz - Messung des
Staubungsverhaltens von Schüttgütern - Teil 2:
Verfahren mit rotierender Trommel

This European Standard was approved by CEN on 26 October 2025.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

EN 15051-2:2025 (E)

Contents	Page
European foreword	3
Introduction	5
1 Scope	6
2 Normative references	6
3 Terms and definitions	6
4 Requirements	7
4.1 General	7
4.2 Conditioning of the bulk material	7
4.2.1 As-received condition	7
4.2.2 Conditioning specifications	8
4.3 Sample and environmental control	8
4.4 Moisture content	8
4.5 Bulk density	8
4.6 Test procedure	8
4.7 Replicate tests	8
4.8 In-house test powder	8
5 Rotating drum method	9
5.1 Description of test apparatus	9
5.2 Particle size-selective foams	12
5.3 Sampling filters	12
5.4 Ancillary equipment	13
5.5 Preparation of test sample	13
5.6 Preparation of test apparatus	13
5.7 Running the test apparatus	13
5.8 Weighing the foams and sampling filters	14
5.9 Determination of the inhalable, thoracic and respirable dustiness mass fractions	15
5.10 Limit of detection (LOD) and limit of quantification (LOQ)	16
6 Evaluation of dustiness	17
7 Test report	17
Annex A (normative) Flow rate and leak checks of the rotating drum	19
Annex B (informative) Characteristics of metal foams	20
B.1 General	20
B.2 Structure	20
B.3 Pore size	21
B.4 Chemical composition	21
B.5 Cell diameter	22
Annex C (informative) Test to identify outliers amongst values obtained from repeat tests	23
Annex D (informative) LOD and LOQ procedure for gravimetric sampling filters and foams	25
Bibliography	29

European foreword

This document (EN 15051-2:2025) has been prepared by Technical Committee CEN/TC 137 “Assessment of workplace exposure to chemical and biological agents”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2026, and conflicting national standards shall be withdrawn at the latest by June 2026.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 15051-2:2013+A1:2016.

EN 15051-2:2025 includes the following significant technical changes with respect to EN 15051-2:2013+A1:2016:

- the introduction was revised to better explain the purpose of dustiness testing;
- 4.2.2: Inclusion of conditioning specifications for standard testing and inter-comparison in addition to as received testing;
- 4.3: Change in the tolerance of relative humidity (RH): Previously, RH was specified at $(50 \pm 10) \%$ RH; now, it is specified at $(50 \pm 5) \%$;
- 4.8: Introduction of an in-house or test powder of relatively high dustiness for quality purpose and to ensure reproducibility in testing;
- 5.7: Change in the minimum of repeat tests to be carried out from three to five and specify procedure for reporting results based on the relative standard deviation.
- 5.10: Limit of detection (LOD) and limit of quantification (LOQ) has been added for the determination and reporting of LOD and LOQ of the weighing of the filters, and the 80 ppi and 20 ppi foams;
- Clause 6: In Table 1, the respirable dustiness mass fraction ($w_{R,A}$) upper limit for the very low dustiness category has been changed from $< 10 \text{ mg/m}^3$ to $< 20 \text{ mg/kg}$. As a result, the low category has been revised from $(10 \text{ to } 60) \text{ mg/m}^3$ to $(20 \text{ to } 60) \text{ mg/m}^3$;
- Annex A: Flow rate and leak check, which is normative, has been added. It provides a procedure to check, evaluate and report the flow rate and potential leaks through the rotating drum;
- Annex B (informative) for the quality control of metal foams has been added;
- Annex C (informative) provides a test to identify outliers amongst values obtained from repeat tests;
- Annex D (informative) provides an example of a procedure to evaluate the LOD and LOQ for gravimetric filters and foams.

EN 15051 *Workplace exposure — Measurement of the dustiness of bulk materials* consists of the following parts:

- *Part 1: Requirements and choice of test methods;*
- *Part 2: Rotating drum method;*

EN 15051-2:2025 (E)

— *Part 3: Continuous drop method.*

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Introduction

This document gives details of the design and operation of the rotating drum test method that categorizes the dustiness of solid bulk materials, in terms of health-related mass fractions.

The dustiness values of a specific method can be used for comparing and ranking powders and are useful for the purpose of safety by design and risk assessment. A dustiness categorization is presented to provide users (e.g. manufacturers, producers, occupational hygienists and workers) with information on the potential for dust emissions when the bulk material is handled or processed in workplaces. It provides the manufacturers of bulk materials with information that can help to improve their products. It allows the users of the bulk materials to assess the effects of pre-treatments, and also to select less dusty products, if available. It is envisaged that different branches of industry might develop their own categorization schemes using experimentally determined dustiness values of the bulk materials of interest.

However, dustiness test methods measure dust at emission source and do not consider the transportation of the airborne particles within a workplace environment to the breathing zone of a worker. Concentrations of respirable or inhalable dust in the workplace air, resulting from the processing and handling of bulk materials, will depend on a wide variety of factors (e.g. environmental factors, quantity used, engineering controls, transport of particles from source to worker's breathing zone, type of activities). Therefore, dustiness values do not provide workplace exposure concentrations.

Although this document does not discuss in detail the analysis of dust released from bulk materials (except in terms of gravimetric analysis), the test method produces samples with the potential for chemical analysis of the contents. However, it is important to understand that for a mixture, the mass percentage of a substance in the bulk material will be different (lower or higher) to the mass percentage of the same substance in the dust collected by the foams and the filter using the rotating drum.

The EN 15051 standard was originally developed in 2006 based on the results of the European project SMT4-CT96-2074 Development of a Method for Dustiness Testing (see [1]). This project investigated the dustiness of 12 bulk materials, with the intention to test as wide a range of bulk materials as possible, i.e. magnitude of dustiness, industrial sectors, chemical composition and particle size distribution. In 2013, the standard was revised based on comments from industrial users of the standard (e.g. Industrial Minerals Association), a number of research papers (for example, [2] and [3]) and the potential influence of the expanding database of dustiness results. In this revised document, the performance and characteristics of the metal foams for the sampling of the respirable fraction and important comments from industrial users of the standard have been taken into account.

For the measurement of dustiness of bulk materials that possibly contain or release nano-objects and their agglomerates and aggregates (NOAA) using the rotating drum, EN 17199-1 and EN 17199-2 apply [6, 7].

EN 15051-2:2025 (E)**1 Scope**

This document specifies the rotating drum test apparatus and associated test method for the reproducible production of dust from a bulk material under standard conditions, and the measurement of the inhalable, thoracic and respirable dustiness mass fractions, with reference to existing European standards, where relevant (see Clause 6).

This method is suitable for general bulk material handling processes, including all those processes where the bulk material is dropped, or can be dropped. It differs from the continuous drop method presented in EN 15051-3:2025 [4]. In EN 15051-2:2025 the same bulk material is repeatedly dropped, whilst in EN 15051-3:2025, the bulk material is dropped only once, but continuously.

Furthermore, this document specifies the environmental conditions, the sample handling and analytical procedures, and the method of calculating and presenting the results. A categorization scheme for dustiness is specified, to provide a standardized way to express and communicate the results to users of the bulk materials.

This document is applicable to powdered, granular or pelletized bulk materials. A standard sample volume is used.

This document does not apply to test the dust released when solid bulk materials are mechanically reduced (e.g. cut, crushed).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1540, *Workplace exposure — Terminology*

EN 15051-1:2025, *Workplace exposure — Measurement of the dustiness of bulk materials — Part 1: Requirements and choice of test methods*

ISO 15767, *Workplace atmospheres — Controlling and characterizing uncertainty in weighing collected aerosols*

koniec náhľadu – text ďalej pokračuje v platenej verzii STN