

<b>STN</b>	<b>Spekané karbidy Palmqvistova skúška húževnatosti (ISO 28079: 2026)</b>	<b>STN EN ISO 28079</b>  42 0875
------------	---	--

Hardmetals - Palmqvist toughness test (ISO 28079:2026)

Táto norma obsahuje anglickú verziu európskej normy.  
This standard includes the English version of the European Standard.

Táto norma bola oznámená vo Vestníku ÚNMS SR č. 03/26

Obsahuje: EN ISO 28079:2026, ISO 28079:2026

**142323**



EUROPEAN STANDARD

**EN ISO 28079**

NORME EUROPÉENNE

EUROPÄISCHE NORM

January 2026

ICS 77.040.10; 77.160

English Version

**Hardmetals - Palmqvist toughness test (ISO 28079:2026)**Métaux-durs - Essai de ténacité de Palmqvist (ISO  
28079:2026)Hartmetalle - Palmqvist-Härteprüfung (ISO  
28079:2026)

This European Standard was approved by CEN on 10 January 2026.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.

EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

**EN ISO 28079:2026 (E)**

<b>Contents</b>	<b>Page</b>
<b>European foreword.....</b>	<b>3</b>

## **European foreword**

This document (EN ISO 28079:2026) has been prepared by Technical Committee ISO/TC 119 "Powder metallurgy" in collaboration with CCMC.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2026, and conflicting national standards shall be withdrawn at the latest by July 2026.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

## **Endorsement notice**

The text of ISO 28079:2026 has been approved by CEN as EN ISO 28079:2026 without any modification.



# International Standard

**ISO 28079**

## Hardmetals — Palmqvist toughness test

*Métaux-durs — Essai de ténacité de Palmqvist*

**Second edition  
2026-01**

## ISO 28079:2026(en)



### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2026

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

**ISO 28079:2026(en)****Contents**

Page

<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>v</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms, definitions and symbols</b> .....	<b>1</b>
3.1 Terms and definitions.....	1
3.2 Symbols.....	1
<b>4 Test pieces and sample preparation</b> .....	<b>2</b>
4.1 Test piece size and sampling.....	2
4.2 Surface preparation.....	2
4.3 Surface condition.....	2
<b>5 Apparatus</b> .....	<b>3</b>
5.1 General.....	3
5.2 Indentation.....	3
5.3 Indentation and crack measurement.....	3
<b>6 Procedure and conditions of testing</b> .....	<b>3</b>
6.1 Indentations.....	3
6.2 Indentation and crack length measurement.....	3
6.3 Test validity.....	5
<b>7 Analysis</b> .....	<b>5</b>
7.1 Vickers hardness.....	5
7.2 Toughness.....	5
<b>8 Measurement uncertainty</b> .....	<b>6</b>
<b>9 Test report</b> .....	<b>6</b>
<b>Annex A (informative) Report pro forma — Palmqvist toughness measurements on hardmetals</b> .....	<b>7</b>
<b>Bibliography</b> .....	<b>9</b>

**ISO 28079:2026(en)****Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at [www.iso.org/patents](http://www.iso.org/patents). ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 119, *Powder metallurgy*, Subcommittee SC 4, *Sampling and testing methods for hardmetals*, in collaboration with the European Committee for Standardization (CEN), in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 28079:2009), which has been technically revised.

The main changes are as follows:

- References to ISO 3878 replaced by ISO 6507-1, ISO 6507-2 and ISO 6507-3;
- [Clause 3](#), symbol “H” for hardness replaced by “HV” for Vickers Hardness;
- [Subclause 4.1](#), 2<sup>nd</sup> paragraph: last sentence deleted;
- Modification of the note in [4.1](#);
- [Subclause 4.2](#) “Surface preparation” modified;
- Modification in [4.3](#) “surface condition”;
- [Formula 1](#) modified, according to modifications in [Clause 3](#);
- Deletion of the note in [7.1](#);
- Calculation example for [Formula \(10\)](#) added as [A.3](#).

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

**ISO 28079:2026(en)****Introduction**

Good test methods are those which enable a user or manufacturer to clearly discriminate between different materials.

Fracture toughness values are required for three reasons:

- for product design and performance assessment;
- for selection of materials;
- for quality control.

A specific International Standard for the toughness of hardmetals<sup>1)</sup> has not been developed to date, primarily because of the difficulty of introducing stable precracks into these tough but hard materials. However, Palmqvist tests for toughness are widely used because of their perceived apparent simplicity. Cracks are formed at the corners of Vickers hardness indentations and these can be used to calculate a nominal surface toughness value. This value is sensitive to the method of measurement and to the method of surface preparation of the sample. This document outlines good practice to minimize uncertainties due to these issues.

There are several possible methods for the measurement of the fracture toughness of hardmetals. The results can be expressed either as a stress intensity factor, in  $\text{MN}\cdot\text{m}^{-3/2}$ , or as a fracture surface energy, in  $\text{J}\cdot\text{m}^{-2}$ . The range of values for typical WC/Co hardmetals is from  $7 \text{ MN}\cdot\text{m}^{-3/2}$  to  $25 \text{ MN}\cdot\text{m}^{-3/2}$ . There is a general inverse trend of hardness against fracture toughness (see References [1] and [2]).

When applied unqualified to hardmetals, “toughness” can have several meanings.

- a) Plane-strain fracture toughness,  $K_{Ic}$ , in  $\text{MN}\cdot\text{m}^{-3/2}$ , is a value obtained from tests on specimens with appropriate geometries for plane-strain conditions and containing a well-defined geometry of crack. There is no standard method for hardmetals and different organizations use different test methods for introducing the precrack.
- b) Strain-energy release rate (or work of fracture),  $G$ , is an alternative expression for toughness, often obtained by converting plane-strain toughness,  $K$ , to  $G$  [i.e.  $G = K^2/E(1 - \nu^2)$ , where  $E$  is Young's modulus and  $\nu$  is Poisson's ratio].  $G$  has units of  $\text{J}\cdot\text{m}^{-2}$ . Again, there is no standard method.
- c) Palmqvist toughness,  $W$ , is a value obtained by measuring the total length of cracks emanating from the four corners of a Vickers hardness indentation. For a given indentation load, the shorter the crack, the tougher the hardmetal.
- d) Finally, toughness is also widely used, in a loose sense, to describe the empirical relation between perceived resistance to dynamic impacts. This is neither standardized nor quantified, but is clearly important for many industrial applications of hard materials. Also, principally for hardmetals, it can be more realistically assessed through either fatigue tests or high-rate strength tests, rather than a conventional fracture toughness test.

There is a considerable body of published information on Palmqvist toughness tests for hardmetals (see References [5] to [29]). Palmqvist toughness,  $W$ , is a toughness value obtained by measuring the crack lengths at the corners of a Vickers indentation. It can be evaluated by making indentations either at a single load, usually 30 kgf, or from the inverse of the slope of a plot of crack length against load for a range of applied loads. For hardmetals, the crack depth profile is normally of the Palmqvist type, i.e. independent shallow arcs emanating from each indentation corner. The measurement of surface crack length is, however, open

---

1) Terminology — There is a range of terms used for this type of material, especially including cemented carbides and/or cermets, as well as hardmetals. The word “hardmetals” has been used in this document. It includes all hard materials based on carbides that are bonded with a metal. In ISO 3252 terminology, “hardmetal” is stated to be “a sintered material characterized by high strength and wear resistance, comprising carbides of refractory metals as the main component together with a metallic binder phase”. “Cemented carbide” is synonymous with “hardmetal”. A “cermet” is defined as “a sintered material containing at least one metallic phase and at least one non-metallic phase, generally of a ceramic nature”.

**ISO 28079:2026(en)**

to operator error. It is widely recognized that test surfaces are carefully prepared to remove the effects of residual surface stresses (see Reference [8]). The test also has a poor fracture-mechanics pedigree because of the uncertainties associated with residual stresses introduced by the indentation.

One advantage of the Palmqvist method is that parallel measurements are made of sample hardness, which is required for quality-control purposes. The crack length, and thus toughness measurements, do not therefore require much more effort and can yield equally useful material characterization data, provided the measurements are obtained carefully in line with the methods proposed in this document.

This document is based on a “Good Practice Guide for the Measurement of Palmqvist Toughness” published by the UK National Physical Laboratory in 1998. This document recommends good practice to minimize levels of uncertainty in the measurement process. The procedure has been validated through underpinning technical work within the VAMAS<sup>2)</sup> framework (see Reference [29]). An interlaboratory exercise was conducted to generate underpinning technical information on toughness tests for hardmetals. More than ten industrial organizations participated, either by correspondence, supply of materials or by conducting tests. Eight organizations were able to complete Palmqvist tests. Good statistics were obtained on the Palmqvist data that enabled a quantitative assessment of uncertainties to be performed for this relatively simple test. Single-edge precracked beam data was thought to be closest to the “true” value, and the mean values from the Palmqvist test data compared reasonably well with these results. However, care was needed in test piece preparation to ensure a good correlation between data from the Palmqvist tests and the single-edge precracked beam results.

---

2) VAMAS, Versailles Project on Advanced Materials and Standards, supports trade in high technology products through international collaborative projects aimed at providing the technical basis for drafting codes of practice and specifications for advanced materials. The scope of the collaboration embraces all agreed aspects of enabling science and technology, i.e. databases, test methods, design methods, and materials technology, which are required as a precursor to the drafting of standards for advanced materials. VAMAS activity emphasises collaboration on pre-standards measurement research, intercomparison of test results, and consolidation of existing views on priorities for standardization action. Through this activity, VAMAS fosters the development of internationally acceptable standards for advanced materials by the various existing standards agencies.

# Hardmetals — Palmqvist toughness test

## 1 Scope

This document specifies a method for measuring the Palmqvist toughness of hardmetals and cermets at room temperature by an indentation method. This document is applicable to a measurement of toughness, called Palmqvist toughness, calculated from the total length of cracks emanating from the corners of a Vickers hardness indentation, and it is intended for use with metal-bonded carbides and carbonitrides (normally called hardmetals, cermets or cemented carbides). The test procedures specified in this document are applicable for use at ambient temperatures, but can be extended to higher or lower temperatures by agreement. The test procedures specified in this document are also applicable for use in a normal laboratory-air environment. This document is not applicable for use in corrosive environments, such as strong acids or seawater.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6507-1, *Metallic materials — Vickers hardness test — Part 1: Test method*

ISO 6507-2, *Metallic materials — Vickers hardness test — Part 2: Verification and calibration of testing machines*

ISO 6507-3, *Metallic materials — Vickers hardness test — Part 3: Calibration of reference blocks*

**koniec náhľadu – text ďalej pokračuje v platenej verzii STN**